Chloride Leaching for Chalcopyrite

by

Jenni Anne Liddicoat

B.Sc., The University of Sydney, 1997

A THESIS SUBMITTED IN PARTIAL FULFILMENT OF
THE REQUIREMENTS FOR THE DEGREE OF

MASTER OF SCIENCE

in

THE FACULTY OF GRADUATE STUDIES

Department of Metals and Materials Engineering

We accept this thesis as conforming
to the required standard

The University of British Columbia

December 2003

© Jenni Liddicoat, 2003

In presenting this thesis in partial fulfilment of the requirements for an advanced degree at the University of British Columbia, I agree that the Library shall make it freely available for reference and study. I further agree that permission for extensive copying of this thesis for scholarly purposes may be granted by the head of my department or by his or her representatives. It is understood that copying or publication of this thesis for financial gain shall not be allowed without my written permission.

Department of Metals and Materials Engineering

The University of British Columbia
Vancouver, Canada

Date 2nd December 2003

ABSTRACT

Two new process flowsheets have been developed which combine chloride leaching for chalcopyrite with solvent extraction, to selectively transfer copper to a conventional sulfate electrowinning circuit. Both models were designed to address the common chloride hydromet problem of product impurity, and they differ with respect to iron deportment. Chloride leaching offers significant advantages for copper hydrometallurgy including increased solubility, increased rates of leaching and stabilization of Cu(I) through chloride complexation. A mass balance was completed for both models and enabled the determination of recycle leach liquor concentrations of copper and iron species for the countercurrent leach tests.

To assist with solid-liquid (S-L) separation a bench size mini-thickener was designed and tested in the continuous countercurrent leach experiments. One mini-thickener was used for leach stage 1 (LS1) S-L separation in a smooth, clean and semi-continuous manner. The leach tests were performed using a chalcopyrite concentrate, from Antamina in northern Peru, which contained a low to moderate amount of gangue material.

The successful completion of mass balances for both circuits demonstrates potential for these two new chloride leach flowsheets particularly in addressing current purification difficulties and waste management issues.

The goethite model leach experiments, in which oxygen was injected to leach stage 2 (LS2) to aid iron oxidation and precipitation, were unsuccessful in achieving >95% copper extraction in the atmospheric conditions tested. It is believed that further intensification of conditions could produce >95% copper extraction.

The hematite model, in which no air is added to the leach, was successful in demonstrating the effect of varying particle size, leach time and temperature to achieve copper extractions >95%. Three hematite process variations achieved >95% copper extraction and these involved fine grinding of the concentrate, and either a 3h residence

time at 95C (98% extraction), a 2h residence time at 95C (96% extraction) or a 3h residence time at 85C (96% extraction).

One final experiment, based on the hematite model, was successfully conducted at optimum leach conditions employing Rosario concentrate from Chile, which contains chalcopyrite, chalcocite and a significant amount of pyrite. Copper extraction exceeded 99% for this experiment.

TABLE OF CONTENTS

ABSTRACT.....	ii
TABLE OF CONTENTS.....	iv
LIST OF FIGURES	vii
LIST OF TABLES.....	ix
ACKNOWLEDGEMENTS.....	xi
1 INTRODUCTION	1
2 LITERATURE REVIEW	4
2.1 Aqueous copper and chloride chemistry.....	4
2.1.1 Chloride complexes	4
2.1.2 Solubility.....	8
2.1.3. Ionic Activity	10
2.1.4 Redox Chemistry	12
2.2 Chalcopyrite leaching in chloride	17
2.2.1 Thermodynamics and kinetics	17
2.2.2 Sulfur.....	23
2.2.3. Iron Deportment.....	25
2.3 Overview of chloride leach processes for copper	29
2.4 Summary	34
3 EXPERIMENTAL.....	35
3.1 Mass balance spreadsheet preparation for the leach models	35
3.2 Feed concentrates.....	35
3.3 Feed solutions	37
3.3.1 Feed liquor for the hematite model.....	38
3.3.2 Feed liquor for the goethite model.....	38
3.3.3 Feed liquor analysis	38
3.4 Experimental Apparatus.....	39
3.4.1 Leach vessels	39
3.4.2 Temperature control.....	40
3.4.3 Solid-liquid separation	40
3.4.4 Compressed air/oxygen addition to LS2.....	43

3.5 Experimental procedures	44
3.6 pH and redox potential measurements.....	48
3.6.1 pH.....	48
3.6.2 Redox potential	49
3.7 Sampling and Analysis	49
3.7.1 Sample Collection.....	49
3.7.2 Preparation and Analysis	50
3.7.3 Calculation of copper and iron extraction.....	51
4 RESULTS AND DISCUSSION.....	52
4.1 Excel mass balance outputs for the hematite and goethite process flowsheets	52
4.1.1 The hematite process.....	53
4.1.2 The goethite process	55
4.1.3 Feed liquor outputs	57
4.2 Overview of continuous countercurrent leach experiments.....	58
4.3 Results of hematite model experiments	62
4.3.1 Potential, pH and free acid.....	63
4.3.2 Copper and iron extraction.....	66
4.3.3 Speciation.....	69
4.3.4 Hematite experiment discussion	71
4.4 Results of goethite model experiments	71
4.4.1 Potential, pH and free acid.....	73
4.4.3 Speciation.....	78
4.4.4 Goethite experiment discussion	79
4.5 Application of hematite leach model to Rosario concentrate	79
4.5.1. Potential, pH and free acid.....	80
4.5.2 Copper and iron extraction.....	81
4.6 Sulfur balance	83
4.7 Trace Metals.....	85
5 CONCLUSIONS AND RECOMMENDATIONS	86
5.1 Model mass balances	86
5.2 Implementation of the mini-thickener	86

5.3 Countercurrent leach experiments	87
5.4 Recommendations for further work	87
6. REFERENCES	89
Sample identification guide for Appendices 1 and 2	93
Appendix 1 Certificates of Analysis (IPL)	94
Appendix 2 Certificates of Analysis (ChemMet)	121
Appendix 3 Certificates of Analysis (Malvern Mastersizer)	131
Appendix 4 XRD Spectra	135
Appendix 5 Methods	136
Appendix 6 Experimental Logs	143
Appendix 7 Calculations	147
Appendix 8 Mass balances for experimental accountability	151
Appendix 9 Experimental Profiles	164

LIST OF FIGURES

Figure 1 The Hematite Process	3
Figure 2 The Goethite Process	3
Figure 3 Cu-H ₂ O Eh pH Diagram at 25°C (1 atm, 1M) [12]	6
Figure 4 Cu-Cl-H ₂ O Eh pH Diagram at 25°C (1 atm, 1M) [12]	6
Figure 5 Cu-H ₂ O Eh pH Diagram at 25°C (1 atm, Cu 1M, Cl 5M)[12]	6
Figure 6 CuCl Solubility [1]	9
Figure 7 PbCl ₂ Solubility [1]	9
Figure 8 Altered redox potentials in chloride solution [3]	13
Figure 9 Eh vs Log aCl [23]	15
Figure 10 Cu-Fe-S-H ₂ O Eh-pH diagram at 25°C [24]	18
Figure 11 Cu-Fe-S-Cl-H ₂ O Eh-pH diagram at 25°C [24]	19
Figure 12 Chloride leach processes for copper	30
Figure 13 Experimental Set-up	39
Figure 14 Mini-thickener design	42
Figure 15 Photo of mini-thickener	42
Figure 16 Photo of titanium rake	42
Figure 17 Photo of countercurrent leach set-up	44
Figure 18 Mass and volume transfers	46
Figure 19 Thickening operation	47
Figure 20 Hematite Process	53
Figure 21 Goethite Process	55
Figure 22 E profile for H4(75µm, 3h, 95C)	64
Figure 23 E profile for H5(41µm, 3h, 95C)	64
Figure 24 pH profile for H4(75µm, 3h, 95C)	64
Figure 25 pH profile for H5(41µm, 3h, 95C)	64
Figure 26 H4: Cu & Fe (%) Extraction	68
Figure 27 H5: Cu and Fe (%) Extraction	68
Figure 28 H4: Concentration vs Time	68
Figure 29 H5: Concentration vs Time	68
Figure 30 H4: Cu and Fe in LS2 Residue	68

Figure 31 H5: Cu and Fe in LS2 Residue	68
Figure 32 E profile for G2(75 μ m, 2h, 85)	74
Figure 33 E profile for G3(41 μ m, 3h, 95C).....	74
Figure 34 pH profile for G2(75 μ m, 2h, 95C)	74
Figure 35 pH profile for G3(41 μ m, 3h, 95C)	75
Figure 36 G1: Cu & Fe (%) Extraction.....	77
Figure 37 G2: Cu & Fe (%) Extraction.....	77
Figure 38 G3: Cu & Fe (%) Extraction.....	78
Figure 39 E profile for H9(37 μ m,3h,95C).....	81
Figure 40 pH profile for H9(37 μ m,3h,95C)	81
Figure 41 Cu & Fe (%) Extraction for H9	82

LIST OF TABLES

Table 1 Metal-chloro complexes with increasing chloride concentration [3]	7
Table 2 Mean activity (a) of H^+ and Cl^- in 2M HCl and several salts [1]	11
Table 3 Summary of chloride leaching kinetics	22
Table 4 Summary of iron compound precipitation [36,37]	28
Table 5 Process Review: Chloride Leach Summary Table	31
Table 6 Process Review: Summary Table	32
Table 7 Cu, Fe and S % in feed concentrates	36
Table 8 Feed concentrate particle size	37
Table 9 Hematite Process: LS2 streams.....	53
Table 10 Hematite Process: LS1 streams.....	54
Table 11 Hematite Process: Solvent Extraction streams	54
Table 12 Hematite Process: Autoclave streams.....	55
Table 13 Goethite Process: LS2 streams	56
Table 14 Goethite Process: LS1 streams	57
Table 15 Goethite Process: Solvent extraction streams.....	57
Table 16 Feed liquor concentrations.....	57
Table 17 Order of experiments	59
Table 18 Hematite model – feed conditions	62
Table 19 E, pH and free acid output for hematite experiments	65
Table 20 Results of hematite model experiments.....	67
Table 21 Total reduced species of exit PLS and LS2 liquors.....	69
Table 22 Feed conditions for goethite model experiments.....	72
Table 23 E, pH and free acid output for goethite experiments	74
Table 24 Output concentrations (solution and solids) for goethite model experiments ...	76
Table 25 Total reduced species in goethite experiments	79
Table 26 Feed conditions for Rosario experiment.....	80
Table 27 E, pH and free acid	81
Table 28 Output concentrations (solution and solids) for the Rosario experiment	82
Table 29 Sulfur species in Final LS2 residues.....	83
Table 30 Sulfur recovery	84

Table 31 Trace metal analysis.....	85
Table 32 Sample identification guide	93
Table 33 Concentrate sample identification	93
Table 34 Comparing IPL free acid results with test titration value	138

ACKNOWLEDGEMENTS

I would like to sincerely thank Professor David Dreisinger for both the opportunity to undertake this masters and for the guidance over the past two years. The Tim-Tam biscuits brought from Australia were also very much appreciated. I also thank Falconbridge Ltd for the opportunity and importantly for the project funding. In particular Mohammed Buarzaiga, from Falconbridge, was a gem in assisting with the design and prompt manufacture of the mini-thickener and rake component. Other department faculty and staff have also been helpful in advising and assisting with not only my studies but also my social enjoyment. I owe thanks to David Dixon for the chemistry instruction, Steve Cockcroft (in particular for the BBQ and softball funding), and the kind staff in the MMAT workshop and stores who were always there to help me put things back together and working again. These guys deserve a special mention Serge, Ross, Carl, Dave and Glenn. I would also like to thank the UBC Department of Mining and Department of Geological Sciences for their cooperation in allowing me to use their analytical instruments.

I owe a great deal of thanks to Prabhjit Bhatia, my trusty research aid, who took care of my experiment during the daytime shift, when I was sleeping to rejuvenate for the night shift. The Department of Metals and Materials Engineering at UBC has been an enjoyable place to work, and the other graduate students and staff have indeed made it a friendly place to be. I would like to say a special thanks to all of my lab and office mates in the hydromet group, both passing and permanent. In particular, there was one thoughtful visitor who kept me going during my early struggles with apparatus and procedure development, and who later helped me to revise my thesis.

1 INTRODUCTION

Within the past 150 years a number of hydrometallurgical techniques have been proposed for the extraction of base metals, copper (Cu), nickel (Ni), lead (Pb) and zinc (Zn), and precious metals, silver (Ag) and gold (Au), from sulfide minerals [1,2]. An alternative method to smelting was initially sought to combat the emission of acidic sulfur dioxide (SO_2) gas to the atmosphere and the loss of associated precious metals to *slag* [3,4].

Now, for copper, approximately 20% of total primary production is achieved via hydrometallurgical processing [5], and hydrometallurgy potentially offers advantages over smelting with respect to lower capital and operational costs, in the recovery of precious metals, recycling of process streams, and the production of inert, environmentally stable, waste residues. The advantage also of constructing a small-scale hydrometallurgy plant at the ore processing site is of increasing importance where transport costs are significant and for newly discovered deposits in remote locations [4].

Currently, commercial hydromet processes for copper largely feature sulfate-based heap or pressure leaching combined with solvent extraction and recovery via electrowinning, and are generally suitable for processing copper oxides or secondary copper sulfides, such as covellite (CuS) or chalcocite (Cu_2S). Chalcopyrite (CuFeS_2), the most abundant copper mineral, is however difficult to leach and competing sulfate based leach systems are currently investigating fine grinding and addition of surfactants to overcome passivation effects and product layer diffusion obstruction [6,7].

Chloride leaching, however, has been extensively proven to extract >95% of copper from CuFeS_2 at temperatures around the boiling point and at atmospheric pressure [3,4,8]. Chloride leaching offers significant advantages for hydrometallurgical processing, in supporting high metal solubility, enhanced redox behaviour, and increased rates of leaching. In this system, both the cuprous ion, Cu^+ , which is sparingly soluble in sulfate systems, and cupric ion, Cu^{2+} , as well as a host of other metal ions are stabilized through complexation with varying arrangements of chloride ions [3]. The result is that high

recoveries of both the primary metal of interest and associated precious metals can be achieved, by leaching at fairly modest temperatures, and thus has potential for treating complex ores and concentrates.

Other attributes of a chloride system include the minimization of sulfate formation and the formation of predominantly elemental sulfur that remains in the leach residue, and that pyrite is generally left undisturbed in the leach solids [4]. Concentrated chloride solutions also induce high ionic activities that can play a beneficial role in the precipitation and separation of metal chloride salts [1]. The chemistry behind the chloride system is complex but it is this complexity that potentially allows for selective separation and recovery of valuable metals from process liquors or waste material.

Yet despite the effectiveness of chloride leaching, there has been a definite lack of progression toward commercial activity. The reasons for this are largely due to problems with product purity and morphology, in addition to changes in the market value of copper and competition with existing smelting techniques [4].

In this thesis work chloride leach experiments are conducted with respect to two process flowsheets, shown in Figures 1 and 2. Both process models, feature chloride leaching of chalcopyrite combined with solvent extraction, an effective method for the selective removal of copper, and copper recovery by conventional sulfate electrowinning, to address the issue of pure product recovery. They differ however with respect to iron deportment. The hematite model, in which no air is introduced to the leach, allows separate sulfur and iron residues to be produced, thus making waste treatment and disposal potentially easier. The goethite model, however, offers simplicity in overall flowsheet design, and air is added to the leach to precipitate iron as goethite (FeOOH) for disposal with the leach residue.

This work builds upon previous experiments undertaken at UBC [9] in which a number of experimental difficulties were encountered performing a four stage countercurrent leach, particularly with respect to S-L separation. For simplification this work has

reduced the number of leach stages to two and examined the use of a novel apparatus to aid smoother S-L transfer.

Figure 1 The Hematite Process

Figure 2 The Goethite Process

The goals of this investigation were:

1. to complete mass balances for both models to determine feed liquor requirements for leaching;
2. to perform continuous 2 stage countercurrent leach experiments for both models varying residence time, temperature and particle size to determine optimum leach conditions;
3. design and implement a bench scale, glass "mini-thickener" to improve countercurrent transfer of the solids and liquids
4. to assess speciation in the pregnant leach solution with respect to downstream processing.

2 LITERATURE REVIEW

2.1 Aqueous copper and chloride chemistry

2.1.1 Chloride complexes

One of the most significant features of the chloride system for copper hydrometallurgy is that the cuprous, Cu^+ , ion becomes stable through complexation with chloride ions. In a pure water or sulfate solution Cu^+ ions are not stable and the cupric, Cu^{2+} , ion is the dominant species [10]. In water at 25°C cuprous chloride solubility is of the order 2×10^{-7} , however this solubility increases significantly with increasing total chloride concentration [11]. Figure 3[12] shows the relative thermodynamic stabilities of the copper ions in the Cu-H₂O system at 25°C in a Pourbaix (Eh-pH) diagrams, and Figures 4[12] and 5[12] show the Cu-Cl-H₂O system at 1M Cl and 5M Cl, respectively.

The ability to support both Cu^+ and Cu^{2+} ions has major process implications for chloride systems with respect to the solubility limit of copper, the redox potential of the process liquor, and product recovery, particularly the decreased energy requirement to electrowin Cu^+ in comparison with Cu^{2+} .

The key issues for chloride complexation are complex stability, the comparative strengths of metal chloride complexes and the expected variations for metals in different chloride concentrations.

For many metal chloride complexes, the maximum number of chlorides is usually four [13]. In the case of the cupric ion, substitution takes place with the four strongly bound equatorial water molecules [2], thus forming a complex with a square planar geometry [2,14].

Figure 3 Cu-H₂O E_h pH Diagram at 25°C (1 atm, 1M) [12]

Figure 4 Cu-Cl-H₂O E_h pH Diagram at 25°C (1 atm, 1M) [12]

Figure 5 Cu-H₂O E_h pH Diagram at 25°C (1 atm, Cu 1M, Cl 5M) [12]

In general, metal ion complexes (ML_n) are formed by the successive addition of ligands (L), and the complex formation reactions can thus be written (a = activity) [10].

Thus for cupric chloride complexes the following exist:

$K_{n=1-4}$ represent the stepwise stability constants for each separate ligand addition, but cumulative stability constants, β_n , are also often quoted and are defined by:

$$M^{z+} + nL^{-1} \rightleftharpoons ML_n^{z-n} \quad \beta_n = \frac{a_{ML_n^{z-n}}}{a_{M^{z+}} a_{L^{-}}^n} \quad (2.6)$$

Many studies have been undertaken and data tabulated for the stability constants of metal-chloro complexes [2,10,11, 15-18]. This information allows for the determination of complex speciation for various concentrations of chloride and the proposal of relative strengths of chloro-complexes [10,11].

From these studies, the following order of strength has been suggested for metal-chloro complexes, from the strongest (Cl^- acceptors): $AgCl > CuCl > PbCl_2 > ZnCl_2 > CuCl_2 > FeCl_3 > FeCl_2 > NiCl_2 > HCl, NaCl, KCl$ (Cl^- donors) [11]. Table 1 [3] provides an overview of metal-chloro complexes and indicates which species are dominant with respect to changes in chloride concentration.

Table 1 Metal-chloro complexes with increasing chloride concentration [3]

	Low Cl^- concentration				High Cl^- concentration	
Cu (II)	Cu^{2+}	$CuCl^+$		$CuCl_2$	$CuCl_3^-$	$CuCl_4^{2-}$
Cu (I)	$CuCl_2^-$		$CuCl_3^{2-}$		$CuCl_4^{3-}$	
Fe (III)	Fe^{3+}			$FeCl^{2+}$		$FeCl_2^+$
Fe (II)	Fe^{2+}					$FeCl^+$
Zn	Zn^{2+}	$ZnCl^+$		$ZnCl_2$	$ZnCl_3^-$	$ZnCl_4^{2-}$
Pb	$PbCl^+$	$PbCl_2$			$PbCl_3^-$	$PbCl_4^{2-}$
Ni	Ni^{2+}					$NiCl^+$
Co	Co^{2+}					$CoCl^+$
Mn	Mn^{2+}					$MnCl^+$
Cd	Cd^{3+}		$CdCl^+$	$CdCl_2$	$CdCl_3^-$	$CdCl_4^{2-}$
Sb	$SbCl_2^{2+}$	$SbCl_2^+$	$SbCl_3$	$SbCl_4^-$	$SbCl_5^{2-}$	$SbCl_6^{3-}$
Bi	$BiCl_2^{2+}$	$BiCl_2^+$	$BiCl_3$	$BiCl_4^-$	$BiCl_5^{2-}$	$BiCl_6^{3-}$
As				$AsCl_3$		
Ag	$AgCl_2^-$					$AgCl_3^{2-}$
Hg	$HgCl^+$		$HgCl_2$		$HgCl_3^-$	$HgCl_4^{2-}$

The formation of chloro-complexes is largely dependent on the chloride concentration, as can be seen by the above equilibrium equations, and tends toward higher substitution by chloride at higher concentrations [2,3,11]. For cupric chloride, Cu^{2+} , CuCl^+ and CuCl_2 , and possibly CuCl_3^- and CuCl_4^{2-} , are observed with increasing chloride concentration, and similarly for the cuprous ion, CuCl_2^- , CuCl_3^{2-} and CuCl_4^{3-} , are observed. Also, polynuclear cuprous chloride complexes, i.e. $\text{Cu}_2\text{Cl}_4^{2-}$, $\text{Cu}_3\text{Cl}_6^{3-}$, Cu_2Cl_3^- , have been suggested [3,16] as probable species and a spectrophotometric study of a highly concentrated $\text{CuCl-NaCl-HCl-H}_2\text{O}$ system has most likely identified $\text{Cu}_2\text{Cl}_4^{2-}$, rather than CuCl_4^{3-} [3].

It is important to note that complexes may have a variety of charges (positive, negative or neutral) and that the chlorides may be replaced with other ligands, i.e. substituted, or the complexed species themselves may be complexed by other ligands, which can be useful in solvent extraction techniques [2].

The relative strengths of each of the metal ion complexes become important in chloride solution leach liquors.

2.1.2 Solubility

It is important that the primary metal of interest for a certain process has an appreciable solubility to allow fast leaching and efficient movement through the process, particularly for economical reasons. Most of the metal ions important to copper chloride systems have greater solubilities than in sulfate solutions, e.g. Cu^{2+} (five times), Fe^{2+} , Ni^{2+} and Zn^{2+} [1,20].

Particularly for the generally water insoluble chloride salts, i.e. PbCl_2 , CuCl and AgCl , much greater solubilities can be achieved in highly concentrated chloride solutions. For example the solubility of CuCl in cold water is 0.6 mg/L but in concentrated brine solutions >100g/L can be achieved (see Figure 6 [1]). The solubility of PbCl_2 in 25°C water is 1 g/L but a solubility increasing ten times can be achieved at 6M total chloride (see Figure 7 [1]).

Figure 6 CuCl Solubility [1]

Figure 7 PbCl₂ Solubility [1]

Though usually present in smaller amounts in the concentrate, Ag recoveries have been high in most chloride extraction processes as it possesses a high solubility in strong brines at the moderately high temperatures used, e.g. above 85°C.[1]

As shown by the above two figures the effect of temperature is quite significant, with solubility increasing with higher temperatures. This effect has been used in the recovery of these metals in piloted chloride processes [3,4], where by simply reducing the temperature the chloride crystals, i.e. CuCl and PbCl_2 , precipitate out of solution, with purity relative to the contents of the process solution.

It has been shown that solubility limits vary not only with the total chloride concentration but also with the type of chloride salt added to the solution. The reason for this is that different metal cations form chloride complexes of differing strengths thereby changing the availability of chloride ions for complexation with typically water insoluble species. For example, Fe^{2+} forms weak complexes in chloride solutions therefore leaving the chloride ions available to complex with Cu^+ , and thus increases the solubility of the cuprous ion. Conversely, Zn^{2+} ions form strong complexes with chloride ions and thus decrease the solubility of the cuprous ion [11].

In conclusion, for chloride hydrometallurgy it is then desired that a high background concentration of chloride salts (e.g. K, Na, Mg, Ca) be present in the leach/process liquor at a moderately high temperature (e.g. near boiling point) for maximum extraction of copper and other valued metals. Despite the possible negative effect on copper solubility by other metal cations present, as long as a significant amount of chloride ions are present, impurities in the leach liquor are generally not a concern. Impurities however will cause concern during product recovery stages.

2.1.3. Ionic Activity

In dilute solutions, e.g. $<1\text{M}$, the chemical potential, or activity (a), of a species can be approximated by the Molar concentration (M , mol/L), or molal concentration (m , mol/Kg H_2O). Therefore by the following relationship the activity coefficient (γ) is 1 [1,13].

$$\text{Activity (a)} = \text{Activity Coefficient } (\gamma) \times \text{Concentration (m,M)} \quad (2.7)$$

However in very concentrated solutions, e.g. >2M chloride (i.e. concentrations typically used in chloride hydrometallurgy), there is a significant effect on the activity of the species present (shown in Table 2 [1]). In summary, a very concentrated solution can greatly increase the activity (or chemical potential) of species present. As an example, a very small amount of acid can be used to keep the pH very low in a concentrated chloride solution.

Table 2 Mean activity (a) of H⁺ and Cl⁻ in 2M HCl and several salts [1]

Salt Concentration	NaCl	CaCl ₂	MgCl ₂
0	2.02	2.02	2.02
2N	4.03	4.89	5.23
4N	7.28	12.05	13.4
6N	12.4*	27.50	30.6

*Supersaturated in NaCl

In addition, cations that have higher charge densities (e.g. Mg²⁺>Ca²⁺>Na⁺) and are present as undissociated species, have a higher hydration number, i.e. have a greater number of interactions with water molecules, and thus decrease the activity of the water and increase the activity of ionic species present.

With respect to the oxidative leaching of chalcopyrite in a concentrated chloride solution, the influence of chloride ion activity is quite important. For cupric leaching the final reaction may be stated as [1].

And at equilibrium, the equilibrium constant K is defined:

$$K = \frac{a_{\text{CuCl}_2}^4 a_{\text{Fe}^{2+}}}{a_{\text{Cu}^{2+}}^3 a_{\text{Cl}^-}^8} \quad (2.9)$$

$$\log K = 4 \log a_{\text{CuCl}_2} + \log a_{\text{Fe}^{2+}} - 8 \log a_{\text{Cl}^-} - 3 \log a_{\text{Cu}^{2+}} \quad (2.10)$$

The aim of the leach is generally to achieve high cuprous and low cupric ion, i.e. to go to completion. This is thermodynamically favoured only at high chloride ion activities [1,10].

2.1.4 Redox Chemistry

The standard potentials for many species are altered in chloride solutions as a result of their chloro-complex formation (see Figure 8 [3]) [1,3]. The formation of strong complexes, e.g. Cu^+ , Pb^{2+} and Zn^{2+} , decreases the potential at which these metal species are reduced to their metallic state.

This can be observed by using the Nernst equation (2.11) to calculate the reversible potential for the species $\text{MCl}_n^{z-n}/\text{M}^0$ in chloride solution, with respect to the standard potential for M^{z+}/M^0 at 25°C.

$$E_{\text{MCl}_n^{z-n}/\text{M}^0} = E_{\text{M}^{z+}/\text{M}^0}^0 - \frac{0.059}{z} \log \frac{\beta_n^0 a_{\text{Cl}^-}^n}{a_{\text{MCl}_n^{z-n}}} \quad (2.11)$$

At higher β , i.e. for stronger complexes, the deposition potential decreases. As an example the potential for cuprous deposition decreases from 0.521 in water to 0.084 in concentrated chloride solution [3,13,21].

The advantage of maintaining copper in the cuprous state is that it allows deposition of copper via a one-electron transfer, if direct electrowinning is used, and therefore offers potential energy savings when compared to cupric deposition, requiring 2 electrons per copper atom. Also, the theoretical cell potential is decreased relative to electrowinning Cu^{2+} in sulfate via reducing Cu^+ at the cathode and oxidizing Cu^+ to Cu^{2+} at the anode. In addition, the Cu^+/Cu^0 deposition is faster, having only to transfer one electron, with an

exchange current density, j_o (rate of electron transfer), in chloride solution (5M NaCl) determined to be 2400A/m^2 at 25°C , when compared to that of the Cu(II)/Cu^0 deposition in sulfate which can be between $20\text{-}200\text{A/m}^2$ [3].

Figure 8 Altered redox potentials in chloride solution [3]

Despite the ability to deposit copper at a fast rate at the cathode, and although this is good for process efficiency, the downside is that the copper is not smooth and fine metallic crystals of copper are formed instead. It should also be noted that the potential ohmic drop for chloride solutions is larger than in sulfate, i.e. the loss of energy as current travels through the electrolyte is greater.

The growth of finer copper crystals (e.g. dendrites, nodules or metallic powder) may lead to greater contamination due to the exposure of a greater surface area to the process liquor, and generally these morphologies also make the product harder to handle. Investigations have consequently been made into the use of additives to aid in better, smoother, product formation [3,16]. However, greater product purity problems arise from the presence of more noble elements in the cell feed solution, e.g. selenium (Se), tellurium (Te) and most notably silver (Ag), and these will even in small concentrations deposit at potentials required for Cu^+ deposition, as this potential will be below the reduction potential for these elements [4].

Of particular interest for gold bearing concentrates, is the significant decrease in the standard potential for the $\text{Au}^{3+}/\text{Au}^0$ couple in concentrated chloride solutions, from 1.5 V to 1.012V in 4M NaCl-0.5M HCl (Figure 8) [3].

However of overall importance is the effect of the concentration of chloride on the oxidation potential of the couples $\text{Fe}^{3+/2+}$ and $\text{Cu}^{2+/+}$, both of which are commonly used in the oxidative leaching of copper sulfide minerals.

The standard reduction potentials (at 25°C) for $\text{Fe}^{3+/2+}$ and $\text{Cu}^{2+/+}$ are 0.77 and 0.153, respectively, and therefore the ferric ion has a far greater oxidizing potential in pure water solutions [3,22]. In 4M NaCl, 0.5M HCl solutions the oxidizing potential of the iron ion couple falls to 0.681 and the copper ion couple increases to 0.584, both of these potentials are high enough for oxidizing most metal sulfides [3].

These changes are again due to the complexation behaviour of the ions. For copper in chloride solution the electron transfer from Cu^{2+} to form the reduced Cu^+ species, i.e. $\text{Cu}^{2+} + \text{e}^{-} \rightleftharpoons \text{Cu}^+$, can be more correctly written as: $\text{Cu}^{2+} + 2\text{Cl}^{-} + \text{e}^{-} \rightleftharpoons \text{CuCl}_2^{-}$. Cuprous is more strongly complexed than the cupric ion, which forms weaker complexes and remains largely uncomplexed to high chloride concentrations. Therefore the ratio of free $\text{Cu}^+:\text{Cu}^{2+}$ decreases with increasing concentrations of chloride and according to the Nernst equation the potential of the $\text{Cu}^{2+/+}$ couple will thus increase [13,21]:

$$E = E_{\text{Cu}^{2+}/\text{Cu}^+}^0 - \frac{RT}{F} \ln \frac{a_{\text{Cu}^+}}{a_{\text{Cu}^{2+}}} \quad (2.12)$$

Conversely, for the $\text{Fe}^{3+}/\text{Fe}^{2+}$ couple the oxidizing potential decreases with increased chloride concentration as the ferric ion forms stronger complexes with the chloride ions than does the ferrous ion. Therefore the ratio of free $\text{Fe}^{3+}:\text{Fe}^{2+}$ decreases with increasing chloride concentration and thus the solution potential decreases. Similarly the relationship can be observed [13,21]:

$$E = E_{\text{Fe}^{3+}/\text{Fe}^{2+}}^0 - \frac{RT}{F} \ln \frac{a_{\text{Fe}^{2+}}}{a_{\text{Fe}^{3+}}} \quad (2.13)$$

Figure 9 [23] shows the effect of chloride activity on the potential of species common to copper chloride hydrometallurgy solutions.

Figure 9 Eh vs Log a_{Cl^-} [23]

The importance of a concentrated chloride solution for the oxidative leaching of chalcopyrite by cupric is that a high oxidation potential can be maintained as the leach progresses. A high ratio of cuprous, reaction product, to cupric can be present, and the reaction still be driven to near completion. This is because cuprous is associated only as chloro-complexed species, effectively reducing the free cuprous ion concentration.

2.2 Chalcopyrite leaching in chloride

2.2.1 Thermodynamics and kinetics

To determine the suitable aqueous conditions in which leaching of a particular mineral can be carried out, an Eh-pH (or Pourbaix) diagram assists by indicating the predominant species, of metal and metal compounds, present at equilibrium with respect to reduction potential and hydrogen ion concentration. By following the progression from mineral to soluble metal species on the diagram leaching pathways can be determined, i.e. what adjustments in pH and/or solution potential are required to liberate the metal ions contained in the mineral [22].

Eh-pH diagrams represent only thermodynamic equilibria however and so alone do not indicate which leaching pathway will work best. The kinetic factors of each reaction must also be considered and are especially important when considering process design. This kinetic information comes from experimentation and observation, and leaching rates are generally influenced by reactant concentration, temperature, particle size (surface area) and product layer formation.

In this study the copper sulfide mineral chalcopyrite (CuFeS_2) is of particular importance as it is presently the most abundant source of copper [22]. By observation of the Cu-Fe-S- H_2O Eh-pH diagram at 25°C , which has been simplified to include only laboratory observed reactions (See Figure 10 [24]), it is also confirmed to be quite refractory, being quite resistant to acid attack and requiring strong acid oxidizing conditions [6]. The stability of chalcopyrite has been attributed to its face-centered tetragonal lattice structural configuration [25].

Figure 10 Cu-Fe-S-H₂O E_h-pH diagram at 25°C [24]

Figure 11 Cu-Fe-S-Cl-H₂O E_h-pH diagram at 25°C [24]

As this study is also focused on chloride solutions, Figure 11 [24] shows that when chloride (at 1M) is added to the Cu-Fe-S-H₂O Eh-pH diagram at 25°C the regions of sulfide stability are not significantly affected and the only difference appears to be in soluble copper and oxide regions. Thus during leaching the presence of chloride appears to prevent oxide formation, that could possibly slow the leach reaction [24].

As a strong acidic oxidizing solution is required, studies and processes for chalcopyrite leaching [1,3,4,10,21, 26-33] have so far employed ferric and/or cupric chloride and have successfully demonstrated the effective leaching of copper at atmospheric pressure in solutions near boiling point. Consequently, the following two leaching reactions are generally accepted:

Not predicted by the Eh-pH diagram is the recovery of predominantly elemental sulfur (S⁰) instead of the oxidized sulfate species. In fact less than 5% of the S in chalcopyrite generally oxidizes to sulfate in atmospheric chloride leaching, and it is when pressure leaching is employed that greater sulfate formation may become a concern [34]. The formation of a S⁰ product layer around the mineral particles has not been observed to affect the rate of leaching [34], and more discussion regarding the fate of sulfur in chloride leaching is presented in a section 2.2.2.

To further complicate the reaction kinetics and mechanisms involved, and despite the reporting of separate studies for ferric and cupric leaching, the two oxidant species are closely linked as ferric leaching will produce cupric ions, cupric leaching will produce ferrous ions, and ferric ions will oxidize cuprous ions to form ferrous and thus regenerate cupric for further leaching, as in the following reaction:

Before discussing the findings of kinetic leaching studies it is important to note that, by simple observation of the above reactions, there is flexibility in which form the copper

ion may be attained during or at the end of the leach, and this may ultimately be important for downstream processing. Also due to the role chloride plays in stabilization of the cuprous ion, copper solubility and the $\text{Cu}^{2+}/\text{Cu}^{+}$ redox potential, chloride concentration is to be a significant factor in the leaching rate and extent of leaching.

It was discovered early on that the ferric oxidation of chalcopyrite in chloride solution was much faster than in sulfate solution [21,27]. However it was not until the development and testing of hydrometallurgical chloride processes for copper in the early 1970s [3,4] that there was significant interest in determining the reaction mechanism and kinetics behind leaching in chloride media. It was then found that the presence of cupric substantially increased the rate of leaching [21,32].

Table 3 below summarizes the main findings of chalcopyrite leaching studies in chloride media and following the table is a brief discussion on important leaching aspects.

The two requirements that enable optimum leaching with cupric ions (Equation 2.15) include the presence of a significant concentration of chloride and also that the potential is low enough to support the cuprous ion [10,21,32]. However, as stated previously, in a chloride solution the $\text{Cu}^{2+}/\text{Cu}^{+}$ redox potential is raised due to chloro-complexation, and therefore the potential required for cupric leaching does not have to be too low, provided the chloride concentration is high.

It has also been reported that to leach to completion, a high chloride concentration, high temperature and short leaching time must be employed to lessen the reduction of elemental sulfur by the cuprous reaction product (Equation 2.17) [30].

Table 3 Summary of chloride leaching kinetics

Linear kinetics observed [10,21]:

Extraction rate was shown to increase with temperature; this is an indication of surface rate control (i.e. rate controlled by electron transfer across mineral surface) as reaction products do not affect leaching rate; activation energies ($>40\text{kJ/mol}$) determined from temperature experiments also indicate surface control of dissolution rate.

Temperatures near boiling point are therefore best to achieve maximum extraction, higher temperatures would cause sulfate formation (See Section 3b.).

Smaller particles increase rate [10,21,28]:

Following from the above, as the surface is rate controlling, an increase in surface area would therefore increase the rate of particle dissolution, and this has been demonstrated.

Rate dependent on [10,21,28]:

Oxidant concentration (i.e. cupric or ferric), cuprous and chloride concentration; also the cupric leaching rate has shown to be greater than ferric.

Rate independent of [21,28]:

Hydrochloric acid concentration, ferrous concentration and completely dissociated chloride salts; pH should however remain low enough to avoid the precipitation of copper-oxy chloride or iron compounds; rate is also independent of stirring rate, which needs only be sufficient to suspend particles.

The presence of air, or stronger oxidants, in the leach can assist also in oxidizing the cuprous ion product to subsequently prevent cuprous reduction of sulfur and/or regenerate cupric for further leaching. Oxidation of cuprous by air may occur either directly (Equation 2.18) or via the oxidation of ferrous to ferric (Equation 2.19) which may then catalyze the oxidation of cuprous to cupric (Equation 2.20).

The conversion of ferrous to ferric may also allow for the removal of iron as goethite at ambient pressure during the leach process via the following reaction (see section 2.2.3 on iron deportment):

It is not always desirable for the iron to be removed with the leach residue and so to prevent the above from occurring oxidant addition needs to be controlled.

Despite the possible array of proposed intermediary Cu/S compounds, from the reaction of chalcopyrite with either ferric and/or cupric ions, generally in concentrated chloride solutions there is observed to be a simultaneous rapid extraction of both copper and iron. This indicates that potentially hindering reactant products are not formed for either species.

In summary, there are a number of factors that contribute to the rate of CuFeS_2 leaching and an atmospheric leach at boiling point, low pH, with relatively fine particles and a high concentration of both oxidant and chloride are important for efficient and effective leaching.

2.2.2 Sulfur

Both fundamental studies and developed hydrometallurgical processes involving chalcopyrite leaching with FeCl_3 or CuCl_2 have generally reported >95% of the sulfur reaction product forming as elemental sulfur, and hence <5% oxidation of sulfur to sulfate [4,34,35]. Even when long retention times (up to 90hr) were employed, or large amounts of oxidant or acid were used, at temperatures below 100°C there was still found to be predominantly elemental sulfur as the sulfur leach reaction product [34].

The advantages in the recovery of sulfur in its elemental form include the following [4,34,35]

- fugitive emissions of SO_2 are avoided, unlike in smelting;
- easy storage and handling;

- limited environmental hazards (in waste residues sulfate hydrolysis causes acidic conditions in the environment);
- oxidant is consumed only by the desired mineral reaction, thereby maximizing the release of the metal of interest (i.e. no oxidant is wasted on S oxidation);
- the precipitation of sulfate containing jarosite is avoided (Jarosite is typically a process waste residue for the removal of iron and tends to be less stable in the environment- see section on Fe deportment). However, if so desired jarosite may be formed with the aim of removing sulfate from the process liquor; and,
- if sulfate forms the leaching rate of the chloride system will be much slower.

Generally, sulfate forms when temperatures are employed above the melting point of sulfur (119°C) [35]. This explains the increased sulfate levels (up to 25% of sulfur product) of chloride hydrometallurgy processes which involve pressure leaching, e.g. in the CLEAR process. However, although for relatively few processes, 5-25% sulfur oxidation has still been reported for systems that remain below 100°C and it has been suggested, that although not precisely clear, it is likely that the mineralogical composition of the concentrate tested was a factor [4]. For example some sulfate may originate from the superficial oxidation of the sulfides prior to leaching (e.g. PbSO_4 on galena, PbS) or by the sulfide leaching reaction itself. In addition, it has been shown that despite the presence of air in the leach there is no significant effect on the relative amounts of elemental sulfur and sulfate produced and the relative amount of elemental sulfur formed is independent of chalcopyrite particle size [34].

The most likely mechanism of elemental sulfur formation appears to be via the dissolved intermediary reaction product H_2S . This mechanism is reasoned by the presence of well-formed euhedral sulfur crystal growth that indicates the elemental sulfur was deposited from aqueous solution, as opposed to conversion of the sulfide remaining on the mineral surface. A variety of morphological arrangements of these sulfur crystals have been observed (dependent on mineral particle size and preparation) ranging from large globules to continuous films. However, due to observed linear leaching kinetics

sufficient porosity must exist in this product layer to allow passage of reactants and thus does not cause passivation [34].

One advantage of the sulfur coating of particularly fine CuFeS_2 particles is to cause agglomeration thus improving thickening and filtration properties of leach residues [4].

The addition of calcium to process liquor, as either a chloride salt (CaCl_2) or carbonate (Limestone, CaCO_3 , typically employed for pH adjustment) is a very good method of removing sulfate, as gypsum (CaSO_4), from solution. Jarosite may also be precipitated at moderate leaching temperatures and in acid concentrations but this reaction will still leave a background concentration of sulfate (e.g. 10g/L) [4].

2.2.3. Iron Deportment

Iron is the fourth most abundant element in the earth's crust and as a consequence is usually present in most metal ores, including those of copper. Iron may be present as an essential constituent of the ore mineral (i.e. the material containing the metal of value), e.g. chalcopyrite CuFeS_2 , bornite Cu_5FeS_4 and cubanite CuFe_2S_3 , and therefore in extracting the metal of interest the associated iron will also accumulate in the leach liquor, and will have to be removed prior to recycling of the stream for leaching.

Iron may also be present in gangue minerals (i.e. materials that do not bear metals of value for the process) either as an essential constituent or partially substituted for an essential constituent. The most common iron-bearing gangue mineral in sulfide ores, and in particular for the chalcopyrite ores this study is interested in, is pyrite FeS_2 . For oxide ores the most common include hematite Fe_2O_3 and magnetite Fe_3O_4 . In addition, owing to iron's similarities in chemical properties with many elements (in particular the first series transition metals) it may substitute for an essential element into the crystal lattice of either ore or gangue mineral [36].

Whilst it is generally unavoidable to accumulate iron in the leach liquor, if iron is present in the ore mineral, it is possible to avoid dissolution of gangue materials by selective

leaching conditions. For example a chloride leach for chalcopyrite operating at atmospheric pressure enables this strategy as pyrite is generally left unattacked. Pyrite in fact reacts much more slowly than chalcopyrite even in oxygen pressure leaching (especially <170°C [36]) and this may be due to the formation of elemental sulfur around the pyrite and/or galvanic protection by less noble minerals such as galena, covellite, and sphalerite [22].

Iron still however makes up an appreciable content of the chalcopyrite leach liquor owing to its 1:1 Cu:Fe ratio, and the most common method for removing iron from hydrometallurgical processes is via the precipitation of iron compounds. The precipitation can occur during the leach stage, and therefore iron is removed with the leach residues, or separated at another stage of the process, which may be preferred so as not hinder the removal of sulfur or precious metals from the leach residue or for the production of a separate saleable iron product.

The three predominant iron compounds that are precipitated in hydrometallurgical processes are goethite FeOOH , hematite Fe_2O_3 , and jarosite $(\text{H}_3\text{O}, \text{K}, \text{Na}, \text{NH}_4) \cdot \text{Fe}_3(\text{SO}_4)_2(\text{OH})_6$ compounds, if sulfate is present [36].

The precipitation of these iron compounds occurs when the iron is present as ferric ion and there is low acid. When oxygen is added to convert ferrous to ferric, as seen by the following equation, then this consumes acid, and can thus raise the pH to initiate precipitation.

If the pH is raised too quickly, with poor agitation at low temperatures [22] ferric hydroxide will form and due to the polymeric nature of this gel colloid precipitate, which contains cross-linked hydroxyl bridges, it is poorly filtered and will not be successfully separated from the process. On the other hand a steady pH increase, high temperatures and good agitation will result in the well-structured, easily filtered iron compounds,

goethite, hematite and jarosite. In a chloride leach stream the iron is often produced as ferrous and therefore by careful mixing with oxygen, to convert ferrous to ferric, the rate of pH increase can be controlled, and therefore a filterable iron compound is easily achieved.

Table 4 [36,37] summarizes process requirements for precipitation of these compounds, with comments on their stability as waste residues in the environment, and their role in hydrometallurgical processing.

It is important to comment on one study [37] that showed by increasing the chloride content of solutions with chloride salts that completely dissociate, e.g. NaCl or CaCl₂, the proton activity increased, thereby decreasing the quantity of hematite produced, without however effecting the composition of the product. When salts which formed complexes with chloride, e.g. ferrous or zinc ion, were added there was no effect of the amount of hematite formed, as the free chloride did not change and therefore the proton activity did not change.

Table 4 Summary of iron compound precipitation [36,37]

Iron Compound	Process Requirements	Comments
Hematite Fe_2O_3 (Fe ~ 70%)	Generally formed at $T > 130^\circ\text{C}$ in an autoclave ($T > 100^\circ\text{C}$ if hematite seed is present). When formed in chloride solutions Cl found to be <1% of product.	Though more costly to produce, it is very stable and good for ponding and possible resale. Stability demonstrated in natural environment, by its occurrence as a weathering product. High Fe% requires less solids to be handled. A study has shown also that by seeding precipitation a more coarse grain is formed which is easier to filter.
Goethite FeOOH (Fe ~ 63%)	Generally formed at $T < 120^\circ\text{C}$. When formed in chloride solutions product may contain ~8% Cl.	Precipitation can occur at atmospheric pressure. Goethite has also been shown to be environmentally stable, after hematite, particularly in wet conditions. In fact the weathering of hematite in a humid environment usually produces goethite, $2\text{FeOOH} \rightleftharpoons \text{Fe}_2\text{O}_3 + \text{H}_2\text{O}$.
Jarosite $\text{M}^*\text{Fe}_3(\text{SO}_4)_2(\text{OH})_6$ $\text{M}^* = \text{H}, \text{Na}, \text{K}, \text{NH}_4^+$ (Fe ~ 35%)	Precipitates over a range of temperatures and is dependent on the content of sulfate. Can be formed at a lower pH.	The iron content is low. Thus more product is required to remove a comparative amount of iron. There are problems with long term stability as acid will leach out: $\text{NaFe}_3(\text{SO}_4)_2(\text{OH})_6 + 3\text{H}_2\text{O} \rightarrow \frac{1}{2}\text{Na}_2\text{SO}_4 + 3\text{Fe}(\text{OH})_3 + \frac{3}{2}\text{H}_2\text{SO}_4$

2.3 Overview of chloride leach processes for copper

Over the last thirty years a number of hydrometallurgical processes that employ chloride leaching for copper have been tested at the laboratory, pilot plant and/or demonstration plant [2,4]. These processes have been quite successful in exhibiting efficient extraction of copper, via leaching at atmospheric pressure and boiling point, but only one process, the Duval Corporation's CLEAR process, has been operated commercially. This process operated for a period of six years until it was closed due to various technical and economic reasons, noting that their product still required further costly refining to achieve wirebar- or cathode-grade material [4,38]. Product impurity (especially due to silver contamination) has in fact been a major hindrance towards commercial development of these processes along with technological constraints faced in the handling of corrosive process liquors [38].

Figure 12 provides an overview of the various methods of recovering copper from chloride leach liquor that have been investigated, and includes the chloride leach process proposed in this thesis work. Tables 5 and 6, on the following pages, summarize the leach and process characteristics of these processes, which were mostly designed to leach chalcopyrite (CuFeS_2) concentrates.

Figure 12 Chloride leach processes for copper

PROCESS	SCALE	LEACH				
	L/P/D/C	Lixiviant	T (°C)	EXTN %	Stages ^a	Time (h)
UBC - Cominco ^[1,4,24]	L	Fe ³⁺ (CaCl ₂ /CaO)	95	99	2	9-12
Cymet ^[3,4,38]	P	Fe ³⁺ /Cu ²⁺ /NaCl	98	99	2	3/stage
Outokumpu ^[39]	L (patent)	Cu ²⁺ /Cl ₂ /NaCl/Air	-	-	several	-
USBM ^[1,4,13,21,24]	L	Fe ³⁺ /Cu ²⁺ (CaCl ₂)	106	99	1	2
CLEAR ^[1,4,21,40]	C	Fe ³⁺ /Cu ²⁺ /Na&KCl	105&150	high	2	1.5/stage
Elkem ^[3,38]	P	Fe ³⁺ /Cu ²⁺ /NaCl	105-115	high	2	-
GCM ^[41]	L	Fe ³⁺ /NaCl	-	99	2	-
Intec ^[41,42]	D	Cu ²⁺ /BrCl ₂ /NaCl/ NaBr/Air	85	98	4	4
Cuprex ^[2-4,38,43,44]	P	ExcessFe ³⁺ /NaCl	95-100	>96	1	9-10
Minemet ^[45,46]	L	Cu ²⁺ /NaCl	100	98.5	2	3/stage
Phelps-Dodge ^[47]	L (patent)	Cu ²⁺ /Na,KCl/O ₂	80-95	-	cocurrent	6
Henkel ^[4,48,49]	L	ExcessFe ³⁺ /NaCl	95	-	1-2	-
Present work	L	Fe ³⁺ /Cu ²⁺ /CaCl ₂	85-95		2	2-3h/stage

Table 5 Process Review: Chloride Leach Summary Table

a = all countercurrent except Phelps-Dodge; L/P/D/C = Laboratory/Pilot/Demonstration/Commercial

PROCESS	SCALE	PROCESS STEPS	COPPER RECOVERY	IRON DEPARTMENT	COMMENTS
	L/P/D/C			H = hematite, G = goethite, J = Jarosite	
UBC - Cominco ^[1,4,24]	L	Cu ^o (Ag,Se,Te) < CR *BLS (Zn, Mg, Ca, Fe)	CuCl → Cu ^o	PO: H > CR	Ag in Cu ^o
Cymet ^[3,4,38]	P	Only Fe pptn > CR	CuCl → Cu ^o	O: G, J > CR	Ag in Cu ^o
Outokumpu ^[39]	L (patent)	Cu ^o < AP < CR < CA (NaOH/Cl ₂ /H ₂)	Cu ₂ O → Cu ^o	O: G in leach	From patent
USBM ^[1,4,13,21,24]	L	Only Fe pptn > EW	Cl EW	O: H at 80°C > EW	Sb in Cu ^o powder
CLEAR ^[1-4,21,40]	C	Cu ^o < EW	Cl EW	PO: H, G, J in LS2	Ag in Cu ^o powder
Elkem ^[3,38]	P	PbCl ₂ , Zn SXEW Cl, CR	Cl EW	O (Air/Cl ₂): G	Ag in Cu ^o
GCM ^[41]	L	I ₂ (AgI) < EW < SR: O ₂	Cl EW	O: H in BLS after LS2	Granular Cu ^o
Intec ^[41,42]	D	Cu ^o < AgHgCu < AP (Fe, In, Bi) < EW *BLS (Zn, Pb, Mg, Cd, Co, Fe)	Cl EW	O: G in leach	Ag and S in dendritic Cu ^o
Cuprex ^[2-4,38,43,44]	P	Gypsum pptn < SX < Ag/Fe ^o	SX Cl EW	PO(O ₂): G after SX	Pure Cu ^o powder
Minemet ^[45,46]	L	1/2 PLS to SX < BLS (Zn, Pb, Ag)	SX SO ₄ EW	1/2 PLS O (Air): G	Pure, smooth Cu ^o
Phelps-Dodge ^[47]	L (patent)	Acid leach of Cu ²⁺ ppt < SX	SX SO ₄ EW	O: G, J in leach	Pure, smooth Cu ^o
Henkel ^[48,49]	L	SX (CA for wash & Cl ₂)	SX SO ₄ EW	O (Cl ₂): G	Pure, smooth Cu ^o
Present work	L	SX	SX SO ₄ EW	PO: H > SX or O: G in leach	

Table 6 Process Review: Summary Table

Abbreviations: AP = Alkali Purification; BLS = bleed stream; CA = chlor-alkali electrolysis; CR = copper recovery; Cu^o = reduction with copper metal (or similarly Fe^o); EW = electrowinning; (P)O = (Pressure) Oxidation; SX = solvent extraction.

Table 5 shows process variations investigated for CuFeS_2 leaching in chloride with, employing and/or ferric in a background of NaCl or CaCl_2 , and these have all reported high extractions. Similar lixiviant characteristics and leach conditions were employed in this thesis work.

Regarding the variations in copper recovery for each of the different processes, initial aims to crystallize pure crystals of copper salt, as cuprous chloride, found that silver was a major contaminant. Even when metallic copper was added to reduce cupric to cuprous, and cement noble impurities [1,4], this technique was not successful in completely removing the silver. Also, the temperature adjustments required and handling of the crystals may have potentially led to technological problems during process scale up. As an example, evolved HCl must be kept dry to prevent corrosion.

Later attempts to electrowin copper from the cuprous state in chloride solution, attempting to reduce operating costs via electrowinning Cu^+ , encountered the same product purity problems with respect to silver (USBM, Intec, Elkem, CLEAR) [3,4,38,40]. These processes were also susceptible to product contamination by insoluble compounds as well as other noble impurities, such as antimony [13]. In addition, due to the high rate of winning in a chloride medium, the product was fine, either dendritic or powder-like, and thus created handling difficulties.

Solvent extraction so far appears to be the best method of selectively removing copper from the leach solution, for preparation of a pure cell feed for electrowinning from either a chloride or sulfate solution. Organic extractants are generally highly selective for the cupric ion [49-51] and impurity transfer along with the copper is therefore minimal. However, it is important to wash the chloride from the loaded solvent to prevent transfer of chloride to the sulfate electrowinning cell, which may even in small quantities lead to corrosion [49-51].

Electrowinning copper in chloride solutions from the cupric state seems to negate the advantage of using chloride. Electrowinning cuprous, which is only stable in concentrated chloride solutions, would require only one electron and therefore half of the energy required to reduce cupric to metallic copper. Also partial and incomplete reduction of cupric to cuprous may occur.

Electrowinning copper from sulfate solutions is a well-developed technology for producing smooth, high purity copper cathodes, and conventional cell designs are now well established.

However, commercial development of these chloride leach/sulfate electrowinning processes has likely been hindered by process complexity and uncertainty regarding the capital and operating costs required to compete with existing sulfate based leaching plants.

The flowsheets of the three chloride leach processes in Table 6 that have proposed copper recovery via solvent extraction and sulfate electrowinning have flowsheets which differ with respect to this thesis work. The closest design is that of the Minemet Recherche process, in which the pregnant leach solution is split, one half going to solvent extraction and the other to atmospheric goethite precipitation, and then both streams combine to return to the leach.

2.4 Summary

The two process models developed in this work combine chloride leaching with solvent extraction and electrowinning of copper from sulfate solution, and evolved from reviewing the various chloride processes previously attempted, see Figure 12. Although the experimental work in this thesis focuses on the leaching step, in hydrometallurgy it is important to consider downstream processing steps and recycling of the liquor to the leach to determine the suitability of a process. Mass balances were completed for both circuits, and leach experiments were performed with respect to the calculated feed liquor requirements.

The leach conditions chosen for the countercurrent leach experiments were based on recommendations in the literature investigating the kinetics of chalcopyrite leaching. The literature indicates that an atmospheric leach, near boiling point, at a low pH, using relatively fine particles and a high concentration of chloride and oxidant are important for effective and efficient leaching of chalcopyrite. As the reaction is linear with temperature and the rate determined to be surface reaction controlled, particle size, temperature and leach time were varied in the experiments to achieve higher extractions of copper.

3 EXPERIMENTAL

3.1 Mass balance spreadsheet preparation for the leach models

For the two chloride leach process models considered in this thesis work, the “hematite” (no air in leach) model and the “goethite” (air in leach) model, simplified mass balance spreadsheets were developed in Excel to determine recycle feed liquor requirements for the leach. These mass balances considered the leach with respect to downstream purification and recovery steps. In particular, the concentration of oxidants cupric and ferric were determined to allow 100% extraction of copper and iron from CuFeS_2 and enable recycling of the process liquor to the leach following copper recovery. These recycle concentrations provided the basis for preparing feed liquors for continuous countercurrent leach experiments.

Assumptions for performing the mass balance included identification of reactions taking place in each process unit and that 100% of the leach liquor moved countercurrently to the leach residues.

3.2 Feed concentrates

The copper concentrate tested in all but the final experiment originated from Antamina in northern Peru, and 30kg was shipped via Falconbridge Ltd. For the final experiment chalcopyrite concentrate from the Rosario deposit at Collahuasi in Chile was tested, and 4kg was provided by Falconbridge.

Both concentrates contained chalcopyrite (CuFeS_2), with differing amounts of gangue material, and the Rosario concentrate also included chalcocite (Cu_2S). To obtain a representative sample of the Antamina concentrate, for the leach tests, the complete concentrate sample was mixed and divided using an automatic splitter in the UBC Department of Mining Coal Lab. The splitter was then used to produce smaller packages, e.g. 2.5kg lots, suitable for testing. The Rosario concentrate was sent for grinding and then divided equally on a bench to select a representative sample for testing.

Prior to use in the leach experiments both concentrates were air dried, over approximately one week, and rolled with a stainless steel rolling pin to break up clumps. For some of the experiments in which finely ground concentrate was employed, a portion of both concentrates was sent to Process Research Associates (PRA) in Vancouver to perform grinding to 20-

25microns. The final and only experiment that employed Rosario concentrate had undergone fine grinding.

Initial characterization of the concentrates involved analysis of 30 elements (including Cu and Fe) by Inductively Coupled Plasma (ICP) spectrometry (via aqua-regia digestion), total sulfur analysis and SiO₂ analysis. These analyses were performed by International Plasma Laboratories (IPL), a contract laboratory in Vancouver. Gold analysis was also performed by ChemMet Consultants in Vancouver. The results of these analyses can be found in Appendices 1 and 2 and a summary of the Cu, Fe and S% are shown in the following table for the three experimental concentrate feeds. The 3 feeds include the as-received coarse Antamina concentrate and the Antamina and Rosario concentrates that had undergone fine grinding.

Table 7 Cu, Fe and S % in feed concentrates

Feed Concentrate	Cu %	Fe %	S%
Antamina (as received)	28.8	28.4	32.1
Antamina (fine grind)	28.5	28.7	32.4
Rosario (fine grind)	26.8	26.8	35.5

Particle size analysis included wet sieving for the as-received coarse material, as a significant proportion of particles were larger than the smallest sieve size of 38µm. For analysis of the finely ground concentrates a Malvern Mastersizer laser analyzer was used to assess particle size distribution. The Mastersizer is an instrument that determines particle sizes via the detection of light refracted by the various sized mineral particles, and is well suited for particles <38µm. The coarse material was also tested using the Mastersizer to provide a comparison. Both particle size analyses were performed in the UBC Department of Mining Coal Lab and the results are shown in the following table. Reports for the Mastersizer analyses can be found in the Appendix 3.

Table 8 Feed concentrate particle size

Feed Concentrate	Method	Results
Antamina (as received)	Wet Sieving Malvern Mastersizer	p90 = ~75 μ m p50= 42 μ m, p90=106 μ m
Antamina (fine grind)	Malvern Mastersizer	p50= 16 μ m, p90=41 μ m
Rosario (fine grind)	Malvern Mastersizer	p50= 16 μ m, p90=37 μ m

p50 or p90 = size under which 50% or 90% of particles exist

Characterization of both concentrates also included x-ray diffraction spectrometry (XRD), and was performed in the UBC Geology Department. The XRD spectra have been included in Appendix 4. The Antamina spectrum reveals that the concentrate consists largely of chalcopyrite with a low-moderate amount of gangue material consisting of pyrite, silica, sphalerite, zinc oxide and molybdenite. The Rosario spectrum reveals that the concentrate consists of two copper minerals chalcopyrite and chalcocite with a significant amount of gangue material, largely of pyrite and lesser amounts of silica, molybdenite, and sphalerite.

3.3 Feed solutions

Feed solutions were prepared in deionised water (DI water) using technical grade ferric chloride (FeCl_3) powder and 4-14 mesh calcium chloride (CaCl_2) pellets obtained in bulk quantities from Anachemia Science. Laboratory grade cupric chloride dihydrate ($\text{CuCl}_2 \cdot 2\text{H}_2\text{O}$) was obtained from Fisher Scientific or Aldrich and concentrated hydrochloric acid (HCl) from Fisher Scientific. To achieve the reduced ferrous solution for the goethite model feed liquor powdered iron was used to reduce ferric chloride.

Feed liquor concentrations were based on the mass balance outputs of the model. For both models, an approximate background concentration of free acid (as HCl) was aimed at around 3g/L, either to approximate the expected free acid concentration in liquor recycled from hematite precipitation in an autoclave or to keep acid sufficiently low to promote goethite precipitation. Total chloride concentration was aimed at greater than 5M with additional free chloride contributed by either 110g/L or 220g/L CaCl_2 .

3.3.1 Feed liquor for the hematite model

To prepare the hematite model feed liquor ferric chloride was added first to generate heat to then aid dissolution of cupric and calcium salts. Finally, hydrochloric acid was added and, to determine the actual free acid concentration, an undiluted sample was sent to IPL for analysis via oxalate masking NaOH titration. Following the reporting of two anomalously high free acid concentrations by IPL, additional free acid titrations were performed at UBC and for all other experiments the results were comparable. Appendix 5 contains the Free Acid method used for the UBC titrations and shows a table comparing IPL and UBC titration results.

3.3.2 Feed liquor for the goethite model

The feed liquor for the goethite experiments contained iron as predominantly ferrous. To prepare the liquor, ferric chloride and calcium chloride were first dissolved in DI water and then powdered iron added to achieve the desired ferrous concentration, according to the following reaction (3.1).

A higher calcium chloride concentration, of 220g/L, was used, following the first experiment, to make up for the reduced amount of metal chloride salt added. Following completion of the reduction reaction, indicated by stabilization of the redox potential at 450mV_{Ag/AgCl} (at room temperature), cupric chloride and hydrochloric acid were added. The final solution was then titrated with acidic certified cerium sulfate solution (0.1M) to determine total reduced iron, and the method used can be found in Appendix 5. The ferric concentration was thus calculated as the difference between the total iron and reduced iron.

3.3.3 Feed liquor analysis

In addition to free acid analysis, two diluted samples of the feed liquor (d.f.x100), one with 2% HCl and one with only DI water, were prepared and sent to IPL for ICP 30 element analysis and total chloride ion analysis respectively. Total chloride was analyzed by IPL using an ion selective electrode (ISE) and reported as g/L HCl. Certificates of analysis for the IPL results can be found in Appendix 1.

3.4 Experimental Apparatus

The layout of the two-stage countercurrent leach circuit is shown in Figure 13. For solid-liquid (S-L) separation one mini-thickener (Th1), was incorporated between Leach Stage 1 (LS1) and Leach Stage 2 (LS2) and pressure filtration (P.F.) was used to separate final leach residues. The filtrate from pressure filtration (LS2 liquor) was then transferred countercurrently to LS1.

The equipment and apparatus used is detailed in the following sections.

Figure 13 Experimental Set-up

3.4.1 Leach vessels

The experiments were conducted using 2L glass water-jacketed leach vessels, approximately 11cm in diameter, for containing 1L leach volumes for Leach Stages 1 and 2 (LS1 and LS2). These tanks had indents, to act as baffles, and were sealed with a removable high-density polyethylene (HDPE) lid. The lid, important to prevent evaporation loss, had several stoppered openings for the temperature probe, pH and E measurement, sampling, stirrer shaft and connection to a condenser. Water condensers were used to maintain atmospheric pressure and prevent water loss due to evaporation.

As the lixiviant, containing ferric and cupric in a total chloride concentration $>5M$, was extremely corrosive and corrodes stainless steel, equipment was largely made of either glass, titanium, or in some cases plastic was used (e.g. the lids and tubing). The titanium stirrers were made of grade 2, 8mm (5/16 inch) diameter rod, featuring a 6 blade radial design, and were attached via overhead motors. The stirrer was suspended approximately 2.5cm from the bottom of the leach vessel, which was 25cm deep, and each radial blade was 2cm long. The stirrer speed was set at 1000rpm, sufficient to suspend all particles.

Pumping of the leach slurry was conducted using peristaltic pumps and three types of Masterflex tubing, C-Flex, Teflon and polycarbonate.

3.4.2 Temperature control

To achieve a leach temperature of 85°C or 95°C a Haake C1 water bath was used to heat and pump water to the water jacket of each leach vessel. To inhibit evaporation of water from the water bath an insulated lid was used in addition to float balls and slow refilling of the bath, at a low flow rate so as not to decrease the bath temperature. The water bath took about two hours to heat prior to the start of the experiment with the aid of additional heaters, which were removed once the experiment had started.

A copper pipe delivered the hot water from the water bath pump outlet to reinforced plastic tubing, wrapped in insulation tape, which was used to circulate the water from water bath to LS1, from LS1 to LS2 and then from LS2 back to the water bath. Hose clamps were used to tightly secure connections and a water circulation test was performed a day in advance of each experiment to check for leaks.

Teflon coated thermocouples, connected to an external digital reader, were inserted via screw fittings through the lids of both LS1 and LS2 to monitor temperature. Readings were noted at the beginning, middle and end of the residence time for each leach cycle.

3.4.3 Solid-liquid separation

The original intention for the countercurrent circuit was to incorporate two mini-thickeners for S-L separation for LS1 and LS2 slurries. This was hoped to achieve a more continuous process and reduce the errors and difficulties previously associated with using pressure filters for all S-L

separation. However as this mini-thickener was a new design and had not been used before, it has only been used for LS1 S-L separation in this work to investigate function capabilities.

3.4.3.1 Mini-thickener for LS1 slurry S-L separation

A glass mini-thickener (see Figures 14 and 15) 20cm in length, featuring a domed lid (with an internal feed well and four available inlet/outlet ports), a cylindrical glass separating column and a cone shaped underflow exit, was designed for bench-scale S-L separation. The glass lid and body were manufactured by Canadian Scientific Glassblowing Ltd, in Vancouver. A slow moving internal titanium rake, featured in Figure 16, was designed and manufactured via Falconbridge and delivered with an overhead motor, to operate slowly at 6 rpm to aid moving the settled solids through the bottom exit.

A support-stand for the mini-thickener was made in the UBC Department of Metals and Materials Engineering (MMAT) workshop. The support consisted of a curved aluminum backing plate attached to a retort stand and large (15cm) diameter hose clamps were used to hold the thickener to the stand. Clamps were used to hold the lid in position.

A thick, clear, half inch diameter piece of PVC tubing 10cm long was attached to the end of the underflow port which was then connected to smaller diameter tubing before reaching a peristaltic pump. This tube was pinched closed with clamps whilst solids settled.

Figure 14 Mini-thickener design

Figure 15 Photo of mini-thickener

Figure 16 Photo of titanium rake

Rake has three radial arms, radial axis = 4.3cm

The original design of the thickener included side overflow ports to assist in achieving continuous operation (i.e. slurry continually fed to the thickener would result in clarified solution exiting via the overflows). These side ports were sealed and not used in the current work due to bench scale limitations, largely with respect to liquor volumes, and instead a semi-continuous type operation was performed. This was generally achieved by pumping slurry into the central feed well, via an inlet port in the lid, and after the solids had settled fully the clarified liquor (the PLS) was removed by pumping liquor from above the mudline. Once the PLS was removed the underflow exit tube was unclamped and underflow slurry pumped out the bottom exit.

3.4.3.2 Pressure filtration for LS2 slurry S-L separation

A 1.5L capacity pressure filter, manufactured by Advantec MFS Incorporated and lined with polyurethane, was used to filter solids using N₂ at 30-45psi. It was found that for filtering finer solids two filter papers were required to prevent blowout and loss of solids.

3.4.4 Compressed air/oxygen addition to LS2

For goethite model experiments air or oxygen was required for leach stage two to regenerate the oxidant species. The gas ran from a cylinder through clear PVC tubing via a flow meter and then bubbled through a stoppered flask of water before reaching LS2, to signal blockages. The air tube inside the leach vessel was a 9.5mm (3/8 inch) diameter polycarbonate tube about 21cm long.

3.5 Experimental procedures

The original idea for incorporating the mini-thickener in the experimental set-up was to achieve continuous S-L separation. Whilst the mini-thickener did enable an inline, smooth countercurrent transfer of LS1 slurry, into partially leached solids and pregnant leach solution (PLS), the actual experiments in this thesis were performed semi-continuously. This means that within each experiment a series of leach cycles were performed as batch operations in continuous succession. This was largely due to limitations of bench scale work, i.e. with respect to volumes of solution and space, and due to this being the first ever commissioning of the mini-thickener, upon which further tests can build. A photo of the set-up is shown in Figure 17.

Figure 17 Photo of countercurrent leach set-up

The continuous countercurrent leach experiments began with 135g of feed concentrate and 1L of feed liquor in both LS1 and LS2. At the end of the designated residence time countercurrent transfer would occur, new feed concentrate was added to LS1 and fresh feed liquor added to LS2, and this leach/transfer pattern would repeat for 5 or 6 cycles. The first three cycles allow the countercurrent system to reach steady state operation and the following cycles were expected to approach "steady state" and thus indicate true extraction behavior.

Further details of the procedures for the leach experiments follow in three sections, 1) prior to start-up, 2) during the leach cycle and 3) S-L separation and countercurrent transfer.

1) Prior to start-up

The feed liquor was prepared at least a day in advance, allowing time for the solution to cool. The redox potential and pH of the feed solution were then measured at room temperature. The water bath generally took 2hrs to heat (with additional heaters) and circulate water at the operating temperature before the experiment could start. During this time, 1L of feed liquor was added to both LS1 and LS2.

2) During the leach cycle

Once the leach temperature had stabilized, redox potential and temperature were recorded in each leach vessel and then concentrate was added. Temperature and redox potential were then recorded at the midpoint and end of each leach cycle. The pH was measured only in samples taken from each leach stage once they had cooled to room temperature on the bench.

During the leach the following were monitored:

- waterbath operation, temperature and water level;
- stirrer connections;
- thickener rake motor off between transfers, and underflow clamp secured before next loading of the mini-thickener;
- water condenser water flowing; and
- hose clamps secured on water jacket tubing connections.

About 15 min prior to transferring LS1 slurry to the thickener, 10-15mL of 1000 ppm Superfloc® A110 anionic flocculant was added to enable quick and complete settling of solids.

This approximated a dosage of 100-150g per ton of leach solids. The higher dosage (15mL A110) was found necessary for experiments employing finer particle sizes.

3) S-L separation and countercurrent transfer

At the end of the leach residence time, all of the LS1 slurry was pumped from LS1 to the glass-thickener. At the same time, all of LS2 slurry was pumped to a flask for immediate pressure filtration, separating final LS2 leach residues (for further washing and drying) and liquor for transfer to LS1. The LS2 filtrate was measured and recorded prior to addition to LS1, whilst allowing solids in the thickener to completely settle. Figure 18 shows the countercurrent transfer operation and volumes generally transferred.

Figure 18 Mass and volume transfers

Pre-heated fresh feed liquor, 1L, was then added to LS2 and, following complete settling of thickener solids (see Figure 19), the clarified PLS was pumped from above the solids bed, generally leaving around 180-200mL of liquor with 100% of solids for underflow transfer to LS2. After the PLS had been removed and measured, the underflow was pumped to LS2. This process required the operation of the slow moving internal rake to effectively move all settled solids through the underflow bottom exit and prevent any solids clinging to walls or cone of the glass thickener. Reverse pumping was sometimes used to recollect solids that were left behind.

Total transfer time took between 20-30min. Slightly before the underflow transfer to LS2 was complete, fresh concentrate (135g) was added to LS1 and this signaled the beginning of the next leach cycle. The temperature of both LS1 and LS2 at the start of the next leach stage was

recorded, and generally this was slightly lower (~ 5 - 10°C) than the designated leach temperature. However, within 5-10min the leach temperature had been reached.

Figure 19 Thickening operation

An example of the experimental logs used to record temperature, redox potential and pH measurements, samples, and mass and volume transfers can be found in Appendix 6.

3.6 pH and redox potential measurements

Due to problems of probe fouling in previous chloride leach experiments performed at UBC, probes were not left in the leach vessels for any length of time. Hot chloride solutions are very aggressive and combined with solids the resulting slurries are very harsh environments for glass and platinum sensors. Care was taken with both pH and redox electrodes to keep them clean between readings.

When refillable probes were used the hole was covered with tape, to prevent slurry or solution entering the inside chamber of the probe.

3.6.1 pH

Due to the difficulty of preventing pH fouling in hot concentrated chloride solutions, it was determined best to take pH measurements only at room temperature in the filtered samples. Measurements of pH were initially taken with plastic gel filled pH probes that had a paper junction for equilibrium ion transfer. However, the high concentrations of iron in the leach solutions quickly fouled these junctions, turning them brown, and performance rapidly deteriorated. For example, calibration was very slow and soon drift and shortening of the range made calibration nearly impossible. A new probe was then purchased, a ThermoOrion refillable combination electrode with a glass-body, rugged bulb (protected with a plastic shell), and ceramic junction. Cleaning of this probe was significantly better, via disposing of the contaminated inner solution and soaking of the ceramic junction. Refilling of the electrode with 4M KCl (saturated with AgCl) restored the inside environment and maintained electrode operation.

The pH measurements quoted in the results section have not been corrected for liquid junction potential, largely due to the complexity of the concentrated chloride leach solution. Therefore, pH readings mainly serve to indicate comparative trends between the experiments and possibly the values at which copper or iron precipitation may occur. Readings were also generally at ~ pH 0 or lower, significantly under the lowest pH buffer of 1. Free acid measurements in the feed and final PLS provide a better indication of acid consumption and behaviour.

3.6.2 Redox potential

Redox potential, E , measurements were originally performed using a glass body combination Ag/AgCl electrode with a ceramic junction and fine platinum sensor. Not only did the fine platinum sensor bend in the hot leach slurry, after only a few trial experiments the glass body cracked without warning simply upon insertion of the probe into the slurry. This happened twice and for one experiment a Saturated Calomel Electrode was thus used as an immediate backup. An epoxy body Ag/AgCl combination electrode (VWR Symphony Brand) with a flat bottom platinum sensor and free flow junction was subsequently purchased. The filling solution used was 4M KCl saturated with Ag/AgCl, suitable for use in concentrated solutions ($>0.2\text{M}$). Light's solution (see Appendix 5) was used to check redox electrode performance.

Redox potential readings were taken *in-situ* in the leach vessels at the start of the experiment, before addition of concentrate, and at the middle and end of each residence time. During the leach Light's solution was used to check performance of the electrode, and whether drifting or fouling of the electrode had occurred. Generally readings were satisfactory and only sometimes the KCl filling solution would need renewing.

Redox potential measurements were not corrected for temperature and have been quoted in this thesis as mV vs Ag/AgCl at either room or experimental temperature. The measurements have also not been corrected for Light's solution changes during the experiments, unless in one or two cases where they were out by greater than 30 mV. E readings can therefore generally be accepted as accurate to within 20-30mV.

The leach solutions in this research work are highly concentrated and depart significantly from ideal solution behaviour. Therefore, the redox measurements largely serve a comparative purpose between experiments in this thesis.

3.7 Sampling and Analysis

3.7.1 Sample Collection

LS1 and LS2 80mL slurry samples were collected at the end of each residence time, during transfers to the thickener and pressure filter. Approximately 200mL was first allowed to flush

through the pump line and then 80mL was collected in a beaker. The samples were then set-aside on the bench for filtration.

Both LS1 and LS2 samples were prepared in the following manner. The sample was filtered via water vacuum filtration and the filtrate was collected in a small (60mL) plastic sample bottle. The sample was cooled to room temperature, prior to dilution for external analysis and pH measurement.

The solids were then washed with 10x diluted concentrated hydrochloric acid (1/10 HCl) until the filtrate ran colorless. This chloride wash solution was collected for all residue washes, and the total volume was recorded and sent for external analysis. Final washing of the filter cake was with DI water and the cake was then transferred to an oven to dry. Once dry, the weight of the residues were recorded and sample bagged for external analysis.

The final LS2 leach residue sample, collected in the pressure filter, was also treated in the same manner as the residue in the slurry samples. For this residue the weight of the wet cake was recorded in addition to the washed and dried product.

All solution and residue samples were prepared accordingly and sent to IPL for analysis. The final LS2 residue was sent to ChemMet for sulfur group analysis.

3.7.2 Preparation and Analysis

The following samples were sent to IPL for analysis.

The feed liquor and LS1 and LS2 liquor samples from each cycle were diluted 100x (2mL in 200mL) with ~2.5% HCl and analyzed for 30 elements (including Cu and Fe) by ICP. In addition, undiluted samples of the feed liquor and final exit PLS were sent for free acid analysis and ICP 30 element analysis.

Dilutions with only DI water for the feed (100x dilution) and final exit PLS (1000x dilution) were also prepared for total chloride ion analysis via ion selective electrode (ISE).

All solids were sent for 30 element ICP analysis (via aquaregia digestion). The feed concentrate was also analyzed for Total S and SiO₂. Two further samples were sent to ChemMet Consultants, the feed concentrate was analyzed for Au and the final LS2 exit residue analyzed for sulfur group analysis (including total sulfur, elemental sulfur, sulfide and sulfate).

3.7.3 Calculation of copper and iron extraction

An example calculation for determining the extraction of copper and iron can be found in Appendix 7.

4 RESULTS AND DISCUSSION

4.1 Excel mass balance outputs for the hematite and goethite process flowsheets

This section reports the input and output streams of the mass balance for the two chloride process models. For both models 135g pure CuFeS_2 concentrate was introduced to the circuit and it was assumed that 100% of the Cu and Fe in CuFeS_2 was leached and subsequently all of the extracted Cu was removed via SX and all extracted Fe was precipitated (i.e. steady state was maintained), either as goethite or hematite. The models were simplified to include only major reactions, assumed from previous experimental work and the literature. These reactions are reported and discussed. Also, the simplified models consider complete countercurrent transfer of liquor with respect to solids. The models do not account for the small portion of LS1 liquor that would return with thickener underflow to LS2.

For each stream, the copper and iron species are written as single, uncomplexed cations (i.e. Cu^+ , Cu^{2+} , Fe^{2+} , Fe^{3+}) but are assumed to be associated with chloride. These copper and iron species would generally be added to the leach liquor as metal chloride salts and thus contribute to the total background chloride concentration. A concentration of 110 g/L CaCl_2 was used to ensure a concentrated chloride medium $>5\text{M}$. In these simplified models, gypsum (CaSO_4) precipitation is not considered, as minimal sulfate production is expected. A background concentration of HCl was also included in both models although remained constant through the balancing of acid consuming and generating reactions. The result of ensuring this acid balance also assisted in regenerating the oxidant species for recycling to Leach Stage 2.

4.1.1 The hematite process

This model focuses on 3 major process units (see Figure 20), a 2 stage countercurrent leach, copper solvent extraction and iron precipitation in an autoclave. Thus separating the leach residue from iron deportment and producing two waste residues. The input and output streams for LS1, LS2, SX and Autoclave, determined from the mass balance for this flowsheet, are shown below alongside the assumed reactions. The mass of each species is given in grams (g) and the total amount of water, 1000g, is comparable to the quantity used in the experiments and is maintained constant, assuming evaporation of water produced.

Figure 20 Hematite Process

Feed Concentrate, 100% CuFeS₂

135g CuFeS₂ (added to LS1): Cu = 46.7g; Fe = 41.1g; S = 47.2g

Assumed extent of extractions: LS1 = 51.5 %; LS2 = 48.5 %

Leach Stage 2 (LS2)

Liquor, rich in ferric and cupric, is recycled from the autoclave and fed to LS2. Ferric is consumed in the oxidation of CuFeS₂, leaving some ferric and cupric for further leaching in LS1.

Table 9 Hematite Process: LS2 streams

Stream	Cu ⁺	Cu ²⁺	Fe ²⁺	Fe ³⁺	CaCl ₂	HCl	H ₂ O
In	0	50.3	0	80.2	110	2	1000
Out	0	73.0	99.6	0.53	110	2	1000

Leach Stage 1 (LS1)

Ferric is completely consumed in LS1 while the remaining CuFeS₂ is leached with cupric. Sulfur oxidation and atmospheric oxidation of cuprous or ferrous is not considered in this simplified model. As the feed is 100% CuFeS₂ the consumption of acid by soluble minerals is not considered. The exit stream is predominantly reduced species, i.e. cuprous and ferrous.

Table 10 Hematite Process: LS1 streams

Stream	Cu ⁺	Cu ²⁺	Fe ²⁺	Fe ³⁺	CaCl ₂	HCl	H ₂ O
In	0	73.0	99.6	0.53	110	2	1000
Out	95.5	1.54	121.3	0	110	2	1000

Solvent Extraction (SX)

Addition of oxygen to the aqueous phase facilitates 100% extraction of the leached copper (i.e. ~50% of the copper in solution) into the organic phase. To balance acid generated, from the donation of protons from the organic extraction, an equal amount of cuprous is oxidized to cupric.

Table 11 Hematite Process: Solvent Extraction streams

Stream	Cu ⁺	Cu ²⁺	Fe ²⁺	Fe ³⁺	CaCl ₂	HCl	H ₂ O
In	95.5	1.54	121.3	0	110	2	1000
Out	2.01	48.3	0	80.2	110	2	1000

Hematite Precipitation in Autoclave (A/C)

Oxygen is added to the autoclave to enable the precipitation of 100% of leached iron as hematite (Fe_2O_3) via ferrous oxidation. This reaction produces a surplus of acid that is subsequently consumed by cuprous and further ferrous oxidation. This acid balance also achieves 100% regeneration of the required ferric and cupric for recycle to LS2.

Table 12 Hematite Process: Autoclave streams

Stream	Cu^+	Cu^{2+}	Fe^{2+}	Fe^{3+}	CaCl_2	HCl	H_2O
In	2.01	48.3	121.3	0	110	2	1000
Out	0	50.3	0	80.2	110	2	1000

4.1.2 The goethite process

This process focuses only on 2 major process units (see Figure 21). Though the leach is more complex than the hematite model, as oxygen is added to precipitate goethite in LS2, and thus a mixed sulfur/iron residue is produced. The input and output streams for LS1, LS2 and SX, determined from the mass balance for this flowsheet are shown below alongside the reactions considered. As above with the hematite model, the mass of each species is given in grams (g) and the total amount of water, 1000g, is comparable to the quantity used in the experiments and is maintained constant, assuming evaporation of water produced. Oxygen addition is not included below but is assumed to be equal to that required.

Figure 21 Goethite Process

Feed Concentrate, 100% CuFeS₂

135g CuFeS₂ (added to LS1): Cu = 46.7g; Fe = 41.1g; S = 47.2g

Assumed extractions: LS1 = 55 %; LS2 = 45 %.

Leach Stage 2 (LS2)

Cupric in solution, recycled from solvent extraction, facilitates leaching of CuFeS₂. Oxygen is added to enable oxidation of ferrous and subsequent precipitation as goethite. With the excess acid generated from goethite precipitation, cuprous and further ferrous oxidation occurs. The oxygen input required is 17.65g.

Table 13 Goethite Process: LS2 streams

Stream	Cu ⁺	Cu ²⁺	Fe ²⁺	Fe ³⁺	CaCl ₂	HCl	H ₂ O
In	0	48.7	31.1	0	110	2	1000
Out	0	69.7	0.27	8.21	110	2	1000

Leach Stage 1 (LS1)

The small amount of ferric generated in LS2 is consumed in CuFeS₂ leaching and then the remainder of the leach is conducted using cupric. The pregnant leach solution is rich in copper, as cuprous, and the iron content is the same as fed to LS2, as there are no further downstream reactions involving iron.

Table 14 Goethite Process: LS1 streams

Stream	Cu ⁺	Cu ²⁺	Fe ²⁺	Fe ³⁺	CaCl ₂	HCl	H ₂ O
In	0	69.7	0.27	8.21	110	2	1000
Out	93.5	1.93	31.1	0	110	2	1000

Solvent Extraction (SX)

This step is the same as for the previous hematite model. Via the addition of oxygen, cuprous is oxidized to enable extraction into the organic phase and complete cupric regeneration, for recycle to LS2.

Table 15 Goethite Process: Solvent extraction streams

Stream	Cu ⁺	Cu ²⁺	Fe ²⁺	Fe ³⁺	CaCl ₂	HCl	H ₂ O
In	93.5	1.93	31.1	0	110	2	1000
Out	0	48.7	31.1	0	110	2	1000

4.1.3 Feed liquor outputs

For both process models, the concentrations of copper and iron species in the recycled LS2 feed stream, as calculated from the above mass balance, are summarized in the following table. These were used for the preparation of feed liquor for the countercurrent leach experiments.

Table 16 Feed liquor concentrations

Model	Feed Requirements
Hematite	Fe ³⁺ 80 g/L, Cu ²⁺ 50g/L, HCl ~3g/L
Goethite	Fe ³⁺ 0 g/L, Fe ²⁺ 30 g/L, Cu ²⁺ 50g/L, HCl Low (<3g/L)

For the hematite model, sufficient ferric and cupric must be fed to LS2 to enable 100% extraction of Cu and Fe from CuFeS_2 , as there is no additional oxidant addition during LS1 or LS2. For the goethite model, ferric is not required in the LS2 feed as oxygen is added to produce ferric for goethite precipitation and regenerate cupric for further leaching.

One aspect of these models is that ferric is consumed in leaching prior to cupric. Whilst this may be true for a medium with a total chloride concentration of $\sim 4.5\text{M}$, where the standard $\text{Fe}^{3+/2+}$ potential is at 668mV and $\text{Cu}^{2+/+}$ at 581mV, at higher chloride concentrations it is predicted that the copper couple will become more oxidizing than the iron couple. With respect to the models, in which 100% of CuFeS_2 occurs and there is no excess oxidant in the feed, it does not matter for the output feed which oxidant is consumed first. For example, in the hematite model both oxidants are completely consumed, and in the goethite model only a small amount of excess ferric is produced, which is subsequently consumed in CuFeS_2 leaching.

4.2 Overview of continuous countercurrent leach experiments

Twelve continuous countercurrent leach experiments have been performed. The order, experimental identifier ('H' or 'G') and conditions used are shown in Table 17. The experimental identifier indicates upon which process model the leach was based, 'H' representing the hematite (no air in leach) process and 'G' the goethite process (with air/oxygen addition to LS2). The residence time (RT) quoted in the table is per each of the two leach stages.

The first eleven experiments were conducted using Antamina concentrate, varying conditions of residence time, temperature and particle size. The final experiment was performed using fine grind Rosario concentrate, at optimum conditions determined from the eleven previous experiments. For all experiments, to start each experiment 135g of feed concentrate was added to volumes of 1L feed solution, and the background concentration of total chloride, contributed by 110 or 220 g/L CaCl_2 , was aimed at greater than $>5\text{M}$.

The aim of these experiments was to find conditions to achieve maximum copper extraction ($>95\%$) by varying conditions of residence time, temperature and particle size, with both leach models to be investigated. The first four experiments were important in establishing experimental procedures and providing direction for subsequent experiments.

Table 17 Order of experiments

Order	Expt	Feed Concentrate	RT (h)	Total Time (h)	Temp. (C)	Air/O ₂ to LS2 (flow rate)
1	H1	Antamina (p90=75 μ m)	2	10.75	85	No
2	G1		2	10	85	Air (200mL/min)
3	H2		2	10	95	No
4	G2		2	10	95	Air (2.5L/min)
5	H3		3	18	85	No
6	H4		3	18	95	No
7	H5	Antamina (p90= 41 μ m)	3	18	95	No
8	H6		2	12	95	No
9	H7		3	18	85	No
10	H8		2	12	85	No
11	G3		3	18	95	O ₂ (2.5L/min)
12	H9	Rosario (p90=37 μ m)	3	17.5	95	No

For the first four experiments 5 leach cycles were performed, but for subsequent experiments 6 cycles were performed. The first three cycles are necessary for the system to reach steady state, and then actual trend data can be collected. Thus it was considered better to have three end cycles rather than two to provide the trend data.

Some anomalies in total experiment duration exist for two experiments, H1 and H9, due to problems with the waterbath. In both cases the total leach time was extended, to make up for leach time when temperatures were depressed, but overall did not significantly affect the output of the experiments. This is discussed further in the following results sections.

Also in the first experiment, H1, redox measurements were taken using an SCE probe due to a glass body probe breaking immediately before start-up. For all subsequent experiments an epoxy body Ag/AgCl probe was acquired and proved to better withstand leach conditions. For the first

two experiments, H1 and G1, pH measurements were measured on the bench at temperatures slightly above room temperature. However for the remainder of experiments pH was consistently measured only at room temperature.

For the goethite experiments, G1 and G2, oxygen addition was required and this was achieved via sparging compressed air to LS2, in accordance with previous UBC chloride leach experiments. A similar flow rate to those previous experiments, of 200mL/min, was used for experiment G1 but upon recalculation, was later found to be inadequate. It was determined then that 535mL/min would deliver the exact amount of air required (containing ~21% oxygen) over two hours and so a 4.7x excess should be used in experiment G2 to overcome inefficiencies, i.e. 2.5L/min. The impact of the greater airflow delivery to the small leach vessel resulted in a depression in leach temperature of ~4C in LS2 to around 91C. This excess air, however, still did not achieve a significantly greater extraction and so the experimental focus shifted to the hematite leach model for the next 6 experiments. For flow rate calculations see Appendix 7.

The next 2 experiments, H3 and H4, were also performed using the coarse Antamina concentrate completing a series of four hematite model experiments comparing residence time (2h vs 3h) and temperature (85 vs 95C).

Then four experiments, H5-H8, again based on the hematite (no air in leach model) were performed using Antamina concentrate that had undergone fine grinding. These four reflected the experimental matrix of the four previous coarse material experiments (i.e. 2 or 3 h RT at 85 or 95 C).

The final two experiments were performed at optimum conditions determined for the hematite model experiments, using fine grind concentrate, a temperature of 95C and residence time of 3h, applied to the goethite model and an alternate concentrate.

This included one further goethite model experiment (G3) but this time oxygen (98% pure) at a flow rate of 2.5L/min (an excess of 33x) was sparged to leach stage two. The final experiment, H9, was conducted based on the hematite (no air in leach) model at optimum conditions (3h, 95C) using finely ground Rosario concentrate.

The following sections in this chapter present the results of the countercurrent leach experiments. Certificates of analysis for all samples can be found in Appendices 1 and 2, and the Cu and Fe mass accountability performed for all experiments, based on feed material in and samples taken out, can be found in Appendix 8. Profiles of measurements over time for each individual experiment, can be found in the Appendix 9.

4.3 Results of hematite model experiments

Eight experiments based on the hematite leach model were conducted and conditions are shown in Table 18. The first four experiments employed the as received Antamina concentrate (p90 = 75 μ m), varying residence time (2 or 3 hour per leach stage) and temperature (85 or 95C). The successive four (H5-H8) employed fine grind Antamina concentrate (p90 = 41 μ m), similarly varying residence time and temperature. Thus an experimental matrix was completed observing the effect of particle size, residence time and temperature on copper extraction.

Table 18 Hematite model – feed conditions

Experiment (RT, Temp.)	Concentrate	Cl ⁻ [M]	E mV Ag/Ag/Cl ^x (a = vs SCE)	pH ^x	Cu ²⁺ g/L	Fe ³⁺ g/L	Free Acid (as HCl) g/L
H1 (2h, 85C)	Antamina (p90=75 μ m)	7.19	626 ^a	-0.48	47.8	76.7	5.74
H2 (2h, 95C)	Antamina (p90=75 μ m)	7.39	650 ^a	-0.24	47.2	79.9	5.28
H3 (3h, 85C)	Antamina (p90=75 μ m)	7.19	639 ^a	-0.36	52.9	87.2	4.04
H4 (3h, 95C)	Antamina (p90=75 μ m)	7.95	661	-0.35	55.8	90.6	4.04
H5 (3h, 95C)	Antamina (p90=41 μ m)	6.29	677	-0.16	45.0	76.0	2.71
H6 (2h, 95C)	Antamina (p90=41 μ m)	6.35	660	-0.25	41.1	70.2	1.94
H7 (3h, 85C)	Antamina (p90=41 μ m)	8.01	659	-0.68	47.7	80.1	2.96
H8 (2h, 85C)	Antamina (p90=41 μ m)	7.17	661	-0.67	48.0	75.3	3.69

^xmeasured at room temperature

After the first four experiments it was observed that the best conditions for copper extraction involved using a 3h RT at 95C. Therefore for the fifth experiment these conditions were used when first testing the fine grind concentrate in order to see potentially what the maximum extraction would be and if further experiments with this model were worthwhile. Upon achieving very good extractions, >98%, the final three experiments were pursued.

The feed liquor cupric and ferric concentrations, with respect to the mass balance output, were aimed to be 50g/L and 80g/L respectively. In a few of the experiments these concentrations were slightly lower, however as the feed concentrate was not 100% CuFeS₂ (unlike in the model mass balance calculations) this decrease of oxidant in the feed liquor was not a concern. A recalculation of oxidant in the feed (see Appendix 7), based on the actual CuFeS₂ content of the Antamina feed shows that 70g/L ferric and 40g/L cupric are sufficient oxidant concentrations for the feed.

Temperature was maintained within 1-2C from the target leach temperature, except in experiments H1 and H3 when there were slight deviations (due to problems with the water bath). In H1 the temperature in the second cycle dropped, thus the leach was extended for 45 min to compensate, and at the end LS2 was slightly elevated at 88C for the last hour. In H3 there was a slight drop of 2-4C in the last cycle for a period of ~20min, due to a water jacket hose clamp connection loosening. These deviations are not considered significant.

The copper and iron mass balance was calculated for each experiment based on the total in feed materials and outgoing samples, solutions and residues. All of the balances were within acceptable limits, of 95-105% accountability, except for copper in H1, for which copper accountability was 94%, and H3, for which copper accountability was 93%. As these were only out by 2% they were not considered significant.

4.3.1 Potential, pH and free acid

All 8 hematite model experiments, involving Antamina concentrate, exhibited similar potential and pH profiles and trends in free acid consumption. The input feed and final output LS1 and LS2 streams are summarized in Table 19. The E and pH profiles for each experiment are found in Appendix 9 and some representative profiles have been included below.

In accordance with the trend predicted for countercurrent leaching, potential decreased from LS2 to LS1. LS2 is expectedly higher in the countercurrent system due to the fresh feed liquor meeting the partially leached solids from LS1. In these experiments there was a general redox potential gradient of 50-100mV from LS2 down to LS1, with *in-situ* redox measurements for LS2 at 450-550mV_{Ag/AgCl} and LS1 at 400-450mV_{Ag/AgCl}. Examples of representative E profiles for experiments H4 and H5 are shown below in Figures 22 and 23.

Figure 22 E profile for H4(75 μ m, 3h, 95C) **Figure 23 E profile for H5(41 μ m, 3h, 95C)**

The pH profiles for all hematite model experiments revealed a similar trend, showing only slight deviations from the feed value. For all hematite model experiments the free acid was measured in the exit PLS stream and found to be completely consumed. The pH therefore was not affected by the decrease in free acid, owing to the extremely high concentrations of chloride and metals. The free acid was likely consumed in the oxidation of reduced species.

Figure 24 pH profile for H4(75 μ m, 3h, 95C) **Figure 25 pH profile for H5(41 μ m, 3h, 95C)**

Table 19 E, pH and free acid output for hematite experiments

Expt	Stream	E mV _{Ag/Ag/ClX} (except a = vs SCE)	pH (at room temp. except b = at 35C)	Free Acid as HCl (g/L)
H1	Feed	677 ^a	-0.48	5.74
	LS1	416 ^a	-0.01 ^b	not measured
	LS2	509 ^a	-0.04 ^b	
H2	Feed	733	-0.24	5.28
	LS1	453	-0.39	0.18
	LS2	530	-0.41	
H3	Feed	750	-0.36	4.04
	LS1	451	-0.34	<0.01
	LS2	530	-0.31	
H4	Feed	747	-0.35	4.04
	LS1	440	-0.55	<0.01
	LS2	537	-0.37	
H5	Feed	754	-0.16	2.71
	LS1	415	-0.27	<0.01
	LS2	492	-0.13	
H6	Feed	735	-0.25	1.94
	LS1	428	-0.42	<0.01
	LS2	497	-0.33	
H7	Feed	748	-0.68	2.96
	LS1	388	-0.77	<0.01
	LS2	468	-0.71	
H8	Feed	733	-0.67	3.69
	LS1	400	-0.41	<0.01
	LS2	462	-0.73	

^aAt reaction temperature

4.3.2 Copper and iron extraction

The following Table 20 summarizes solids and solution concentrations in the feed and final LS1 and LS2 output streams. The calculated copper and iron extraction values in the final LS1 and LS2 residues are also shown. The profiles of solution and residue concentrations for each experiment can be found in Appendix 9 and representative profiles have been included in the following discussion of the results.

These experiments revealed a consistent trend with respect to CuFeS_2 leaching in varying temperature and residence time with respect to particle size. The copper extraction at steady state in the first four experiments (H1-H4), employing $p_{90} = 75\mu\text{m}$ concentrate, show that increasing the temperature from 85C to 95C had a greater impact on extraction than increasing the residence time from 2h to 3h. Observing the final LS2 extraction data, for experiments H1-H4, the copper extractions were 80% (2h,85C), 87% (2h,95C), 83% (3h,85C) and 93% (3h,95C) respectively.

As >95% copper extraction in chloride media has been well demonstrated by others, the subsequent experiments (H5-H8) were performed using a concentrate of a finer particle size, $p_{90} = 41\mu\text{m}$, in order to achieve higher copper extraction. The first experiment in this series, H5, was thus performed using conditions of 3h residence time and 95C. This experiment was very successful and an average of $\sim 98\%$ copper extraction was achieved. The final three experiments, H6-H8, were then completed to mirror the experimental matrix performed for the $p_{90} = 75\mu\text{m}$ Antamina concentrate, i.e. varying residence time (2 and 3h) and temperature (85 and 95C). The lowest average copper extraction was 90% when a 2h leach stage residence time was employed and conducted at 85C, see H8. Interestingly, experiments H6 (2h, 95C) and H7 (85C), both reported similar copper extraction behavior and a final value of 96%.

The lower values reported for iron extraction have been examined and found to represent iron remaining from unleached CuFeS_2 and iron remaining as undisturbed pyrite (FeS_2).

Examples of representative profiles for solution concentration, Cu and Fe in LS2 residue and Cu and Fe extraction for experiments H4 and H5 are shown in Figures 26-31.

Table 20 Results of hematite model experiments

Expt	Stream	Solution		Solids			Percentage Extn	
		Cu g/L	Fe g/L	Mass g	Cu %	Fe %	Cu %	Fe %
H1	Feed	47.8	76.7	135	28.8	28.4		
	LS1	74.1	101.7	87.6	18.0	23.0	59	47
	LS2	54.1	85.2	44.5	17.5	22.1	80	74
H2	Feed	47.2	79.9	135	28.8	28.4		
	LS1	81.8	114.3	79.3	17.9	19.6	64	59
	LS2	60.1	93.1	63	8.1	12.4	87	80
H3	Feed	52.9	87.2	135	28.8	28.4		
	LS1	86.3	125.1	88.9	20.7	22.0	53	49
	LS2	63.0	100.7	57.7	11.3	16.2	83	76
H4	Feed	55.8	90.6	135	28.8	28.4		
	LS1	94.6	127.9	46.6	21.4	24.3	74	70
	LS2	68.1	102.9	46.9	6.1	12.5	93	85
H5	Feed	45.0	76.0	135	28.3	28.8		
	LS1	86.0	118.0	114	25.0	24.7	27	28
	LS2	71.0	100.0	41	2.0	8.5	98	91
H6	Feed	41.1	70.2	135	28.5	28.7		
	LS1	75.3	103.9	100.1	25.2	24.8	34	36
	LS2	60.8	87.4	46.6	3.7	9.6	96	88
H7	Feed	47.7	80.1	135	28.5	28.7		
	LS1	81.1	112.9	71.5	20.7	21.8	61	60
	LS2	65.4	96.9	43	4.0	10.2	96	89
H8	Feed	48.0	75.3	135	28.5	28.7		
	LS1	80.4	106.5	87	23.0	24.9	48	44
	LS2	63.8	91.5	49.1	7.9	13.36	90	83

Leach Conditions: H4 = 75 μ m, 3h, 95C and H5 = 41 μ m, 3h, 95C

Figure 26 H4: Cu & Fe (%) Extraction

Figure 27 H5: Cu and Fe (%) Extraction

Figure 28 H4: Concentration vs Time

Figure 29 H5: Concentration vs Time

Figure 30 H4: Cu and Fe in LS2 Residue

Figure 31 H5: Cu and Fe in LS2 Residue

4.3.3 Speciation

Both models predict that the exit PLS will contain predominantly reduced species, of iron and copper, and hence downstream purification and recovery steps were balanced accordingly. Theoretical calculations (based on the actual feed concentrate, feed liquor and completeness of leaching) for total reduced species (TRsp) content in the PLS have been performed (an example calculation is included in Appendix 7) and presented in Table 21 along with actual titration values. Both results are compared and variations from the model are discussed, as are implications for downstream processing.

Table 21 Total reduced species of exit PLS and LS2 liquors

Expt	CuFeS ₂ in (mol)	Final Cu extn %	CuFeS ₂ reacted (mol)	TRsp (theoretical) LS1 (M)	Ttl theo. M	TRsp (titration) LS1 (M)	Ttl actual M	TRsp Difference (Theoretical - Titration) (M)	Titration TRsp % of Theoretical	TRsp (titration) LS2 (M)
H2	0.612	87	0.532	2.66	3.24	2.44	3.33	0.22	92	1.02
H3	0.612	83	0.508	2.54	3.41	2.28	3.60	0.26	90	0.78
H4	0.612	93	0.569	2.84	3.64	2.60	3.78	0.24	91	0.88
H5	0.605	98	0.593	2.97	3.26	2.60	3.47	0.37	88	0.88
H6	0.605	96	0.581	2.91	3.07	2.53	3.05	0.38	87	1.48
H7	0.605	96	0.581	2.91	3.35	2.62	3.30	0.29	90	1.22
H8	0.605	90	0.545	2.72	3.19	2.39	3.17	0.33	88	1.30

The calculation for determining the theoretical reduced species concentration takes into account the feed liquor oxidant concentrations and the actual CuFeS₂ reacted for each experiment. It does not matter which oxidant, ferric or cupric, is consumed first in leaching, as both reactions produce the equivalent amount of reduced species, i.e. 5 mol reduced species per mol CuFeS₂ reacted, as shown in equations 4.15 and 4.16.

The titration values reported in the above table are all lower than the theoretical calculation by 0.22-0.33M, and in both cases oxidant was still found remaining in the PLS. To explain the difference between theoretical and titration total reduced species values two things were considered, additional oxidation occurring in the leach liquor during the experiment and error in the titration method.

The first considers that additional cuprous or ferrous may be oxidized by atmospheric oxygen, available in the headspace of the leach vessel, with available acid, HCl. However a calculation of air volume and acid required indicate that between 7-12L of air would be the exact amount of air required to deliver the required oxygen and 8-12g/L HCl would be required. Whilst there may certainly be acid available in the leach solution it is not feasible that the solution would meet with such a volume of ambient air, considering that there is only 1L of headspace in both leach stages. Also an excess of air, above the stoichiometric ratio, would be required to overcome gas transfer limitations. Although not all of the difference can be attributed to atmospheric oxidation a small amount is certainly possible.

It is more likely that cuprous, being incredibly unstable in more dilute solutions of chloride on exposure to air, may have been oxidized during dilution for the titration. In either case, both results indicate that copper and iron species in the PLS stream are not likely to be fully reduced as predicted in the models and downstream implications must be considered.

Complete reduction of the liquor could be achieved by adding copper metal to the stream to reduce the oxidized species prior to downstream processing. This however would not only increase the cost of production but also increase the copper tenor, which is already high. Another alternative is to investigate what the actual impact would be of sending this liquor containing oxidized copper as well as reduced species direct to solvent extraction. The result is actually not detrimental as the following discussion suggests.

The uptake of copper by the organic extractant is actually in the form Cu^{2+} and thus oxidized species would be available without requiring addition of oxygen. However without the complete balance of oxidation of cuprous to cupric there would be an excess of acid produced. Though ferrous is still available and may be oxidized thus consuming acid produced by copper extraction. The following equations (4.17-4.19) demonstrate these reactions.

Thus the stream leaving SX would contain cupric, ferrous and some ferric, which is then available for hematite precipitation.

as opposed to

This may produce a slight excess of acid in the autoclave.

4.3.4 Hematite experiment discussion

Conditions for achieving the highest extraction of copper involved employing a fine grind concentrate, 95C and leaching for 3h in each leach stage. Depending on the copper recovery necessary there may be some flexibility with respect to leach design, due to fairly high extraction rates reported at the lower temperatures or leach residence times. For example, if >95% recovery is sufficient, then using fine grind concentrate and either a 2h residence time at 95C or a 3hr residence time 85C may be sufficient. Should fine grinding of the concentrate be avoided then it may be possible to conduct the leach at 95C with a 3h leach residence time and still achieve a satisfactory copper extraction of around 93%.

4.4 Results of goethite model experiments

Three experiments based on the goethite leach model have been performed and conditions are shown in Table 22. In the first two experiments air (~21% O₂) was added to leach stage 2 to regenerate cupric for further leaching and ferric for goethite precipitation. These first two experiments were not successful in achieving high copper extractions and so for the third experiment fine grind Antamina concentrate was tested and 98% oxygen used as the oxidant source. The flow rate for the third experiment was kept the same as for the second, i.e. 2.5L/min. This was to ensure that an excess (circa. 30x) of oxygen was delivered to overcome inefficiencies and solubility limitations. The calculations for oxygen delivery are contained in Appendix 7.

Table 22 Feed conditions for goethite model experiments

Experiment ^a	Flow rate to LS2	Cl ⁻ [M]	E mV Ag/Ag/Cl ^x	pH	Cu ²⁺ g/L	Fe ³⁺ g/L	Fe ²⁺ g/L	CaCl ₂ g/L	Free Acid (as HCl) g/L
G1 (2h, 85C)	Air (200mL/min)	4.5	463	0.02	54.1	7.9	27.1	110	0.72
G2 (2h, 95C)	Air (2.5L/min)	5.7	457	-0.47	55.9	11.6	22.9	220	10.02
G3 (3h, 95C)	O ₂ (2.5L/min)	5.6	443	-0.29	47.4	4.9	25.1	220	<0.01

^a(residence time per leach stage, temperature); ^x measured at room temperature

In accordance with the calculated feed requirements, liquor concentrations approximated 50g/L cupric, with 30g/L iron as ferrous and a low concentration of ferric. Although experiment G3 had a slightly lower cupric concentration, this was not important as there was additional oxidant available in the feed as ferric and the feed was not 100% CuFeS₂, unlike the mass balance model.

In experiment G1 the background concentration of 110g/L CaCl₂ provided just under 5M total chloride, as a result of the lower content of metal chlorides used in the feed compared to the hematite feed. Thus for further goethite model experiments the background CaCl₂ concentration was raised to 220g/L to ensure a total chloride concentration of 5M. A high chloride content is important for supporting high metal concentrations and maintaining a low pH, however this increase was not thought to be significant for comparison of these experiments.

It was intended that the feed liquor contain a low (<3g/L) concentration of free acid as HCl to promote goethite precipitation. The second experiment G2 however was prepared with a significantly higher HCl content. Whilst this was not a concern regarding copper extraction it was interesting to observe the effect on iron extraction behavior.

The temperatures for the experiments were kept within 1-2C of the set conditions, except for LS2 in experiments G2 and G3 where the temperature was depressed ~4C due to the high flow rate (2.5L/min) of air and oxygen addition.

The copper and iron mass balance was calculated for each experiment based on the total feed liquor and concentrate in and outgoing samples, solutions and residues. All of the balances were within acceptable limits, of 95-105% accountability, except for experiment G1 in which Cu accountability was 88% and iron accountability was 86%. One problem that may have contributed to this poor recovery was the difficulty processing and filtering the sticky, orange goethite residue. Another problem with this experiment was that insufficient oxygen was delivered to LS2 and so overall this experiment can only serve to provide an approximate guide for goethite model leaching. The results of the above goethite model experiments are reported below.

4.4.1 Potential, pH and free acid

The measurements of redox potential, pH and free acid for the input feed and final output LS1 and LS2 streams for the three goethite experiments are summarized in Table 23. Similarly, in accordance with the trend predicted by countercurrent leaching, potential decreased from LS2 to LS1. As the potential of the feed liquor was quite low and the air (~21% O₂) addition was not very high in the first experiment the E gradient from LS2 to LS1 was not very large. In experiment G2 when air addition was substantially increased, the resulting potentials of LS1 and LS2 were still not observed to increase and did not differ from G1. The resulting extraction results, as discussed below, were not very high either and this is further discussed below. Thus air delivery, even in excess, did not seem successful at regenerating oxidant species or even restoring potential to that of the feed value.

A significantly higher oxidation potential was however achieved in the final experiment, G3, with LS2 between 550-600mV_{Ag/AgCl}, when almost pure oxygen (98%) was added to LS2 at a rate of 2.5L/min and thus delivering a 20 times excess. A substantial E gradient was observed across LS2/LS1. This E increase also paralleled a greater copper extraction. Figures 32 and 33 show the E profiles for experiments G2 and G3. This experiment confirmed that copper extraction could be improved by increasing oxidation potential in LS2 and it is likely that >95% copper leach extraction could be achieved with longer leach residence time and further fine grinding of the concentrate.

Table 23 E, pH and free acid output for goethite experiments

Expt	Stream	E mV _{Ag/Ag/Cl} ^x (LS1/LS2 for feed)	pH	Free Acid as HCl (g/L)
G1	Feed	504/524	0.02	0.72
	LS1	439	0.75 ^y	1.5
	LS2	451	0.64 ^y	
G2	Feed	534/571	-0.47	10.02
	LS1	439	-0.04	2.8
	LS2	456	0.54	
G3	Feed	515/580	-0.29	<0.01
	LS1	409	-0.24	<0.01
	LS2	606	0.32	

^xAt reaction temperature; ^y measured at 50C.

Figure 32 E profile for G2(75μm, 2h, 85)

Figure 33 E profile for G3(41μm, 3h, 95C)

Fairly similar pH profiles were observed for all goethite experiments, as shown in Figures 34 and 35. As expected there was greater fluctuation in pH for the goethite experiments, compared to the hematite model, due to LS2 reactions involving acid, i.e. ferrous and cuprous oxidation and iron precipitation reactions. During the first leach cycle, prior to steady state, the pH in LS2 rose sharply but then returned to stabilize at a lower pH. This reflects acid consumption reactions dominating, i.e. oxidant regeneration, until a sufficient acid deficit can drive goethite precipitation. This occurs significantly in G3, in which the feed liquor already had a lower free acid content. In G3, the pH was observed to rise sharply to a value of 2, which is the value at which iron is expected to precipitate in concentrated chloride solutions. Following this first cycle a better balance was achieved between oxidation and precipitation reactions stabilizing the pH at a lower value. A slightly different situation occurred in experiment G2 due to the feed liquor containing a greater concentration of free acid. As a result it appears that pH is stabilized at a moderately low value, and it is likely that oxidation regeneration dominated due to the available concentration of free acid in the feed, and only a small amount goethite precipitation could occur when sufficient acid had been consumed.

Figure 34 pH profile for G2(75 μ m, 2h, 95C)

Figure 35 pH profile for G3(41 μ m, 3h, 95C)

4.4.2 Copper and iron extraction

The following table summarizes solids and solution concentrations in the feed and final LS1 and LS2 output streams. The calculated copper and iron extraction values in the final LS1 and LS2 residues are also shown. The profiles of solution and residue concentrations for each experiment can be found in Appendix 9. The results of sulfur analyses are given in section 4.6.

Table 24 Output concentrations (solution and solids) for goethite model experiments

Expt	Stream	Solution		Solids			Percentage Extn	
		Cu g/L	Fe g/L	Mass g	Cu %	Fe %	Cu %	Fe %
G1	Feed	54.1	35.0	135	28.8	28.4		
	LS1	55.5	27.6	90	25.5	25.4	41	40
	LS2	67.3	29.6	112	13.9	29.8	60	13
G2	Feed	55.9	34.5	135	28.8	28.4		
	LS1	87.9	59.7	93	29.1	26.9	30	35
	LS2	76.7	48.5	78	16.6	23.2	67	53
G3	Feed	47.4	30.0	135	28.5	28.7		
	LS1	93.9	26.2	88	24.5	26.5	44	40
	LS2	79.3	11.3	108	4.0	38.4	89	-7

Experiments G1 and G2, at 2h RT and 85C and 95C respectively, were able to demonstrate leaching only to 60% and 67% copper extraction. Therefore in these conditions, despite delivering a 4.7 times excess of oxygen in experiment G2, copper extraction was not acceptable. Oxygen solubility in hot liquor at atmospheric pressure is likely to be the limiting factor.

With respect to iron, precipitation of goethite in G1 successfully recovered all but 13% of iron, driven by a low free acid in the feed liquor. However, in G2, iron precipitation was inhibited by the presence of 10g/L HCl in the feed liquor, although this had no apparent consequence on copper extraction. The increase of 8% copper extraction from experiment G1 to G2 mirrors the 7% increase in the hematite experiments when a 2h leach stage residence time was used at 85C

the 95C, i.e. H1 and H3. The extraction profiles for copper and iron in experiments G1 and G2 are shown in Figures 36 and 37.

The best result for the goethite model was experiment G3 using Antamina fine grind concentrate (3h RT, 95C) and oxygen (98%) sparging to LS2, instead of air. Following the first three cycles, copper extraction stabilized at 89% and a much higher oxidation potential in LS2 was recorded. The extraction profiles for copper and iron in experiment G3 is shown in Figure 38. A longer residence time and/or finer grinding may lead to achieving >95% copper extraction. Interestingly however iron precipitation was too high in G3, i.e. greater than the amount of iron contained in the feed concentrate, resulting in a negative -7% iron extraction. A greater amount of acid in the feed would reduce iron precipitation, however the value of free acid would be fixed by solvent extraction step for this model. The current precipitation value may however be acceptable providing a greater overall extraction of Cu and Fe from CuFeS_2 can be achieved, or by ensuring that further cycles through the system will achieve an overall iron balance.

Figure 36 G1: Cu & Fe (%) Extraction

Figure 37 G2: Cu & Fe (%) Extraction

Figure 38 G3: Cu & Fe (%) Extraction

4.4.3 Speciation

The following table presents the titration values for total reduced species concentrations, along with total species determined from the addition of copper and iron concentrations, for the feed and final LS1 and LS2 streams. Similarly as with the hematite model, the exit PLS streams all contain a significant portion of oxidized species. However, as the next process step in the goethite model flowsheet is copper solvent extraction the impact on downstream process is insignificant, as discussed previously for the hematite model experiments.

Table 25 Total reduced species in goethite experiments

Expt	Stream	Total Species (M)	Total reduced species (M)	% Total Reduced species
G1	LS1	1.37	0.65	48
	LS2	1.59	0.55	35
G2	LS1	2.45	1.41	58
	LS2	2.08	0.94	45
G3	LS1	1.95	1.12	58
	LS2	1.45	0.09	6

4.4.4 Goethite experiment discussion

The goethite experiments were not successful in achieving greater than 95% copper extraction. Even when conditions were used that had achieved the highest extraction in the hematite model, i.e. fine grind concentrate, 3 hour leach and 95C, and an excess of oxygen was delivered to the leach the highest extraction achieved was 89%. This value was a significant improvement on the experiments employing air addition to LS2, G1 and G2, and by extending residence time and/or finer grinding of the concentrate there is potential for achieving >95% copper extraction.

Although such a large excess of oxygen (circa. x20), as used in experiment G3, would be very unreasonable in scaling up of the process. It is likely that there exists an industrial scale reactor designed to increase oxygen utilization efficiency in a commercial plant, thus improving upon the bench scale system.

Another negative aspect of this model was that the mixed, orange sulfur/goethite leach residue was very sticky and difficult to filter. Not only was filtering slow but the residue encapsulated a significant amount of liquor which required large amounts of 1/10 HCl for washing away soluble copper and iron.

4.5 Application of hematite leach model to Rosario concentrate

The highest copper extraction from the Antamina concentrate in this investigation was achieved employing the hematite model with a fine grind concentrate (p90 = 41 μ m), leach residence time

of 3h and a temperature of 95C. The aim of the final experiment, H9, was to achieve a similarly high copper extraction from a different concentrate under the same conditions. The Rosario concentrate was selected as it is currently of interest. The Rosario concentrate contains a similar amount of copper (26.8%) as the Antamina (28.5%), but contains less CuFeS_2 and an additional copper mineral, chalcocite, Cu_2S . The Rosario concentrate underwent fine grinding prior to the experiment, to a p90 of $37\mu\text{m}$. The conditions of the feed liquor for the Rosario experiment are shown in the following table, and are similar to the conditions for the previous hematite model experiments, H1-8.

Table 26 Feed conditions for Rosario experiment

Experiment ^a	Cl^- [M]	E mV Ag/Ag/Cl^x	pH	Cu^{2+} g/L	Fe^{3+} g/L	CaCl_2 g/L	Free Acid (as HCl) g/L
H9 ($37\mu\text{m}$, 3h, 95C)	7.08	659	-0.41	50.6	82.0	110	2.35

^a(residence time per leach stage, temperature); ^xmeasured at room temperature

During cycles 5 and 6 of this experiment water bath circulation problems significantly disrupted the temperature profile. Interestingly, copper extraction, as discussed below, was not significantly affected.

The mass balance accountabilities for copper and iron, determined from feed and outgoing samples and materials, were 95% and 97% respectively.

4.5.1. Potential, pH and free acid

The potential, pH and free acid trends were similar to those of the other hematite experiments and the results are shown in Table 27 and Figures 38 and 40. The free acid was similarly depleted in the PLS, the pH stayed close to the feed value and the range of LS1 and LS2 E values were $400\text{--}450\text{mV}_{\text{Ag/AgCl}}$ and $450\text{--}550\text{mV}_{\text{Ag/AgCl}}$ respectively.

Table 27 E, pH and free acid

Expt	Stream	E mV _{Ag/Ag/ClX}	pH	Free Acid as HCl (g/L)
H9 (37μm,3h,95C)	Feed	743	-0.41	2.35
	LS1	463	-0.51	<0.01
	LS2	562	-0.53	

^xAt reaction temperature

Figure 39 E profile for H9(37μm,3h,95C)

Figure 40 pH profile for H9(37μm,3h,95C)

4.5.2 Copper and iron extraction

Table 28 reports the successful output data for the final hematite experiment. Not only was the final copper extraction 98%, by the end of the first leach stage 96% extraction had already been achieved. The presence of Cu_2S in this material thus indicates that it is easier to leach than a predominantly CuFeS_2 concentrate, and, as a result thereof, the required leaching time is significantly decreased. The following equation (4.22) is shown for Cu_2S leaching. The unleached iron in the residue was examined and found to contain represent undisturbed pyrite.

Table 28 Output concentrations (solution and solids) for the Rosario experiment

Expt	Stream	Solution		Solids			Percentage Extn	
		Cu g/L	Fe g/L	Mass g	Cu %	Fe %	Cu %	Fe %
H9 (37 μ m, 3h, 95C)	Feed	50.6	82.0	135	26.8	26.8		
	LS1	91.7	100.5	76.3	2.1	28.3	96	40
	LS2	55.1	84.9	68.6	1.1	27.5	98	48

Figure 41 Cu & Fe (%) Extraction for H9(37 μ m,3h,95C)

4.6 Sulfur balance

The feed concentrate was analyzed for Total sulfur (S), and the final LS2 leach residue of each experiment was analyzed for total S, elemental S, sulfide (S^{2-}) and sulfate (SO_4^{2-}). The sulfur group analyses in the final LS2 residue of each experiment are shown in Table 29.

Table 29 Sulfur species in Final LS2 residues

Expt	Elemental (%)	Sulfide (%)	Sulfate (%)
H1	28.0	23.9	0.91
H2	50.4	15.0	<0.1
H3	39.6	16.6	<0.1
H4	42.0	13.9	<0.1
H5	49.8	9.91	<0.01
H6	56.5	11.8	<0.01
H7	53.6	11.4	0.02
H8	46.8	14.4	<0.01
H9	23.1	34.1	<0.01
G1	15.0	16.0	1.33
G2	24.2	21.3	0.12
G3	20.4	6.68	1.09

The residue (<10g) from the slurry sample taken from LS1 was not however analyzed for sulfur, and to calculate the sulfur mass balance an expected loss of sulfur from LS1 was determined based on Cu and Fe concentrations in the sample. Table 30 reports these sulfur values and presents the sulfur balance.

The generally very low amounts of sulfate indicate almost 100% yield of elemental sulfur. The hematite model experiments produced a mainly elemental S residue, with some sulfide remaining from unleached $CuFeS_2$ and/or FeS_2 . For the goethite model experiments, elemental sulfur was also the major reaction product left in the residue along with goethite ($FeOOH$). For both models, there was no significant amount of sulfate in the exit leach residues. This correlates

previous reports of minimal oxidation of elemental sulfur to sulfate, which would precipitate with gypsum in these experiments. A small but insignificant amount of sulfate was detected in the first and final goethite experiments, the two in which goethite was successfully precipitated with the residue.

Table 30 Sulfur recovery

Expt	Total S in (g)	LS2 Output Mass (g)	Total Sulfur in LS2 (%)	S out of LS2 (g)	Est'd S out of LS1 sample (g)	Total S out (g)	S out/in (%)	S in - S out (g)	Final Cu ext'n (%)
H1	43.3	44.5	53.2	23.7	4.0	27.7	64	15.6	80
H2	43.3	63.0	65.6	41.3	3.3	44.6	103	-1.3	87
H3	43.3	57.7	56.2	32.4	2.9	35.4	82	8.0	83
H4	43.3	46.9	55.9	26.2	2.5	28.7	66	14.6	93
H5	43.8	41.0	59.8	24.5	3.5	28.0	64	15.7	98
H6	43.8	46.6	68.3	31.8	3.4	35.2	80	8.6	96
H7	43.8	43.0	65.0	28.0	3.2	31.2	71	12.6	96
H8	43.8	49.1	61.1	30.0	3.7	33.7	77	10.1	90
H9	48.0	68.6	57.2	39.2	6.1	45.3	95	2.6	98
G1	43.3	112.4	32.6	36.6	2.8	39.4	91	3.9	60
G2	43.3	77.8	45.5	35.4	2.4	37.8	87	5.5	68
G3	43.8	108.2	28.2	30.5	4.1	34.6	79	9.1	89

The sulfur balance for nearly all experiments does not lie within acceptable limits, 95-105%, despite acceptable copper and iron balances. There appears to be a loss of S in the range of 5-15g across all experiments. Reasons for this are not clear other than to consider the possibility of loss of residue or slurry.

It was observed in the hematite experiments, that the light sulfur residue would tend to float to the top and stick to the walls of the flask or thickener. This indicates potential for loss of sulfur from the final residue and may have a significant effect on the balance. It is indeed the sulfur

balance of the hematite experiments that report the greatest lack of accountability of sulfur (up to 15g).

The three goethite model experiments and the final Rosario leach experiment reported better sulfur recovery figures, with a lack of accountability between 2.6-9.1g. These residues contained a significant amount of goethite or pyrite that may have helped bond the residue together and prevented floating or frothing of the lighter sulfur.

In scaling up of the process, attention to engineering design would address the lack of sulfur accountability in the leach residue.

4.7 Trace Metals

All the elements reported in ICP analysis were examined to determine which other elements were leached with copper. The following table reports the extraction values of these elements in the final LS2 residues of three experiments, and includes copper and iron extractions for comparison. Silver (Ag), chromium (Cr), lead (Pb), magnesium (Mg), nickel (Ni) and zinc (Zn) all reported significantly high extractions, i.e. all generally above 90%. This indicates the suitability of chloride leaching for complex sulfides.

Table 31 Trace metal analysis

Element	Extraction % in final LS2 residue		
	H5 (41µm,3h,95C)	G3 (41µm,3h,95C,O ₂ to LS2)	H9 (Rosario,3h,95C)
Ag	97.1	92.4	98.9
Cd	not in feed	not in feed	100.0
Cr	92.1	46.2	93.9
Cu	98.2	88.7	97.9
Fe	91.1	-7.0	47.7
Pb	99.9	99.7	94.3
Mg	96.7	93.4	95.5
Ni	93.0	90.1	92.4
Zn	98.9	98.4	98.7

5 CONCLUSIONS AND RECOMMENDATIONS

5.1 Model mass balances

Two new process flowsheets, the Goethite Process and the Hematite Process, were developed and the successful completion of mass balances shows potential for both circuits particularly in addressing current purification difficulties and waste management issues. Solvent extraction (SX) is known to be a very effective method of selective uptake of copper from sulfate leach liquor, for transfer to the electrowinning circuit with minimal impurity transfer, and is expected to work well for a chloride system. As goethite (FeOOH) is a less stable iron residue in the environment than hematite (Fe_2O_3) it is important to have two process options because in some localities goethite will not be accepted in waste for disposal.

The mass balances were also useful in determining feed liquor requirements for the leach. Although these models were simplified, considering only major reactions and assumed complete extraction of chalcopyrite, they were still beneficial and successfully tested in the continuous countercurrent leach experiments. Whilst the aqueous processing assumptions were fairly accurate with respect to the experimental outcomes, the delivery of gas containing oxygen did not perform as well as the goethite model intended in an atmospheric leach system. Both Goethite and Hematite Processes did however improve upon a previously proposed flowsheet in which air was added to leach stage two in addition to use of an autoclave downstream for iron recovery, thus requiring careful control so as not to precipitate iron in the leach. In the two current models investigated in this thesis, either oxygen was added to the leach to precipitate iron or an autoclave was incorporated downstream, therefore clearly defining at which part of the process iron deportment would occur.

5.2 Implementation of the mini-thickener

The mini-thickener proved very useful in achieving consistent operation for all countercurrent continuous-batch experiments. Complete transfer of the solids was achieved from LS1 to LS2 and the transfer of leach liquor volumes could be carefully tracked. In previous UBC chloride leach testing, a more continuous countercurrent leach system was investigated in which half the slurry was removed and countercurrently transferred at each half-residence time. However, it was difficult to accurately take out half each time and use of the pressure filter, for S-L separation, was difficult to perform cleanly. The transfer time in this investigation was still

comparable to previous work, at 20-30min, but as the LS1 S-L separation was achieved inline via the mini-thickener the transfer operation was much smoother. Following from this initial testing of the mini-thickener, it is feasible that future work could potentially incorporate two mini-thickeners, for both LS1 and LS2 S-L separation, in addition to working towards a more continuous operation. This would likely involve slurry being continuously fed to the thickener and the overflow ports being used to slowly remove clarified pregnant leach solution.

5.3 Countercurrent leach experiments

The countercurrent leach experiments performed for the hematite model were successful in demonstrating the effect of varying particle size, leach time and temperature to achieve copper extractions >95%. There are three hematite process variations possible if 96% extraction is sufficient. All three involved fine grind concentrate (p90=41 μ m) with either a 2h residence time at 95C (96% extraction), a 3h residence time at 85C (96% extraction) or a 3h residence time at 96C (98% extraction). The benefits of this model include a relatively straightforward 2-stage leach (in which all the oxidant required is fed as aqueous species to LS2) and the separation of sulfur leach residue from iron precipitate, thus making reuse or waste treatment easier. The substitution of NaCl for CaCl₂ may be possible for the hematite model as there is no iron precipitation in the leach, and hence there is no concern for jarosite formation, as in previous Falconbridge Copper Chloride Process experiments undertaken at UBC. This substitution would reduce processing cost. The goethite model experiments were unsuccessful in achieving >95% extraction of copper, with the highest extractions stabilizing at 89%. However a longer residence time or finer grinding may be investigated to achieve higher extractions for this model. Alternatively, use of an autoclave for Leach Stage 2 may overcome oxygen solubility limitations and in turn may assist in the increase of copper extraction. With respect to fine grinding, although potentially costly and energy intensive, grinding to 20microns is considerably more feasible than grinding to 10microns or less, as is required for some competing sulfate based leach processes.

5.4 Recommendations for further work

Following the success of the leaching aspect of the hematite model it would now be recommended to test the subsequent process units with respect to the actual exit liquor arising from the leach or relevant previous process unit. Thus for solvent extraction a feed should be

tested containing variations of reduced and oxidized copper and iron species, instead of assuming a feed containing only reduced species.

Further work should also involve development of a more continuous countercurrent leach employing the use of two mini-thickeners for LS1 and LS2 S-L separation.

6. REFERENCES

1. Peters, E. (1977) Applications of chloride hydrometallurgy to treatment of sulphide minerals, *Proceedings of Chloride Hydrometallurgy*, Brussels, Benelux Metallurgie, 1-37.
2. Szymanowski, J. (1996) Copper hydrometallurgy and extraction from chloride media, *J.Rad. and Nuc. Chem., Articles*. Vol.208, No.1:183-194
3. Winand, R. (1991) Chloride hydrometallurgy, *Hydrometallurgy*, 27:285-316
4. Dutrizac, J.E. (1992) The leaching of sulphide minerals in chloride media, *Hydrometallurgy*, 29:1-45
5. Drescher, W.H. (2001) How hydrometallurgy and the SX/EW process made copper the "green" metal, article in *Innovations*, online publication of the Copper Development Association, www.copper.org, August.
6. Hackl, R.P., Dreisinger, D.B., Peters, E. and King, J.A. (1995) Passivation of chalcopyrite during oxidative leaching in sulfate media, *Hydrometallurgy*, 39, 25-48.
7. Dreisinger, D.B., Marsh, J. and Dempsey, P. (2003) The Anglo-American Corporation/University of British Columbia (AAC/UBC) chalcopyrite copper hydrometallurgy process, *Cobre 2003*, 5th International Conference, Santiago, Chile.
8. Flett, D.S. (2002) Chloride hydrometallurgy for complex sulphides: a review, *CIM Bulletin*, Vol 95, Issue 1065, 95-103.
9. Fisher, N. (2001) Counter current leaching of chalcopyrite in cupric/ferric chloride media, Falconbridge Copper Chloride Leaching Project Report, University of British Columbia, Vancouver.
10. Wilson, J.P. and Fisher, W.W. (1981) Cupric chloride leaching of chalcopyrite, *Journal of Metals*, February, 52-57.
11. Berger, J.M. and Winand, R. (1984) Solubilities, densities and electrical conductivities of aqueous copper (I) and copper (II) chlorides in solutions containing other chlorides such as iron, zinc, sodium and hydrogen chlorides, *Hydrometallurgy*, 12:61-81.
12. H.S.C. Chemistry Software version 4.0 (Eh-pH diagrams) Outokumpu
13. Dixon, D. G. (1997) Chloride-based leaching of sulfides: principles and practice, a short course for the Industrial Research Chair in Hydrometallurgy, University of British Columbia, Vancouver.
14. Chiswell, B. and James, D.W. (1969) *Fundamental Aspects of Inorganic Chemistry*, John Wiley and Sons Australasia Pty Ltd, Australia.
15. Duby, P. (1977) INCRA Monograph IV, The metallurgy of copper: the thermodynamic properties of aqueous inorganic copper systems, (New York: International Copper Research Association)

16. Lin, H.K., Wu, X.J. and Rao, P.D. (1991) the electrowinning of copper from a cupric chloride solution, *JOM*, August, 60-65.
17. Weast, R.C. (2002) CRC handbook of chemistry and physics, 3rd electronic edition, <http://www.hbcpnetbase.com/hbcp/>. (4 April 2002).
18. Sillen. L. G. (1964) Stability constants of metal-ion complexes, Sect.1: In-organic Compounds, special pub. No.17 (London: the Chemical Society).
19. Martell, A.E. and Smith, R.M. (1974) Critical stability constants, New York : Plenum Press.
20. Linke, W. F. (1958-1965) Solubilities, inorganic and metal-organic compounds; a compilation of solubility data from the periodical literature. 4th ed. [Washington, D.C.] : American Chemical Society.
21. Bonan, M, Demarthe, J.M., Renon, H. and Baratin, F. (1981) Chalcopyrite leaching by CuCl_2 in strong NaCl solutions *Metallurgical Transactions B* Vol.12B: 269-274.
22. Hayes, P.C. (1993) Process principles in minerals and materials production, Hayes Publishing Co., Brisbane QLD Australia.
23. Muir, DM (2002) Basic principles of chloride hydrometallurgy, Chloride Metallurgy 2002, 32nd Annual Hydrometallurgy Meeting, Vol.2.
24. Peters, E. (1976) Direct leaching of sulfides: chemistry and applications, *Metallurgical Transactions B*, Vol.7B: 505-517.
25. Jones, D.L. (1974) The leaching of chalcopyrite, Ph.d. Thesis, Department of Metals and Materials Engineering, University of British Columbia.
26. Dutrizac J.E. (1978) The kinetics of dissolution of chalcopyrite in ferric ion media, *Metallurgical Transactions B*, Vol.9B: 431-439.
27. Haver, F.P. and Wong, M. M. (1971) Recovery of copper, iron and sulfur from chalcopyrite concentrate using a ferric chloride leach, *Journal of Metals*, February, 25-29.
28. Dutrizac J.E. (1981) The dissolution of chalcopyrite in ferric sulfate and ferric chloride media, *Metallurgical Transactions B*, Vol.12B: 371-378.
29. Dutrizac J.E. (1982) Ferric ion leaching of chalcopyrites from different localities, *Metallurgical Transactions B*, Vol.13B: 303-309.
30. McDonald, G.W., Udovic, T.J., Dumesic, J.A. and Langer, S.H. (1984) Equilibria associated with cupric chloride leaching of chalcopyrite concentrate, *Hydrometallurgy*, 13: 125-135.
31. Hirato, T., Kinoshita, Y., Awakura, Y. and Majima, H. (1986) The leaching of chalcopyrite with ferric chloride, *Metallurgical Transactions B*, Vol.17B: 19-28.
32. Hirato, T., Majima, H. and Awakura, Y. (1987) The leaching of chalcopyrite with cupric chloride, *Metallurgical Transactions B*, Vol.18B: 31-39.
33. O'Malley and Liddell, K.C. (1987) Leaching of CuFeS_2 by aqueous FeCl_3 , HCl and NaCl : Effects of solution composition and limited oxidant, *Metallurgical Transactions B*, Vol.18B: 505-510.

34. Dutrizac, J.E. (1990) Elemental sulphur formation during the ferric chloride leaching of chalcopyrite, *Hydrometallurgy*, 23:153-176
35. Lotens, J.P. and Wesker, E. (1987) The behaviour of sulphur in the oxidative leaching of sulphidic minerals, *Hydrometallurgy*, 18:39-54
36. Chen, T.T. and Cabri, L.J. (1986) Mineralogical overview of iron control in hydrometallurgical processing, Chapter 1:19-55 in Iron control in hydrometallurgy, Eds: J.E. Dutrizac and A.J. Monhemius, Ellis Horwood series in industrial metals. Chichester : E. Horwood ; New York : Halsted Press.
37. Riveros, P.A. and J.E. Dutrizac (1997) The precipitation of hematite from ferric chloride media, *Hydrometallurgy* (46) 85-104.
38. Hoffman, J.E. (1991) Winning copper via chloride chemistry – an elusive technology, *JOM*, August, 48-49.
39. Hyvarinen, O. and Hamalainen, M. (1999) Method for producing copper in hydrometallurgical process, US Patent, 6,007,600.
40. Schweitzer, F.W. and Livingstone, R.W. (1982) Duval's CLEAR hydrometallurgical process, In: P.D.Parker (Ed), Chloride Electrometallurgy, TMS-AIME, New York, 221-227.
41. Moyes, J. and Houlis, F. (1999) The INTEC copper process, Copper '99, Arizona.
42. Moyes, J. (2000) A revolution in copper – the Intec copper process, January, Sydney, Australia.
43. Dalton, R.F., Diaz, G., Price, R. and Zunkel, A.D. (1991) The cuprex metal extraction process: recovering copper from sulfide ores, *JOM*, August, 51-56.
44. Ferron, C.J., Williamson, R.G. and Zunkel, A.D. (1996) Metal recovery from a complex sulphide concentrate using a ferric chloride leach process, Minerals, EPD Congress, California, Metals and Materials Society/AIME (USA), 181-192.
45. Demarthe, J.M., Gandon, L. and Georgeaux, A. (1976) A new hydrometallurgical process for copper, In: J.C.Yannopoulos and J.C.Agarwal (Editors), Extractive Metallurgy of Copper, TMS-AIME, New York, 825-848.
46. Demarthe, J.M. and Georgeaux, A. (1978) Hydrometallurgical treatment of complex sulphides, Complex Metallurgy '78, IMM, 113-120
47. Satchell, D.P. and Gerlach, J.N. (1986) Chloride hydrometallurgical process for production of copper, US Patent, 4,594,132.
48. Fletcher, A.W., Sudderth and Olafson, S.M. (1991) Combining sulfate electrowinning with chloride leaching, *JOM*, August, 57-59.
49. Kordosky, Gary (1999) Copper solvent extraction coupled with concentrate leaching, a short course presented at Copper '99, Arizona.

50. Kordosky, Gary (1999) Solvent extraction and electrowinning of copper from concentrate leaching solutions I, solvent extraction of metals, a short course presented at Copper '99, Arizona.
51. Tinkler, O. (1999) Solvent extraction and electrowinning of copper from concentrate leaching solutions II, hydrometallurgical processing of concentrates, Copper '99, Arizona.

Sample identification guide for Appendices 1 and 2

The following table provides a guide indicating to which experiment the samples in the certificates of analysis belong, e.g. H1 has an original experiment identification number of 7 and 'M' and 'N' represent LS1 or LS2 samples respectively. The concentrate samples analyzed are also identified in Table 33.

Table 32 Sample identification guide

Experiment	Identifier	Original Identification Number	Samples LS1, LS2
1	H1	7	7M, 7N
2	G1	8	8P, 8Q
3	H2	9	9K, 9L
4	G2	10	10J, 10K
5	H3	11	11C, 11D
6	H4	12	12M, 12N
7	H5	13	13G, 13H
8	H6	14	14V, 14W
9	H7	15	15S, 15T
10	H8	16	16X, 16Y
11	G3	17	17K, 17L
12	H9	18	18A, 18B

Table 33 Concentrate sample identification

Concentrate	Sample I.D.
Antamina	AN
Rosario	RO

Appendix 1 Certificates of Analysis (IPL)

Certificate#: 02F0668
 Client: Metals & Materials Eng UBC
 Project: BD28F06 CBUY 713000
 No. of Samples: 7
 Date In: Jun 28, 2002
 Date Out: Jul 02, 2002

Sample Name	SampleType	S(tot) %	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm	Mo ppm	Tl ppm	Bi ppm	Cd ppm	Co ppm	Ni ppm	Ba ppm
#1 JLCOA	CoarsePulp	32	58.7	485512	216	2349	502	59	<3	1725	<10	<2	75.9	103	15	20
#2 JLCOB	CoarsePulp	31.78	55.6	454054	199	2291	495	58	<3	1493	<10	<2	72.6	98	15	20
#3 JLLP	CoarsePulp	27.08	634.3	204460	2952	16562	12690	276	<3	370	<10	<2	297.9	72	38	6
#4 JLKCA	CoarsePulp	34.55	495.7	305804	5347	28096	328	<5	<3	12	<10	<2	88.7	405	196	20
#5 JLKCB	CoarsePulp	34.51	475.8	306440	5416	27358	307	<5	<3	15	<10	<2	89.4	409	219	15
#6 JLA	CoarsePulp	32.08	199.7	295941	3573	24074	1451	72	<3	1596	<10	<2	19.7	93	10	10
#7 JLS	CoarsePulp	34.18	90.3	330960	282	1325	<5	<5	<3	16	<10	<2	<0.1	92	3962	22
Minimum detection		0.01	0.1	1	2	1	5	5	3	1	10	2	0.1	1	1	2
Maximum detection		100	100	20000	20000	20000	10000	1000	10000	1000	1000	10000	100	10000	10000	10000
Method		AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Sample Name	SampleType	W ppm	Cr ppm	V ppm	Mn ppm	La ppm	Sr ppm	Zr ppm	Sc ppm	Ti %	Al %	Ca %	Fe %	Mg %	K %	Na %	P %
#1 JLCOA	CoarsePulp	<5	5	11	22	3	12	4	2	<0.01	0.08	0.07	18.94	0.02	0.02	0.02	<0.01
#2 JLCOB	CoarsePulp	<5	5	11	20	4	13	8	3	<0.01	0.08	0.07	18.62	0.02	0.04	0.03	<0.01
#3 JLLP	CoarsePulp	15	29	28	396	2	41	10	1	0.01	0.23	3.39	25.11	0.3	0.03	0.04	<0.01
#4 JLKCA	CoarsePulp	<5	4	15	54	7	3	19	2	<0.01	0.08	0.08	30.03	0.05	0.01	0.02	<0.01
#5 JLKCB	CoarsePulp	<5	4	15	51	6	3	20	2	<0.01	0.08	0.09	29.83	0.05	0.01	0.03	<0.01
#6 JLA	CoarsePulp	<5	3	20	441	<2	5	7	1	0.01	0.15	0.74	27.8	0.05	0.03	0.03	<0.01
#7 JLS	CoarsePulp	<5	8	18	28	<2	3	7	2	0.01	0.06	0.08	31.44	0.09	0.02	0.03	<0.01
Minimum detection		5	1	2	1	2	1	1	1	0.01	0.01	0.01	0.01	0.01	0.01	0.01	0.01
Maximum detection		1000	10000	10000	10000	10000	10000	10000	10000	1	10	10	10	10	10	5	5
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate#: 02G0735
 Client: Metals & Materials Eng UBC
 Project: BD28F06 CBUY 713000
 No. of Samples: 6
 Date In: Jul 15, 2002
 Date Out: Jul 17, 2002

Sample Name	SampleType	SiO2 %
JLCO	Pulp	4.21
JLLP	Pulp	9.89
JLKC	Pulp	1.63
JLANA	Pulp	3.95
JLANB	Pulp	4.07
JLST	Pulp	1.42
Minimum detection		0.01
Maximum detection		100
Method		AsyFus

Certificate#: 03B0145
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 1
 Date In: Feb 10, 2003
 Date Out: Feb 12, 2003

Sample Name	SiO2 %	S(tot) %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm	Pb ppm	Mg ppm
RO1 (Sample type = pulp)	6.93	36.01	956	<5	619	10	<2	60.3	661	6	91	284814	301542	<2	456	485
Minimum detection	0.01	0.01	100	5	5	2	2	0.1	100	1	1	1	100	2	2	100
Maximum detection	100	100	50000	1000	10000	10000	10000	100	100000	10000	10000	20000	50000	10000	20000	100000
Method	AsyFus	AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Sample Name	Mn ppm	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Tl ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
RO1 (Sample type = pulp)	173	<3	1023	19	1657	379	2	53.4	<100	7	<10	<100	<5	25	10361	5
Minimum detection	1	3	1	1	100	100	1	0.1	100	1	10	100	5	2	1	1
Maximum detection	10000	10000	1000	10000	50000	100000	10000	100	50000	10000	1000	10000	1000	10000	20000	10000
Method	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate# 03E0585
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 8
 Date In: May 12, 2003
 Date Out: May 16, 2003

Sample Name	SampleType	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm	Pb ppm	Mg ppm	Mn ppm
7S	Pulp	1271	54	1553	4	<2	<0.2	7634	3	80	275429	291879	<2	3336	379	404
7M2S	Pulp	813	78	2087	16	<2	<0.2	22604	7	64	215394	240584	<2	42	266	63
7M3S	Pulp	1435	95	2185	4	<2	<0.2	31118	5	58	182023	205214	<2	406	458	92
7M5S	Pulp	1636	98	2247	16	<2	<0.2	22355	6	80	179516	225093	3	32	580	104
7N2S	Pulp	1255	82	2179	5	<2	<0.2	4200	41	77	188225	236364	<2	33	414	73
7N3S	Pulp	1717	107	2561	8	<2	<0.2	23361	26	68	157060	197191	<2	46	1322	103
7N5S	Pulp	935	105	2711	7	<2	<0.2	4911	18	76	182416	227485	<2	20	344	68
7N5Bulk	Pulp	1151	91	2388	9	<2	<0.2	16086	20	68	177507	213839	<2	14	524	75
Minimum detection		100	5	5	2	2	0.2	100	1	1	1	100	2	2	100	1
Maximum detection		50000	2000	10000	10000	2000	2000	100000	10000	10000	10000	50000	10000	10000	100000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP
Sample Name	SampleType	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Ti ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
7S	Pulp	<3	1095	4	<100	390	2	167.1	188	4	<10	<100	48	18	22392	7
7M2S	Pulp	<3	2442	3	<100	256	<1	67.1	326	14	<10	109	20	13	8399	6
7M3S	Pulp	<3	5013	<1	<100	295	<1	58.4	540	20	<10	188	13	8	10493	7
7M5S	Pulp	<3	2665	16	<100	387	1	69.8	2932	16	<10	183	24	11	10406	8
7N2S	Pulp	<3	5255	8	<100	231	<1	60	637	1	<10	176	31	9	5017	10
7N3S	Pulp	<3	3562	10	<100	477	<1	52.6	2010	15	<10	219	17	10	6131	11
7N5S	Pulp	<3	2585	10	<100	266	<1	59.6	533	2	<10	142	18	11	6891	8
7N5Bulk	Pulp	<3	2316	<1	<100	346	<1	58.1	677	8	<10	157	20	11	6640	13
Minimum detection		3	1	1	100	100	1	0.1	100	1	10	100	5	1	1	1
Maximum detection		10000	1000	10000	50000	100000	10000	100	100000	10000	1000	100000	1000	10000	100000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate#: 03E0586
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 7
 Date In: May 12, 2003
 Date Out: May 16, 2003

Sample Name	Sample Type	Cl- mg/L	F.A. HCl G/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L	Mg mg/L
7L	Solution	255242	5.74	21.4	<0.1	10	0.41	<0.1	<0.01	30284.6	15.82	3.54	47757.15	76721.8	<0.05	3.49	3.3
7M2	Solution	N/A	N/A	173.6	<0.1	48.4	<0.01	<0.1	<0.01	27113	21.78	10.47	86042.63	113767.16	<0.05	822.38	50.2
7M3	Solution	N/A	N/A	102.3	<0.1	41.7	0.11	<0.1	<0.01	27190.8	26.12	8.17	71829.57	98135	<0.05	405.17	29.2
7M5	Solution	N/A	N/A	106.7	0.3	44.6	0.11	<0.1	<0.01	28031.1	25.91	8.4	74088.58	101694.75	<0.05	448.62	30.2
7N2	Solution	N/A	N/A	39.1	<0.1	16.3	0.41	<0.1	<0.01	29811.5	16.17	4.5	51127.19	82328.09	<0.05	38.5	8.8
7N3	Solution	N/A	N/A	47.2	<0.1	19.7	0.37	<0.1	<0.01	29968.7	16.63	5.23	58809.84	88101.77	<0.05	61.22	12.2
7N5	Solution	N/A	N/A	41.4	<0.1	16.6	0.39	<0.1	<0.01	30212.9	16.73	4.74	54059.48	85188.92	<0.05	43.09	9.7
Minimum detection		0.5	0.01	0.2	0.1	0.2	0.01	0.1	0.01	0.1	0.01	0.01	0.01	0.03	0.05	0.05	0.1
Maximum detection		1000	1000	9999	9999	9999	999	9999	999	9999	9999	9999	9999	9999	999	9999	9999
Method		CH-SE	Env	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Sample Name	Sample Type	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L
7L	Solution	499.34	<0.05	1.22	9.64	<0.1	91	0.21	<0.02	1732	7.11	<0.2	2.9	11.5	6.69	42.61	2.09
7M2	Solution	617.46	<0.05	3.99	13.38	<0.1	122	0.39	17.94	1769	4.15	<0.2	3.4	10.2	10.41	4420.7	3.07
7M3	Solution	572.55	<0.05	3.89	15.97	<0.1	109	0.37	16.34	1775	5.31	<0.2	3	9.9	9.52	2447.75	2.77
7M5	Solution	577.46	<0.05	3.87	16.97	<0.1	108	0.37	16.68	1819	5.52	<0.2	3.3	9.6	9.69	2508.61	2.97
7N2	Solution	531.92	<0.05	1.7	10.27	<0.1	95	0.24	2.12	1828	7.31	<0.2	3.5	9.5	7.47	551.46	2.29
7N3	Solution	527.35	<0.05	1.84	8.99	<0.1	100	0.3	4.66	1817	6.81	<0.2	4	10.4	8.34	682.7	2.48
7N5	Solution	530.58	<0.05	1.71	10.41	<0.1	108	0.27	2.95	1819	7.03	<0.2	3.8	10.1	7.51	603.74	2.36
Minimum detection		0.01	0.05	0.02	0.02	0.1	2	0.01	0.02	1	0.01	0.2	0.1	0.1	0.01	0.01	0.01
Maximum detection		999	9999	9999	9999	9999	9999	100	999	9999	999	999	999	9999	999	9999	999
Method		ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Certificate#: 03E0709
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 19
 Date In: May 29, 2003
 Date Out: Jun 05, 2003

Sample Name	Sample Type	SiO2 %	S(tot) %	S(els) %	S(-2) %	S(SO4) %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm	
6Y3SB	Pulp	5.3	46.6	24.17	19.97	2.08	745	86	2000	11	<2	<0.2	22565	66	54	145777	195883	<2	
7N1SB	Pulp	N/A	N/A	N/A	N/A	N/A	509	76	2133	6	<2	<0.2	14292	26	61	209808	224767	<2	
7N3SB	Pulp	N/A	50.06	27.22	20.06	2.45	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	
7N4SB	Pulp	N/A	N/A	N/A	N/A	N/A	585	84	2250	4	<2	<0.2	20492	15	53	168088	184174	<2	
7N5SB	Pulp	3.78	53.19	27.97	23.88	0.91	376	70	1970	5	<2	<0.2	12364	10	64	164310	223709	<2	
8P1S	Pulp	N/A	N/A	N/A	N/A	N/A	868	67	1836	15	<2	<0.2	3909	6	57	243214	247189	<2	
8P2S	Pulp	N/A	N/A	N/A	N/A	N/A	812	62	1778	5	<2	<0.2	3936	9	60	268857	271417	<2	
8P3S	Pulp	N/A	N/A	N/A	N/A	N/A	946	68	1891	4	<2	<0.2	4198	8	58	258100	268109	<2	
8P4S	Pulp	N/A	N/A	N/A	N/A	N/A	1085	64	1872	7	<2	<0.2	4804	8	60	264188	273262	<2	
8P5S	Pulp	N/A	N/A	N/A	N/A	N/A	919	65	1747	6	<2	<0.2	16093	7	56	254948	254198	<2	
8Q1S	Pulp	N/A	N/A	N/A	N/A	N/A	887	58	1623	15	<2	<0.2	3686	61	52	158905	317182	<2	
8Q2S	Pulp	N/A	N/A	N/A	N/A	N/A	910	58	1723	22	<2	<0.2	3909	77	44	113257	325931	<2	
8Q3S	Pulp	N/A	N/A	N/A	N/A	N/A	681	60	1735	15	<2	<0.2	2772	92	49	139869	312737	<2	
8Q4S	Pulp	N/A	N/A	N/A	N/A	N/A	769	64	1835	13	<2	<0.2	3032	80	51	145436	309699	<2	
8Q5S	Pulp	N/A	N/A	N/A	N/A	N/A	724	62	1710	13	<2	<0.2	2854	81	46	139575	308410	<2	
8Q2Bulk	Pulp	N/A	N/A	N/A	N/A	N/A	726	60	1734	22	<2	<0.2	6294	72	46	114417	319615	<2	
8Q3Bulk	Pulp	N/A	32.46	14.52	16.65	1.05	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	
8Q4Bulk	Pulp	N/A	N/A	N/A	N/A	N/A	767	62	1823	13	<2	<0.2	13066	77	52	141027	296769	<2	
8Q5Bulk	Pulp	3.21	32.59	15.01	15.97	1.33	756	67	1774	13	<2	<0.2	16693	75	48	137821	287526	<2	
Minimum detection		0.01	0.01	0.01	0.01	0.01	100	5	5	2	2	0.2	100	1	1	1	100	2	
Maximum detection		100	100	100	100	100	50000	2000	10000	10000	2000	2000	100000	10000	10000	10000	50000	10000	
Method		AsyLen	AsyWet	AsyWet	AsyWet	AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	
Sample Name	Sample Type	Pb ppm	Mg ppm	Mn ppm	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Ti ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
6Y3SB	Pulp	3417	321	54	<3	3632	<1	<100	447	<1	.47	311	8	<10	124	<5	10	7952	5
7N1SB	Pulp	28	191	45	<3	3039	<1	<100	157	<1	60.4	114	11	<10	<100	14	10	11085	5
7N3SB	Pulp	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
7N4SB	Pulp	80	245	37	<3	3607	<1	<100	124	<1	50.3	125	17	<10	<100	13	8	5349	5
7N5SB	Pulp	14	177	32	<3	2616	<1	<100	<100	<1	50.2	116	8	<10	<100	17	8	6759	4
8P1S	Pulp	4111	373	84	<3	1985	<1	<100	380	<1	72.8	170	3	<10	<100	44	15	12621	6
8P2S	Pulp	2361	308	81	<3	1796	<1	<100	390	<1	86.3	227	3	<10	<100	36	16	10833	6
8P3S	Pulp	4154	419	91	<3	1322	<1	<100	400	<1	82.9	193	4	<10	<100	25	18	11542	6
8P4S	Pulp	4742	448	103	<3	1870	<1	<100	559	<1	85.6	265	4	<10	<100	28	18	12711	7
8P5S	Pulp	1783	343	84	<3	1471	<1	<100	356	<1	84.1	159	3	<10	<100	28	16	8595	6
8Q1S	Pulp	3062	343	78	<3	1641	<1	<100	658	<1	52	258	3	<10	<100	16	22	8337	8
8Q2S	Pulp	3320	338	69	<3	2438	<1	<100	778	<1	35.5	283	4	<10	<100	5	21	5489	8
8Q3S	Pulp	2823	282	57	<3	2341	<1	<100	580	<1	43.3	265	3	<10	<100	8	19	6453	7
8Q4S	Pulp	3205	313	62	<3	2933	<1	<100	667	<1	46.2	259	4	<10	<100	16	18	6546	7
8Q5S	Pulp	2523	280	57	<3	3177	<1	<100	612	<1	43.2	239	3	<10	<100	15	18	5967	7
8Q2Bulk	Pulp	3209	301	58	<3	2133	<1	<100	669	<1	35.6	260	4	<10	<100	10	21	5553	8
8Q3Bulk	Pulp	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
8Q4Bulk	Pulp	2827	290	58	<3	2977	<1	<100	598	<1	44.7	271	4	<10	<100	7	17	6118	7
8Q5Bulk	Pulp	1762	244	63	<3	3453	<1	<100	518	<1	43.2	288	4	<10	<100	13	17	5755	7
Minimum detection		2	100	1	3	1	1	100	100	1	0.1	100	1	10	100	5	1	1	1
Maximum detection		10000	10000	10000	10000	1000	10000	50000	100000	10000	100	100000	10000	10000	100000	1000	10000	10000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate#: 03E0708
Client: Metals & Materials Eng UBC
Project: BD28F06 EFDJ 713000
No. of Samples: 20
Date In: May 29, 2003
Date Out: Jun 03, 2003

Sample Name	Sample Type	Cl- mg/L	F.A. HCl G/L	F.A. H2SO4 G/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L
6L	Solution	256	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
6X3	Solution	2004.7	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
7M1	Solution	N/A	N/A	N/A	98.9	0.3	35	0.22	<0.1	4.05	23929.6	15.38	7.12	65019.62	95106.1	<0.05	418.21
7M4	Solution	N/A	N/A	N/A	110.5	<0.1	40.8	0.16	<0.1	5.83	23262	20.87	8.5	76894.03	107577.55	<0.05	527.84
7WW	Solution	N/A	N/A	N/A	19.2	<0.1	1	2.27	2.2	<0.01	27281.2	1.53	0.42	3451.28	4796.19	<0.05	15.42
8L	Solution	N/A	N/A	N/A	2.1	0.1	<0.2	<0.01	<0.1	<0.01	33	0.04	0.02	55.19	37.06	<0.05	<0.05
8UL	Solution	159673.9	0.72	N/A	16.1	<0.1	1.1	0.43	<0.1	<0.01	25344.4	5.86	1.87	52927.93	32880.44	<0.05	2.48
8P1	Solution	N/A	N/A	N/A	71.6	<0.1	4.9	<0.01	<0.1	0.93	24095.2	5.92	4.68	62861.46	41614.22	<0.05	84.06
8P2	Solution	N/A	N/A	N/A	93.4	<0.1	1.5	<0.01	<0.1	4.88	21970.8	7.65	8.02	71252.57	34344.07	<0.05	145.33
8P3	Solution	N/A	N/A	N/A	75.1	<0.1	2.6	<0.01	<0.1	2.32	23395.5	10.65	5.94	69047.35	35453.25	<0.05	79.58
8P4	Solution	N/A	N/A	N/A	69	<0.1	1.2	<0.01	<0.1	2.39	23300.2	10.71	6.1	88539.37	35021.64	<0.05	64.3
8P5	Solution	121132.1	N/A	N/A	53.1	<0.1	1.7	<0.01	<0.1	0.87	15933.6	9.31	4.44	48484.33	23156.87	<0.05	52.36
8O1	Solution	N/A	N/A	N/A	50.4	<0.1	1	<0.01	<0.1	1.05	24002.7	0.85	5.17	71217.17	31616.86	<0.05	48.35
8O2	Solution	N/A	N/A	N/A	25.4	<0.1	0.5	<0.01	<0.1	<0.01	23425.7	2.07	2.8	60230.18	27776.81	<0.05	18.87
8Q3	Solution	N/A	N/A	N/A	34.6	<0.1	0.9	<0.01	<0.1	<0.01	25146.5	2.15	3.84	68699.47	31754.39	<0.05	27.97
8Q4	Solution	N/A	N/A	N/A	29	<0.1	1.2	<0.01	<0.1	<0.01	25258.9	1.12	3.56	68771.33	31445.4	<0.05	18.42
8Q5	Solution	N/A	N/A	N/A	28.1	<0.1	0.9	<0.01	<0.1	<0.01	24058.7	1.03	3.44	67316.3	29552.02	<0.05	19.53
8PD5	Solution	N/A	N/A	N/A	2.1	<0.1	<0.2	<0.01	<0.1	<0.01	20.4	0.02	0.04	55.5	27.57	<0.05	<0.05
8OD3	Solution	N/A	N/A	N/A	2.5	0.1	<0.2	<0.01	<0.1	<0.01	27.2	<0.01	<0.01	69.51	32.92	<0.05	<0.05
8WW	Solution	N/A	N/A	N/A	27.2	<0.1	2.4	<0.01	<0.1	<0.01	4160.2	11.18	0.67	6053.12	4272.59	0.1	91.33
Minimum detection		0.5	0.01	0.01	0.2	0.1	0.2	0.01	0.1	0.01	0.1	0.01	0.01	0.01	0.03	0.05	0.05
Maximum detection		1000	1000	1000	9999	9999	9999	9999	9999	999	9999	9999	9999	9999	9999	999	9999
Method		CHSE	Env	Env	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Sample Name	Sample Type	Mg mg/L	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L
6L	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
6X3	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
7M1	Solution	29.4	534.44	<0.05	2.86	10.03	<0.1	113	0.27	12.65	1753	5.48	<0.2	4	9.4	8.52	1969.11	2.61
7M4	Solution	31.9	556.84	<0.05	3.56	10.69	<0.1	105	0.31	17.01	1767	105	<0.2	3	9.2	9.46	2647.46	2.94
7WW	Solution	3	25.57	<0.05	0.39	0.78	<0.1	17	0.02	0.86	2637	16.26	<0.2	<0.1	0.6	0.21	100.61	0.08
8L	Solution	0.4	0.18	<0.05	<0.02	<0.02	<0.1	9	<0.01	0.04	16	0.02	<0.2	<0.1	<0.1	<0.01	0.19	0.03
8UL	Solution	1.7	148.97	<0.05	1.06	6.26	<0.1	83	0.35	<0.02	1741	6.88	<0.2	1.6	13	2.03	<0.01	0.7
8P1	Solution	17.8	197.82	<0.05	0.16	6.89	<0.1	85	0.4	11.63	1745	6.98	<0.2	1.7	9.6	2.88	1818.78	0.92
8P2	Solution	19.8	250.47	<0.05	<0.02	15.45	<0.1	30	0.5	16.92	1742	6.97	<0.2	1.7	11.4	2.09	3894.96	0.68
8P3	Solution	15.4	211.16	<0.05	0.12	12.99	<0.1	43	0.48	12.33	1787	6.92	<0.2	1.6	11.1	2.41	2487.35	0.71
8P4	Solution	13.8	212.01	<0.05	0.16	13.94	<0.1	42	0.47	9.12	1725	6.91	<0.2	1.5	10.1	2.31	2531.84	0.7
8P5	Solution	9.7	140.95	<0.05	0.42	11.29	<0.1	63	0.35	10.73	1206	4.86	<0.2	1.4	8.7	1.36	1716.73	0.45
8Q1	Solution	9.4	198.43	<0.05	<0.02	7.66	<0.1	40	0.49	12.91	1749	6.89	<0.2	1.6	10.9	1.89	1887.28	0.62
8Q2	Solution	4	147.2	<0.05	0.45	6.32	<0.1	48	0.42	3.42	1639	6.5	<0.2	1.3	12.7	1.52	454.97	0.54
8Q3	Solution	6.7	168.63	<0.05	0.3	7.66	<0.1	59	0.48	6.23	1732	7.04	<0.2	1.5	13	1.95	849.44	0.64
8Q4	Solution	4.7	162.97	<0.05	0.17	6.96	<0.1	70	0.48	5.12	1662	6.97	<0.2	1.5	12.4	1.96	702.26	0.61
8Q5	Solution	4.1	155	<0.05	0.27	8	<0.1	132	0.47	5.1	1679	6.74	<0.2	1.5	13.6	1.79	640.23	0.56
8PD5	Solution	0.4	0.18	<0.05	<0.02	<0.02	<0.1	11	<0.01	<0.02	14	0.02	<0.2	<0.1	0.1	<0.01	1.86	0.02
8OD3	Solution	0.4	0.19	<0.05	<0.02	0.04	<0.1	8	<0.01	<0.02	15	0.02	<0.2	<0.1	0.2	<0.01	0.96	0.03
8WW	Solution	9.9	16.66	<0.05	1.34	7.17	<0.1	23	0.05	0.76	157	0.95	<0.2	0.7	1.4	0.3	118.52	0.1
Minimum detection		0.1	0.01	0.05	0.02	0.02	0.1	2	0.01	0.02	1	0.01	0.2	0.1	0.1	0.01	0.01	0.01
Maximum detection		9999	1000	9999	9999	9999	9999	9999	100	999	9999	999	999	999	9999	999	9999	999
Method		ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Certificate#: 03F0896
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 12
 Date In: Jun 19, 2003
 Date Out: Jun 25, 2003

Sample Name	SampleType	S(tot) %	S(ele) %	S(-2) %	S(SO4) %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm	Pb ppm
9K1S	Pulp	N/A	N/A	N/A	N/A	566	76	2099	2	<2	<0.2	1695	14	72	161590	197236	<2	23
9K2S	Pulp	N/A	N/A	N/A	N/A	626	71	1780	2	<2	<0.2	2204	2	66	231669	245509	<2	16
9K3S	Pulp	N/A	N/A	N/A	N/A	873	102	2517	<2	<2	<0.2	3295	8	68	182807	191090	<2	18
9K4S	Pulp	N/A	N/A	N/A	N/A	542	84	2076	5	<2	<0.2	1214	2	71	187611	204376	<2	16
9K5S	Pulp	N/A	N/A	N/A	N/A	531	89	2207	4	<2	<0.2	1474	3	69	178514	195711	<2	15
9L1S	Pulp	N/A	N/A	N/A	N/A	709	87	2278	5	<2	<0.2	2030	23	68	170009	196137	<2	18
9L2S	Pulp	N/A	N/A	N/A	N/A	800	104	2409	<2	<2	<0.2	1941	47	68	134124	158052	<2	19
9L3S	Pulp	N/A	N/A	N/A	N/A	539	104	2282	<2	<2	<0.2	928	19	71	115202	145682	<2	18
9L4S	Pulp	N/A	N/A	N/A	N/A	547	137	3084	<2	<2	<0.2	790	16	57	76220	110957	<2	15
9L5S	Pulp	N/A	N/A	N/A	N/A	506	123	2821	<2	<2	<0.2	914	14	59	81443	116460	<2	9
9L3Bulk	Pulp	N/A	N/A	N/A	N/A	650	104	2389	<2	<2	<0.2	1616	25	66	115278	153970	<2	15
9L5Bulk	Pulp	64.03	48.1	14.88	0.01	737	137	3073	<2	<2	<0.2	1398	23	73	81252	132331	<2	18
Minimum detection		0.01	0.01	0.01	0.01	100	5	5	2	2	0.2	100	1	1	1	100	2	2
Maximum detection		100	100	100	100	50000	2000	10000	10000	2000	2000	100000	10000	10000	10000	50000	10000	10000
Method		AsyWet	AsyWet	AsyWet	AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Sample Name	SampleType	Mg ppm	Mn ppm	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Ti ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
9K1S	Pulp	205	42	<3	4964	2	<100	<100	<1	49.9	140	<1	<10	<100	<5	6	9028	4
9K2S	Pulp	240	43	<3	3014	<1	<100	191	<1	68.7	145	1	<10	<100	<5	11	7885	5
9K3S	Pulp	309	57	<3	5081	5	<100	135	<1	54	115	2	<10	126	<5	9	8845	5
9K4S	Pulp	211	39	<3	3416	<1	<100	146	<1	61.6	133	<1	<10	<100	<5	9	8038	5
9K5S	Pulp	184	45	<3	2089	<1	<100	142	<1	58.3	284	<1	<10	<100	<5	9	9185	4
9L1S	Pulp	216	56	<3	2938	<1	<100	134	<1	55.2	107	<1	<10	166	<5	9	9404	5
9L2S	Pulp	248	46	<3	5001	2	<100	174	<1	40.5	132	<1	<10	144	<5	6	5897	5
9L3S	Pulp	201	29	<3	5022	5	<100	182	<1	26.8	130	<1	<10	<100	<5	4	5140	4
9L4S	Pulp	233	28	<3	5292	3	<100	136	<1	34.2	139	<1	<10	<100	<5	1	5030	3
9L5S	Pulp	182	27	<3	4509	4	<100	152	<1	34.1	102	<1	<10	<100	<5	2	4754	3
9L3Bulk	Pulp	232	31	<3	5276	<1	<100	101	<1	40.5	136	<1	<10	102	<5	4	4888	4
9L5Bulk	Pulp	258	35	<3	5473	7	<100	103	<1	34.9	175	<1	<10	107	<5	3	4574	4
Minimum detection		100	1	3	1	1	100	100	1	0.1	100	1	10	100	5	1	1	1
Maximum detection		100000	10000	10000	1000	10000	50000	100000	10000	100	100000	10000	10000	100000	1000	10000	10000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate# 03F0897
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 18
 Date In: Jun 19, 2003
 Date Out: Jun 23, 2003

Sample Name	Sample Type	Cl- mg/L	F.A. H2SO4 G/L	F.A. HCl G/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L	Zr mg/L
9Jdb	Solution	N/A	N/A	N/A	2.8	<0.1	<0.2	0.02	<0.1	<0.01	273.6	0.27	0.06	472.23	794.44	<0.05	<0.05	
9Jd	Solution	N/A	N/A	N/A	2.8	<0.1	<0.2	<0.01	0.2	<0.01	273.9	0.25	0.02	471.5	798.6	<0.05	<0.05	
9J	Solution	N/A	N/A	5.28	23.2	<0.1	<0.2	0.39	<0.1	<0.01	27154.3	15.92	3.78	47365.35	79121.57	<0.05	4.7	
9K1	Solution	N/A	N/A	N/A	3.8	<0.1	<0.2	<0.01	<0.1	<0.01	275.2	0.28	0.1	740.51	1085.9	<0.05	3.4	
9K2	Solution	N/A	N/A	N/A	4.8	<0.1	<0.2	<0.01	1.6	<0.01	231.3	0.43	0.19	861.62	1201.52	<0.05	8.61	
9K3	Solution	N/A	N/A	N/A	3.8	<0.1	<0.2	<0.01	0.8	<0.01	247.2	0.35	0.13	786.69	1111.35	<0.05	4.61	
9K4	Solution	N/A	N/A	N/A	4	<0.1	<0.2	<0.01	1	<0.01	248.3	0.4	0.14	817.63	1147.46	<0.05	4.4	
9K5	Solution	N/A	N/A	N/A	4.5	0.1	<0.2	0.01	0.4	<0.01	252.9	0.39	0.12	817.4	1142.75	<0.05	4.1	
9K5ud	Solution	N/A	0.48	N/A	177.9	0.2	11.7	0.12	<0.1	<0.01	24388.2	23.03	8.39	79753.15	109081.93	<0.05	421.84	
9L1	Solution	N/A	N/A	N/A	4	<0.1	<0.2	0.01	0.1	<0.01	285.6	0.3	0.13	756.44	1104.02	<0.05	4.18	
9L2	Solution	N/A	N/A	N/A	3.2	<0.1	<0.2	0.02	0.1	<0.01	288	0.25	0.08	542.52	892.66	<0.05	0.46	
9L3	Solution	N/A	N/A	N/A	3.3	<0.1	<0.2	<0.01	<0.1	<0.01	273.7	0.28	0.1	663.23	1008.43	<0.05	0.96	
9L4	Solution	N/A	N/A	N/A	3.5	<0.1	<0.2	0.02	<0.1	<0.01	278	0.26	0.06	584.7	920.82	<0.05	0.24	
9L5	Solution	N/A	N/A	N/A	2.9	<0.1	<0.2	<0.01	<0.1	<0.01	275.8	0.25	0.05	601.11	930.87	<0.05	0.18	
9L5ud	Solution	N/A	N/A	N/A	50.5	<0.1	<0.2	0.36	<0.1	<0.01	26652	17.22	5.53	59866.48	90567.66	<0.05	46.6	
9WW	Solution	N/A	N/A	N/A	17.4	<0.1	<0.2	0.09	1.9	<0.01	6076.6	18	0.78	4165.17	6344.88	<0.05	13.28	
9A	Solution	2621	N/A	N/A	<0.2	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
9B	Solution	2632	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection		0.5	0.01	0.01	0.2	0.1	0.2	0.01	0.1	0.01	0.1	0.01	0.01	0.01	0.03	0.05	0.05	0.01
Maximum detection		1000	1000	1000	9999	9999	9999	999	9999	999	9999	9999	9999	9999	9999	999	9999	999
Method		CHSE	Env	Env	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Sample Name	Sample Type	Mg mg/L	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L
9Jdb	Solution	0.3	5.29	<0.05	0.02	0.14	<0.1	6	0.02	0.02	25	0.08	0.2	<0.1	0.3	0.05	0.59	0.06
9Jd	Solution	0.2	5.29	<0.05	0.05	0.26	<0.1	<2	<0.01	0.02	26	0.08	<0.2	<0.1	0.2	<0.01	0.59	0.03
9J	Solution	6	501.61	<0.05	1.61	10.09	<0.1	87	0.16	<0.02	1693	6.95	<0.2	2.6	<0.1	6.22	58.9	2.16
9K1	Solution	0.2	6.27	<0.05	0.02	0.11	<0.1	<2	0.02	0.12	27	0.08	<0.2	<0.1	0.1	0.05	22.2	0.05
9K2	Solution	1.2	6.58	<0.05	0.14	0.22	<0.1	8	0.02	0.37	26	0.08	<0.2	<0.1	<0.1	0.05	45.4	0.05
9K3	Solution	0.8	5.97	<0.05	0.15	0.32	<0.1	4	<0.01	0.23	29	0.05	<0.2	0.1	0.1	0.03	27.68	0.04
9K4	Solution	0.7	6.12	<0.05	0.12	0.35	<0.1	3	0.02	0.22	28	0.05	<0.2	<0.1	<0.1	<0.01	30.06	0.02
9K5	Solution	0.6	6.03	<0.05	0.13	0.14	<0.1	<2	0.02	0.27	28	0.04	<0.2	<0.1	0.2	0.03	27.52	0.03
9K5ud	Solution	36.5	550.37	<0.05	3.84	13.66	<0.1	115	0.3	15.93	1666	5.12	<0.2	5.8	<0.1	9.16	2696.14	2.94
9L1	Solution	0.4	6.55	<0.05	0.07	0.16	<0.1	<2	<0.01	0.21	32	0.08	<0.2	<0.1	<0.1	0.03	24.38	0.04
9L2	Solution	0.3	5.68	<0.05	0.07	0.13	<0.1	5	<0.01	<0.02	29	0.09	<0.2	<0.1	0.1	<0.01	6.38	<0.01
9L3	Solution	0.2	5.71	<0.05	0.07	0.23	<0.1	6	<0.01	0.06	28	0.08	<0.2	<0.1	0.2	0.03	10.52	0.02
9L4	Solution	<0.1	5.6	<0.05	<0.02	0.14	<0.1	4	<0.01	0.05	29	0.08	<0.2	<0.1	<0.1	<0.01	7.82	0.01
9L5	Solution	<0.1	5.55	<0.05	<0.02	0.14	<0.1	<2	<0.01	<0.02	27	0.08	<0.2	<0.1	0.1	0.03	7.46	0.02
9L5ud	Solution	15.2	517.91	<0.05	2.13	8.63	<0.1	92	0.23	4.35	1710	6.56	<0.2	4.9	<0.1	7.87	698.62	2.5
9WW	Solution	1.7	34.49	<0.05	1.68	11.02	<0.1	10	0.02	0.84	116	3.62	<0.2	0.7	<0.1	0.32	102.54	0.12
9A	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
9B	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection		0.1	0.01	0.05	0.02	0.02	0.1	2	0.01	0.02	1	0.01	0.2	0.1	0.1	0.01	0.01	0.01
Maximum detection		9999	999	9999	9999	9999	9999	9999	100	999	9999	999	999	999	9999	999	9999	999
Method		ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Certificate#: 03G1007
 Client: Metals & Materials Eng.UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 12
 Date In: Jul 04, 2003
 Date Out: Jul 10, 2003

Sample Name	Sample Type	S(tol) %	S(ele) %	S(-2) %	S(SCd4) %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm	Pb ppm
10J1S	Pulp	N/A	N/A	N/A	N/A	531	58	1523	15	<2	<0.2	1274	3	76	243103	230141	9	11
10J2S	Pulp	N/A	N/A	N/A	N/A	923	46	1721	18	<2	<0.2	2840	1	79	303028	277825	3	14
10J3S	Pulp	N/A	N/A	N/A	N/A	705	37	1542	19	<2	<0.2	2628	<1	89	258874	261166	21	12
10J4S	Pulp	N/A	N/A	N/A	N/A	799	39	1317	18	<2	<0.2	2752	3	86	269007	252962	12	15
10J5S	Pulp	N/A	N/A	N/A	N/A	811	57	1648	20	<2	<0.2	2763	2	79	290999	268533	12	18
10K1S	Pulp	N/A	N/A	N/A	N/A	1247	70	1962	20	<2	<0.2	5018	65	71	162509	265963	13	495
10K2S	Pulp	N/A	N/A	N/A	N/A	909	92	2368	11	<2	<0.2	1930	51	71	129500	208290	15	17
10K3S	Pulp	N/A	N/A	N/A	N/A	1391	120	2498	9	<2	<0.2	3526	78	67	114118	211078	13	<2
10K3 bulk	Pulp	N/A	N/A	N/A	N/A	1277	97	2516	11	<2	<0.2	3071	104	57	90975	219191	13	25
10K4S	Pulp	N/A	N/A	N/A	N/A	851	90	2540	11	<2	<0.2	2291	53	81	158177	231043	14	29
10K5S	Pulp	N/A	N/A	N/A	N/A	1013	85	2350	10	<2	<0.2	2525	52	77	164963	228091	16	19
10K5S bulk	Pulp	46.28	24.26	21.56	0.24	928	106	2492	10	<2	<0.2	3987	50	81	165963	235306	8	12
Minimum detection		0.01	0.01	0.01	0.01	100	5	5	2	2	0.2	100	1	1	1	100	2	2
Maximum detection		100	100	100	100	50000	2000	10000	10000	2000	2000	100000	10000	10000	10000	50000	10000	10000
Method		AsyWet	AsyWet	AsyWet	AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Sample Name	Sample Type	Mg ppm	Mn ppm	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Ti ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
10J1S	Pulp	246	41	<3	1630	3	<100	1606	<1	73.5	961	<1	<10	<100	<5	8	6751	5
10J2S	Pulp	346	75	<3	2636	24	<100	1364	<1	96.5	991	<1	<10	<100	<5	5	8344	5
10J3S	Pulp	360	64	<3	1266	13	<100	3626	<1	82.5	898	<1	<10	<100	<5	7	7216	3
10J4S	Pulp	345	69	<3	1912	5	<100	2140	<1	86.8	895	<1	<10	<100	<5	7	7658	4
10J5S	Pulp	314	69	<3	1060	2	<100	2211	2	95.3	997	3	<10	<100	<5	11	7604	6
10K1S	Pulp	480	100	<3	1974	<1	<100	2624	<1	57	993	2	<10	<100	<5	10	7719	5
10K2S	Pulp	352	47	<3	3213	<1	<100	2334	<1	44.6	973	3	<10	<100	<5	5	5583	3
10K3S	Pulp	495	63	<3	4076	<1	<100	2258	<1	43.7	933	<1	<10	<100	<5	6	4106	7
10K3 bulk	Pulp	513	54	<3	3463	<1	<100	2117	<1	34.2	1085	<1	<10	<100	<5	7	3385	3
10K4S	Pulp	383	53	<3	4254	21	<100	2985	<1	56.6	1007	<1	<10	<100	<5	<1	5796	3
10K5S	Pulp	348	56	<3	4915	<1	<100	2541	<1	55.5	988	<1	<10	<100	<5	4	5464	4
10K5S bulk	Pulp	319	54	<3	4780	19	<100	2261	<1	57.1	1063	<1	<10	<100	<5	<1	5468	5
Minimum detection		100	1	3	1	1	100	100	1	0.1	100	1	10	100	5	1	1	1
Maximum detection		100000	10000	10000	1000	10000	50000	100000	10000	100	100000	100000	1000	10000	10000	10000	10000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate#: 03G1008
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 16
 Date In: Jul 07, 2003
 Date Out: Jul 10, 2003

Sample Name	SampleType	Cl- mg/L	F.A. H2SO4 G/L	F.A. HCl G/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L
10Fd	Solution	N/A	N/A	N/A	2.3	0.1	<0.2	0.02	0.3	<0.01	542.8	0.1	0.06	558.84	345.06	0.06	0.36
10F	Solution	N/A	N/A	10.02	15.3	<0.1	0.8	0.89	0.7	<0.01	56260.6	5.08	1.79	55255.63	33977.67	<0.05	2.61
10U1	Solution	N/A	N/A	N/A	3.9	<0.1	0.3	<0.01	0.2	<0.01	569.7	0.12	0.09	773.97	550.95	<0.05	5.28
10U2	Solution	N/A	N/A	N/A	4.1	<0.1	0.2	<0.01	0.4	0.09	516.8	0.08	0.2	896.91	564.7	<0.05	10.95
10U3	Solution	N/A	N/A	N/A	3.6	<0.1	<0.2	0.02	0.8	0.03	535.5	0.1	0.13	847.9	566.46	<0.05	6.05
10U4	Solution	N/A	N/A	N/A	3.6	<0.1	<0.2	0.02	0.6	0.03	521.8	0.11	0.11	857.29	555.58	<0.05	5.97
10U5	Solution	N/A	N/A	N/A	3.9	<0.1	<0.2	<0.01	0.4	0.05	545.3	0.11	0.11	879.45	597.29	<0.05	6.06
10U5ud	Solution	N/A	7.56	N/A	106	<0.1	10.5	0.41	0.4	4.57	55092.2	11.89	5.64	87900.77	57165.71	<0.05	503.54
10K1	Solution	N/A	N/A	N/A	3.3	<0.1	<0.2	0.02	0.9	0.04	590	0.05	0.11	869.96	512.46	0.06	5.9
10K2	Solution	N/A	N/A	N/A	2.7	<0.1	<0.2	0.02	<0.1	<0.01	579.1	0.07	0.06	717.05	448.88	<0.05	0.9
10K3	Solution	N/A	N/A	N/A	3.1	<0.1	<0.2	<0.01	0.2	<0.01	570.7	0.05	0.06	781.36	484.18	<0.05	1.38
10K4	Solution	N/A	N/A	N/A	2.4	<0.1	<0.2	<0.01	<0.1	<0.01	589.7	0.08	0.08	756.71	484.29	<0.05	0.66
10K5	Solution	N/A	N/A	N/A	2.9	<0.1	<0.2	0.02	0.4	<0.01	566.9	0.05	0.05	767.35	484.76	<0.05	0.73
10WW	Solution	N/A	N/A	N/A	17.6	<0.1	2.6	0.1	3.5	0.08	8641.4	15.31	0.67	5912.07	4512.58	0.09	21
10A	Solution	2006.7	N/A	N/A	1.8	<0.1	<0.2	0.03	<0.1	<0.01	577.3	0.15	0.04	589.59	343.83	0.05	0.28
10B	Solution	11981.6	N/A	N/A	4	<0.1	<0.2	0.02	<0.1	0.05	552.1	0.25	0.16	896.32	598.1	<0.05	5.85
Minimum detection		0.5	0.01	0.01	0.2	0.1	0.2	0.01	0.1	0.01	0.1	0.01	0.01	0.01	0.03	0.05	0.05
Maximum detection		1000	1000	1000	9999	9999	9999	999	9999	999	9999	9999	9999	9999	9999	999	9999
Method		CH-SE	Env	Env	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO

Sample Name	SampleType	Mg mg/L	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L
10Fd	Solution	0.5	1.58	<0.05	0.06	0.23	<0.1	7	<0.01	0.03	35	0.17	<0.2	<0.1	<0.1	0.04	1.02	0.02
10F	Solution	2.3	141.8	<0.05	0.78	7.75	<0.1	148	0.27	<0.02	3130	12.31	<0.2	0.4	<0.1	2.14	96.7	0.63
10U1	Solution	0.8	2.35	<0.05	<0.02	0.15	<0.1	5	<0.01	0.23	38	0.18	0.3	<0.1	<0.1	0.04	23.28	0.01
10U2	Solution	1.2	3.06	0.18	<0.02	0.35	<0.1	8	0.02	0.42	38	0.12	0.4	<0.1	<0.1	0.03	50.92	0.01
10U3	Solution	0.8	2.39	<0.05	<0.02	0.22	<0.1	8	<0.01	0.25	37	0.15	<0.2	<0.1	<0.1	0.03	30.44	0.02
10U4	Solution	0.7	2.46	<0.05	0.02	0.34	<0.1	7	0.02	0.26	36	0.16	<0.2	<0.1	<0.1	0.03	32.75	0.02
10U5	Solution	0.6	2.48	<0.05	<0.02	0.3	<0.1	7	<0.01	0.27	41	0.15	<0.2	<0.1	<0.1	0.03	32.83	<0.01
10U5ud	Solution	24.9	207.38	<0.05	1.71	9.97	<0.1	171	0.3	14.83	3483	9.3	0.5	0.7	<0.1	3.55	3306.29	0.98
10K1	Solution	0.5	2.47	<0.05	<0.02	0.28	<0.1	9	<0.01	0.27	40	0.17	<0.2	<0.1	<0.1	0.03	27.77	0.02
10K2	Solution	0.3	1.85	<0.05	<0.02	0.23	<0.1	7	0.02	0.06	38	0.17	0.4	<0.1	<0.1	0.05	7.83	0.01
10K3	Solution	0.5	1.91	<0.05	<0.02	0.18	<0.1	6	0.02	0.1	41	0.17	0.2	<0.1	<0.1	<0.01	11.28	<0.01
10K4	Solution	0.3	1.81	0.05	<0.02	0.34	<0.1	6	0.02	0.1	38	0.17	<0.2	<0.1	<0.1	0.02	8.63	0.02
10K5	Solution	0.3	1.8	<0.05	<0.02	0.16	<0.1	6	<0.01	0.08	286	4.83	<0.2	<0.1	<0.1	0.02	8.29	0.02
10WW	Solution	2.5	15.55	<0.05	0.72	5.09	<0.1	23	0.05	0.9	286	4.83	2.3	0.6	<0.1	0.26	144.87	0.09
10A	Solution	0.5	1.65	<0.05	<0.02	0.21	<0.1	11	<0.01	0.04	33	0.16	0.6	<0.1	<0.1	0.06	1.14	0.05
10B	Solution	0.7	2.52	<0.05	<0.02	0.32	<0.1	5	<0.01	0.25	41	0.13	<0.2	<0.1	<0.1	<0.01	33.22	<0.01
Minimum detection		0.1	0.01	0.05	0.02	0.02	0.1	2	0.01	0.02	1	0.01	0.2	0.1	0.1	0.01	0.01	0.01
Maximum detection		9999	999	9999	9999	9999	9999	9999	100	999	9999	999	999	999	9999	999	9999	999
Method		ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO	ICPHZO

Certificate# 03G1045
 Client: Metals & Materials Eng. UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 14
 Date In: Jul 10, 2003
 Date Out: Jul 15, 2003

Sample Name	SampleType	S(tot) %	S(ele) %	S(-2) %	S(SO4) %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm	Pb ppm
11C1S	Pulp	N/A	N/A	N/A	N/A	919	91	2186	<2	<2	<0.2	2474	22	65	194422	223010	<2	33
11C2S	Pulp	N/A	N/A	N/A	N/A	1124	96	1974	6	<2	<0.2	2931	4	70	252988	258604	<2	20
11C3S	Pulp	N/A	N/A	N/A	N/A	1254	110	2254	<2	<2	0.8	2813	4	67	199321	223436	<2	44
11C4S	Pulp	N/A	N/A	N/A	N/A	1035	93	2195	3	<2	<0.2	2580	3	66	224148	240609	<2	46
11C5S	Pulp	N/A	N/A	N/A	N/A	1311	98	2299	<2	<2	<0.2	4002	8	65	190289	212156	<2	67
11C6S	Pulp	N/A	N/A	N/A	N/A	799	95	2205	<2	<2	0.3	2013	3	68	207296	220228	<2	20
11D1S	Pulp	N/A	N/A	N/A	N/A	609	89	2120	3	<2	0.8	1657	14	64	206111	226781	<2	29
11D2S	Pulp	N/A	N/A	N/A	N/A	768	100	2376	<2	<2	<0.2	2033	27	61	176623	203639	<2	34
11D3S	Pulp	N/A	N/A	N/A	N/A	929	113	2253	<2	<2	<0.2	2417	26	65	143456	179566	<2	19
11D3bulk	Pulp	N/A	N/A	N/A	N/A	1165	1913	2947	<2	<2	<0.2	1879	43	70	142297	180047	<2	22
11D4S	Pulp	N/A	N/A	N/A	N/A	1058	124	2489	<2	<2	<0.2	1253	23	73	152210	193137	<2	31
11D5S	Pulp	N/A	N/A	N/A	N/A	1002	136	2982	<2	<2	<0.2	2669	26	66	127623	170012	<2	39
11D6S	Pulp	N/A	N/A	N/A	N/A	1154	136	2900	<2	<2	<0.2	3000	32	68	114020	162451	<2	54
11D6bulk	Pulp	62.22	42.89	18.85	0.09	1059	120	2666	<2	<2	<0.2	2587	32	65	112436	162280	<2	53
Minimum detection		0.01	0.01	0.01	0.01	100	5	5	2	2	0.2	100	1	1	1	100	2	2
Maximum detection		100	100	100	100	50000	2000	10000	10000	2000	2000	100000	10000	10000	10000	50000	10000	10000
Method		AsyWet	AsyWet	AsyWet	AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Sample Name	SampleType	Mg ppm	Mn ppm	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Ti ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
11C1S	Pulp	302	64	<3	6607	<1	<100	200	<1	53.1	<100	<1	<10	112	<5	14	8977	5
11C2S	Pulp	362	79	<3	4685	5	<100	218	<1	63.8	153	<1	<10	142	<5	19	8850	6
11C3S	Pulp	388	84	<3	6910	<1	<100	239	<1	58.3	106	<1	<10	164	<5	16	9590	5
11C4S	Pulp	314	64	<3	6926	<1	<100	142	<1	61.5	<100	<1	<10	144	<5	16	8758	5
11C5S	Pulp	401	78	<3	6853	<1	<100	210	<1	56.5	128	2	<10	187	448	17	8793	5
11C6S	Pulp	263	60	<3	6517	<1	<100	176	<1	47	115	<1	<10	<100	<5	15	9159	5
11D1S	Pulp	199	53	<3	5370	<1	<100	117	<1	57.9	107	<1	<10	<100	<5	13	9605	4
11D2S	Pulp	223	47	<3	6281	<1	<100	149	<1	51.8	114	<1	<10	<100	<5	12	4843	4
11D3S	Pulp	284	57	<3	5946	<1	<100	140	<1	43.8	115	<1	<10	136	<5	12	5721	5
11D3bulk	Pulp	354	64	<3	6784	18	<100	407	<1	45	135	<1	<10	160	<5	13	5641	6
11D4S	Pulp	309	65	<3	6740	4	<100	169	<1	45.8	115	<1	<10	153	<5	15	5059	5
11D5S	Pulp	294	57	<3	7700	<1	<100	250	<1	41.4	110	<1	<10	147	<5	11	5233	4
11D6S	Pulp	335	64	<3	7539	6	<100	237	<1	38.9	116	<1	<10	173	<5	12	5242	5
11D6bulk	Pulp	338	60	<3	8092	<1	<100	210	<1	35.6	107	<1	<10	146	<5	11	5099	4
Minimum detection		100	1	3	1	1	100	100	1	0.1	100	1	10	100	5	1	1	1
Maximum detection		100000	10000	10000	1000	10000	50000	100000	10000	100	100000	10000	10000	100000	1000	10000	10000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate# 03G1047
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 19
 Date In: Jul 10, 2003
 Date Out: Jul 14, 2003

Sample Name	Sample Type	Cl- mg/L	F.A. H2SO4 G/L	F.A. HCl G/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L	Zr mg/L
11F	Solution	N/A	N/A	N/A	2.9	<0.1	<0.2	0.04	<0.1	<0.01	275.2	0.28	0.09	529.03	871.58	<0.05	<0.05	0.03
11Fud	Solution	N/A	N/A	12.97	17.6	<0.1	<0.2	0.15	<0.1	1.09	28429.2	15.16	3.77	53313.94	89537.22	<0.05	6.14	1.99
11C1	Solution	N/A	N/A	N/A	2.6	0.1	<0.2	0.02	<0.1	<0.01	265.1	0.28	0.15	740.26	1107.04	<0.05	4.31	0.03
11C2	Solution	N/A	N/A	N/A	4.8	<0.1	<0.2	<0.01	1.3	<0.01	217.3	0.44	0.2	907.06	1302.23	<0.05	9.32	0.02
11C3	Solution	N/A	N/A	N/A	4.1	<0.1	<0.2	0.01	0.6	<0.01	233.6	0.42	0.15	788.82	1180.46	<0.05	5.02	0.02
11C4	Solution	N/A	N/A	N/A	4	<0.1	<0.2	0.01	1.4	<0.01	233.7	0.37	0.17	853.44	1233.91	<0.05	5.44	0.02
11C5	Solution	N/A	N/A	N/A	4	<0.1	<0.2	0.03	0.5	<0.01	242.8	0.42	0.15	545.39	1238.32	<0.05	4.89	0.02
11C6ud	Solution	N/A	<0.01	N/A	105	<0.1	<0.2	0.03	1.1	<0.01	241	0.43	0.17	862.79	1250.87	<0.05	4.94	0.04
11D1	Solution	N/A	N/A	N/A	2.8	<0.1	<0.2	0.01	1	<0.01	25211.1	22.45	8.4	87073.78	122593.9	<0.05	450.34	0.04
11D2	Solution	N/A	N/A	N/A	3.1	<0.1	<0.2	0.02	0.3	<0.01	268.2	0.27	0.18	761.64	1121.44	<0.05	4.52	0.02
11D3	Solution	N/A	N/A	N/A	3.3	<0.1	<0.2	0.02	0.5	<0.01	264.5	0.29	0.1	665.6	1054.94	<0.05	0.63	0.02
11D4	Solution	N/A	N/A	N/A	3.2	<0.1	<0.2	0.02	0.2	<0.01	278.8	0.3	0.1	613.67	985.15	<0.05	1.13	0.02
11D5	Solution	N/A	N/A	N/A	3.3	<0.1	<0.2	0.02	<0.1	<0.01	274.3	0.26	0.09	647.47	1027.03	<0.05	0.47	0.02
11D6	Solution	N/A	N/A	N/A	3	<0.1	<0.2	0.02	0.2	<0.01	270.7	0.28	0.09	630.29	1006.96	<0.05	0.64	0.02
11WW	Solution	N/A	N/A	N/A	15.9	<0.1	<0.2	0.05	4.3	<0.01	6755.9	14.26	0.83	5117.87	7681.99	<0.05	15.49	0.02
DRUM	Solution	N/A	N/A	N/A	2	<0.1	<0.2	0.01	0.3	<0.01	388.3	2.01	0.2	480.95	687.73	<0.05	3.93	0.02
11A	Solution	2545.1	N/A	N/A	1.5	<0.1	<0.2	0.04	<0.1	<0.01	277.9	0.26	0.11	514.32	863.7	<0.05	<0.05	0.02
11B	Solution	2625.2	N/A	N/A	1.5	<0.1	<0.2	0.02	<0.1	<0.01	253	0.02	0.18	805.58	1012.18	<0.05	3.9	0.02
Minimum detection Maximum detection Method		0.5 1000 CHSE	0.01 1000 Env	0.01 1000 Env	0.2 9999 ICPH2O	0.1 9999 ICPH2O	0.2 9999 ICPH2O	0.01 999 ICPH2O	0.1 9999 ICPH2O	0.01 989 ICPH2O	0.1 9999 ICPH2O	0.01 9999 ICPH2O	0.01 9999 ICPH2O	0.01 9999 ICPH2O	0.03 9999 ICPH2O	0.05 999 ICPH2O	0.05 9999 ICPH2O	0.05 9999 ICPH2O
Sample Name	Sample Type	Mg mg/L	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L
11F	Solution	0.4	5.58	<0.05	<0.02	0.28	<0.1	12	0.01	0.07	32	0.09	<0.2	<0.1	0.3	0.05	0.92	0.03
11Fud	Solution	6.2	513.59	<0.05	1.15	11.26	<0.1	80	0.17	<0.02	1856	6.12	<0.2	2.5	<0.1	3.13	78.44	1.99
11C1	Solution	0.9	6.48	<0.05	0.04	0.29	<0.1	12	<0.01	0.2	32	0.06	0.9	<0.1	0.1	0.06	24.58	0.03
11C2	Solution	1.1	6.82	<0.05	0.07	0.48	<0.1	7	0.01	0.4	31	0.04	<0.2	<0.1	<0.1	0.05	47.77	0.02
11C3	Solution	0.7	6.13	<0.05	0.03	0.51	<0.1	10	0.01	0.23	33	0.05	<0.2	<0.1	<0.1	0.03	29.31	<0.01
11C4	Solution	0.8	6.24	<0.05	0.06	0.33	<0.1	10	<0.01	0.3	32	0.04	0.4	<0.1	<0.1	0.04	31.68	0.02
11C5	Solution	0.5	6.3	<0.05	0.05	0.35	<0.1	9	0.01	0.24	34	0.06	<0.2	<0.1	<0.1	0.06	30.56	0.02
11C6	Solution	0.6	6.28	<0.05	0.11	0.38	<0.1	11	0.01	0.27	31	0.06	<0.2	<0.1	0.1	0.06	30.18	0.04
11C6ud	Solution	31.8	578.76	<0.05	3.3	14.7	<0.1	100	0.29	15.7	1867	4.13	<0.2	3.3	<0.1	5.79	3185.45	2.75
11D1	Solution	0.9	6.65	<0.05	0.09	0.47	<0.1	14	0.01	0.18	33	0.06	<0.2	<0.1	<0.1	0.05	25.85	0.03
11D2	Solution	0.4	5.76	<0.05	0.04	0.29	<0.1	12	0.01	0.07	32	0.09	<0.2	<0.1	<0.1	0.04	7.71	0.03
11D3	Solution	0.6	5.75	<0.05	0.06	0.34	<0.1	9	<0.01	0.11	32	0.08	<0.2	<0.1	<0.1	0.07	9.6	0.04
11D4	Solution	0.4	5.84	<0.05	0.06	0.23	<0.1	10	0.01	0.06	31	0.09	<0.2	<0.1	0.2	0.06	7.92	0.03
11D5	Solution	0.3	5.86	<0.05	0.08	0.38	<0.1	9	<0.01	0.09	36	0.09	<0.2	<0.1	<0.1	0.03	8.21	0.01
11D6	Solution	0.4	5.73	<0.05	<0.02	0.31	<0.1	11	<0.01	0.07	34	0.06	0.3	<0.1	0.3	0.03	7.87	0.02
11WW	Solution	1.8	39.08	<0.05	1.29	8.59	<0.1	17	0.03	0.85	146	4.16	6.2	0.7	<0.1	0.41	126	0.12
DRUM	Solution	3.2	2.94	<0.05	0.08	2.03	<0.1	25	<0.01	0.19	43	0.07	<0.2	<0.1	0.1	0.04	16.26	<0.01
11A	Solution	0.6	5.66	<0.05	0.06	0.29	<0.1	13	0.01	0.02	33	0.07	<0.2	<0.1	0.1	0.05	0.88	0.02
11B	Solution	0.9	6.63	<0.05	0.07	0.55	<0.1	13	<0.01	0.19	32	0.06	0.2	<0.1	<0.1	0.03	31.7	<0.01
Minimum detection Maximum detection Method		0.1 9999 ICPH2O	0.01 999 ICPH2O	0.05 9999 ICPH2O	0.02 9999 ICPH2O	0.02 9999 ICPH2O	0.1 9999 ICPH2O	2 9999 ICPH2O	0.01 100 ICPH2O	0.02 999 ICPH2O	0.1 9999 ICPH2O	0.01 999 ICPH2O	0.2 999 ICPH2O	0.1 999 ICPH2O	0.1 9999 ICPH2O	0.01 999 ICPH2O	0.01 9999 ICPH2O	0.01 9999 ICPH2O

Certificate#: 03G1118
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 14
 Date In: Jul 19, 2003
 Date Out: Jul 22, 2003

Sample Name	SampleType	S(tot) %	S(ele) %	S(-2) %	S(SO4) %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm	Pb ppm
12M1S	Pulp	N/A	N/A	N/A	N/A	1060	111	2433	<2	53	5	2190	33	68	133365	173816	<2	27
12M2S	Pulp	N/A	N/A	N/A	N/A	664	69	1647	2	38	<0.2	1830	2	77	269874	296485	<2	33
12M3S	Pulp	N/A	N/A	N/A	N/A	989	105	2256	<2	48	1.9	2456	3	68	166675	196083	<2	22
12M4S	Pulp	N/A	N/A	N/A	N/A	674	99	2188	<2	9	<0.2	1387	2	68	205638	222340	<2	28
12M5S	Pulp	N/A	N/A	N/A	N/A	820	96	2177	4	81	0.9	1698	3	66	175862	200595	<2	32
12M6S	Pulp	N/A	N/A	N/A	N/A	347	100	2292	4	<2	<0.2	861	1	74	213749	243284	<2	31
12N1S	Pulp	N/A	N/A	N/A	N/A	658	110	2468	7	39	5.7	1895	15	77	133196	183740	<2	28
12N2S	Pulp	N/A	N/A	N/A	N/A	703	128	2736	<2	3	<0.2	1451	37	69	70983	128401	<2	25
12N3S	Pulp	N/A	N/A	N/A	N/A	598	98	2173	<2	13	<0.2	1121	23	74	90520	147026	<2	17
12N3bulk	Pulp	N/A	N/A	N/A	N/A	832	107	2297	<2	35	<0.2	4670	34	82	83683	152456	<2	27
12N4S	Pulp	N/A	N/A	N/A	N/A	712	136	2861	<2	11	<0.2	1433	23	75	57840	123944	<2	19
12N5S	Pulp	N/A	N/A	N/A	N/A	679	131	2359	<2	<2	<0.2	1189	27	78	73140	138017	<2	23
12N6S	Pulp	N/A	N/A	N/A	N/A	958	154	3071	<2	14	<0.2	1953	40	71	59745	119605	<2	25
12N6bulk	Pulp	66.45	51.51	14.67	0.02	1027	143	2904	<2	20	<0.2	2639	51	76	62972	129914	<2	24
Minimum detection		0.01	0.01	0.01	0.01	100	5	5	2	2	0.2	100	1	1	1	100	2	2
Maximum detection		100	100	100	100	50000	2000	10000	10000	2000	2000	100000	10000	10000	10000	50000	10000	10000
Method		AsyWet	AsyWet	AsyWet	AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Sample Name	SampleType	Mg ppm	Mn ppm	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Ti ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
12M1S	Pulp	303	56	<3	6256	<1	<100	190	<1	42.6	125	<1	<10	154	<5	15	7443	5
12M2S	Pulp	202	45	<3	3524	<1	<100	144	<1	70.3	165	<1	<10	102	<5	20	6742	6
12M3S	Pulp	350	54	<3	4680	<1	<100	190	<1	51.5	130	1	<10	148	<5	15	6888	5
12M4S	Pulp	254	37	<3	2523	6	<100	167	<1	64.4	144	<1	<10	107	<5	16	6180	5
12M5S	Pulp	300	45	<3	3733	<1	<100	173	<1	52.3	134	<1	<10	127	<5	15	6321	4
12M6S	Pulp	182	27	<3	1066	2	<100	135	<1	62.4	142	<1	<10	<100	<5	15	5128	4
12N1S	Pulp	252	54	<3	3789	7	<100	811	<1	44.1	422	<1	66	<100	<5	14	7968	5
12N2S	Pulp	239	37	<3	5935	3	<100	155	<1	29	158	<1	11	<100	<5	11	3829	4
12N3S	Pulp	189	28	<3	6088	3	<100	216	<1	31.2	180	<1	60	<100	<5	11	3758	4
12N3bulk	Pulp	259	38	<3	6902	3	<100	224	<1	30.3	169	3	<10	112	<5	14	3588	4
12N4S	Pulp	248	33	<3	6637	7	<100	134	<1	26.2	167	<1	<10	<100	<5	11	3091	3
12N5S	Pulp	210	28	<3	5837	7	<100	212	<1	29	320	<1	99	<100	<5	11	2992	4
12N6S	Pulp	282	41	<3	6465	6	<100	177	<1	28.3	139	<1	<10	154	<5	12	2992	4
12N6bulk	Pulp	297	43	<3	6994	12	<100	202	<1	27.5	180	1	<10	156	<5	13	3025	4
Minimum detection		100	1	3	1	1	100	100	1	0.1	100	1	10	100	5	1	1	1
Maximum detection		100000	10000	10000	1000	10000	50000	100000	10000	100	100000	10000	1000	10000	1000	10000	10000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate#: 03G1117
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 18
 Date In: Jul 19, 2003
 Date Out: Jul 21, 2003

Sample Name	Sample Type	Cl- mg/L	F.A. H2SO4 G/L	F.A. HCl G/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L
12F	Solution	N/A	N/A	N/A	3	<0.1	<0.2	<0.01	<0.1	<0.01	281.3	0.26	0.04	558.19	904.75	<0.05	<0.05
12Fud	Solution	N/A	N/A	12.53	21.6	<0.1	8.7	0.18	420.7	3.09	31655.8	15.62	4.09	59249.7	96651.7	<0.05	7.55
12M1	Solution	N/A	N/A	N/A	4.2	<0.1	<0.2	<0.01	1	<0.01	271.3	0.28	0.2	864.63	1226.51	0.09	4.84
12M2	Solution	N/A	N/A	N/A	5.7	<0.1	0.4	<0.01	1.6	0.03	223.5	0.34	0.21	1025.2	1333.02	<0.05	10.46
12M3	Solution	N/A	N/A	N/A	4.6	<0.1	0.3	0.01	0.8	<0.01	247.2	0.5	0.18	919.48	1250.82	0.06	5.44
12M4	Solution	N/A	N/A	N/A	4.7	<0.1	0.6	0.01	0.9	<0.01	241.1	0.44	0.17	932.71	1259.33	<0.05	5.9
12M5	Solution	N/A	N/A	N/A	4.7	<0.1	0.5	<0.01	1.3	<0.01	246.9	0.39	0.17	919.38	1250.17	<0.05	5.37
12M6	Solution	N/A	N/A	N/A	4.8	<0.1	0.7	0.01	0.9	<0.01	243.5	0.38	0.14	945.92	1279.17	<0.05	5.54
12M6ud	Solution	N/A	2.17	N/A	117.3	<0.1	63	<0.01	442.6	9.01	24381	15.73	7.72	96342.3	128470.48	<0.05	477.25
12N1	Solution	N/A	N/A	N/A	3.8	<0.1	0.4	<0.01	0.8	<0.01	293.9	0.31	0.19	888.12	1294.75	<0.05	4.76
12N2	Solution	N/A	N/A	N/A	3.2	<0.1	<0.2	<0.01	0.5	<0.01	293.5	0.27	0.09	661.27	1030.66	<0.05	0.78
12N3	Solution	N/A	N/A	N/A	3.5	<0.1	0.6	<0.01	0.8	<0.01	288.2	0.33	0.13	785.87	1132.98	0.06	1.27
12N4	Solution	N/A	N/A	N/A	3.3	<0.1	<0.2	0.02	0.4	<0.01	285.9	0.33	0.1	681.83	1041.14	0.07	0.89
12N5	Solution	N/A	N/A	N/A	3.3	<0.1	0.7	0.02	0.4	<0.01	281.7	0.31	0.09	728.83	1078.94	<0.05	0.59
12N6	Solution	N/A	N/A	N/A	3.5	<0.1	0.2	0.02	0.3	<0.01	279	0.31	0.07	680.86	1029.45	<0.05	0.36
12N6	Solution	N/A	N/A	N/A	17.8	<0.1	3.1	0.05	4.8	<0.01	7696.5	12.7	0.83	5796.87	8366.7	0.13	14.38
12N6	Solution	2817.7	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
12A	Solution	265.9	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
12B	Solution																
Minimum detection		0.5	0.01	0.01	0.2	0.1	0.2	0.01	0.1	0.01	0.1	0.01	0.01	0.01	0.03	0.05	0.05
Maximum detection		1000	1000	1000	9999	9999	9999	999	9999	999	9999	9999	9999	9999	9999	999	9999
Method		CHSE	Env	Env	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20

Sample Name	Sample Type	Mg mg/L	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L
12F	Solution	0.2	6.01	<0.05	0.03	0.36	<0.1	7	<0.01	<0.02	30	0.08	<0.2	<0.1	<0.1	0.04	1.23	0.02
12Fud	Solution	6.7	569.53	<0.05	1.14	9.85	<0.1	83	0.15	<0.02	1476	6.5	127.3	2.3	<0.1	6.83	104.46	2.16
12M1	Solution	1	6.94	<0.05	0.1	0.31	<0.1	12	0.02	0.2	33	0.08	<0.2	<0.1	<0.1	0.03	27.29	0.04
12M2	Solution	1.1	7.5	<0.05	0.04	0.36	<0.1	6	<0.01	0.46	36	0.04	<0.2	<0.1	<0.1	0.02	54.38	<0.01
12M3	Solution	0.9	6.81	<0.05	0.13	0.45	<0.1	9	<0.01	0.3	29	0.06	0.7	<0.1	<0.1	0.06	33.45	0.03
12M4	Solution	1	6.79	<0.05	0.07	0.41	<0.1	9	<0.01	0.31	28	0.04	0.5	0.1	<0.1	0.05	35.29	0.02
12M5	Solution	0.9	6.71	<0.05	<0.02	0.45	<0.1	9	<0.01	0.3	30	0.06	<0.2	<0.1	<0.1	0.06	32.3	0.02
12M6	Solution	1.1	6.84	<0.05	0.07	0.55	<0.1	8	<0.01	0.31	29	0.06	0.8	0.1	<0.1	0.06	34.4	0.02
12M6ud	Solution	31.2	582.15	<0.05	2.93	4.8	<0.1	91	0.22	14.69	1200	3.54	212.3	4.5	<0.1	8.41	3489.05	2.41
12N1	Solution	0.7	7.39	0.14	0.07	0.45	<0.1	7	<0.01	0.24	30	0.07	0.3	<0.1	<0.1	0.05	29.31	0.02
12N2	Solution	0.2	6.4	0.16	0.06	0.38	<0.1	7	<0.01	0.08	32	0.08	<0.2	<0.1	<0.1	0.03	8.43	0.02
12N3	Solution	0.5	6.53	<0.05	0.1	0.35	<0.1	9	<0.01	0.15	31	0.08	<0.2	<0.1	<0.1	0.05	12.27	0.04
12N4	Solution	0.4	6.3	<0.05	0.11	0.4	<0.1	11	<0.01	0.07	31	0.08	<0.2	<0.1	<0.1	0.05	8.74	0.03
12N5	Solution	0.5	6.29	<0.05	0.03	0.52	<0.1	7	<0.01	0.1	34	0.08	<0.2	<0.1	<0.1	0.03	8.99	0.03
12N6	Solution	0.3	6.18	<0.05	<0.02	0.25	<0.1	5	<0.01	0.06	31	0.08	<0.2	<0.1	0.1	0.04	7.91	0.03
12N6	Solution	2.1	40.97	<0.05	1.06	8.5	<0.1	14	0.04	0.88	146	4.08	9.2	0.6	<0.1	0.39	126.33	0.15
12N6	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
12A	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
12B	Solution																	
Minimum detection		0.1	0.01	0.05	0.02	0.02	0.1	2	0.01	0.02	1	0.01	0.2	0.1	0.1	0.01	0.01	0.01
Maximum detection		9999	999	9999	9999	9999	9999	9999	100	999	9999	999	999	999	9999	999	9999	999
Method		ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20	ICPH20

Certificate#: 03H1328
Client: Metals & Materials Eng UBC
Project: BD28F06 EFDJ 713000
No. of Samples: 16
Date In: Aug 15, 2003
Date Out: Aug 21, 2003

Sample Name	SampleType	S(tot) %	S(ele) %	S(-2) %	S(SO4) %	SiO2 %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm
13FS	Pulp	32.42	N/A	N/A	N/A	4.48	1277	57	1222	5	<2	<0.2	6386	258	74	283460	288129	<2
13FSb	Pulp	N/A	N/A	N/A	N/A	N/A	1289	60	1338	5	<2	<0.2	6564	268	76	286261	286192	<2
13G1S	Pulp	N/A	N/A	N/A	N/A	N/A	921	136	1346	4	<2	<0.2	1484	65	74	118348	158732	<2
13G2S	Pulp	N/A	N/A	N/A	N/A	N/A	743	52	1337	5	<2	<0.2	1128	50	66	277976	258611	<2
13G3S	Pulp	N/A	N/A	N/A	N/A	N/A	698	106	2581	7	<2	<0.2	1065	57	70	183111	206582	<2
13G4S	Pulp	N/A	N/A	N/A	N/A	N/A	582	80	2068	8	<2	<0.2	1135	68	66	227136	231448	<2
13G5S	Pulp	N/A	N/A	N/A	N/A	N/A	736	90	2231	12	<2	<0.2	1545	48	68	222339	234398	<2
13G6S	Pulp	N/A	N/A	N/A	N/A	N/A	631	77	1916	3	<2	<0.2	818	44	67	250251	247285	<2
13H1S	Pulp	N/A	N/A	N/A	N/A	N/A	553	142	3212	<2	<2	<0.2	1336	39	76	116054	160149	<2
13H2S	Pulp	N/A	N/A	N/A	N/A	N/A	762	184	3992	<2	<2	<0.2	1015	68	71	14034	77270	<2
13H3S	Pulp	N/A	N/A	N/A	N/A	N/A	955	158	3470	<2	<2	<0.2	1004	83	73	33920	94160	<2
13H3bulk	Pulp	N/A	N/A	N/A	N/A	N/A	858	135	3745	<2	<2	<0.2	1017	81	82	37291	103285	<2
13H4S	Pulp	N/A	N/A	N/A	N/A	N/A	1014	138	1957	<2	<2	<0.2	1357	88	70	9406	76461	<2
13H5S	Pulp	N/A	N/A	N/A	N/A	N/A	721	141	3113	<2	<2	<0.2	588	58	72	25000	85917	<2
13H6S	Pulp	N/A	N/A	N/A	N/A	N/A	757	107	2333	<2	<2	<0.2	693	64	75	15680	83433	<2
13H6bulk	Pulp	72.76	61.81	10.41	0.1	N/A	898	113	2416	<2	<2	<0.2	916	71	75	18105	85730	<2
Minimum detection		0.01	0.01	0.01	0.01	0.01	100	5	5	2	2	0.2	100	1	1	1	100	2
Maximum detection		100	100	100	100	100	50000	2000	10000	10000	2000	2000	100000	10000	10000	10000	50000	10000
Method		AsyWet	AsyWet	AsyWet	AsyWet	AsyFus	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Sample Name	SampleType	Pb ppm	Mg ppm	Mn ppm	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Ti ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
13FS	Pulp	3648	386	180	<3	1223	152	<100	240	1	175.6	218	4	<10	116	<5	21	14704	8
13FSb	Pulp	3645	401	186	<3	1127	169	<100	209	1	119.6	242	5	<10	108	<5	22	14961	8
13G1S	Pulp	25	351	35	<3	2525	35	<100	177	<1	47.7	133	<1	<10	167	<5	7	2394	5
13G2S	Pulp	22	257	33	<3	3107	24	<100	131	<1	84.3	150	<1	<10	131	<5	12	4307	7
13G3S	Pulp	15	303	29	<3	2044	32	<100	221	<1	62.2	145	<1	<10	132	<5	10	2859	6
13G4S	Pulp	15	243	28	<3	1868	18	<100	147	<1	69.1	153	<1	<10	109	<5	11	3891	6
13G5S	Pulp	10	258	28	<3	2938	23	<100	107	<1	67.5	165	1	<10	145	<5	11	3417	6
13G6S	Pulp	15	224	26	<3	2059	20	<100	157	<1	74.1	147	<1	<10	139	<5	12	4200	6
13H1S	Pulp	15	215	31	<3	1729	23	<100	121	<1	46.3	150	<1	<10	105	<5	7	3041	4
13H2S	Pulp	16	293	24	<3	3240	38	<100	132	<1	22.6	136	<1	<10	138	<5	2	600	4
13H3S	Pulp	8	352	26	<3	6386	41	<100	193	<1	23.9	143	1	<10	170	5	<1	1154	4
13H3bulk	Pulp	11	296	26	<3	6062	51	<100	170	<1	27.9	143	<1	<10	153	<5	<1	1248	4
13H4S	Pulp	16	406	28	<3	6201	43	<100	235	<1	11.7	171	1	<10	187	8	<1	441	5
13H5S	Pulp	6	275	16	<3	8400	34	<100	114	<1	19.6	158	<1	<10	104	<5	<1	724	4
13H6S	Pulp	11	268	17	<3	8534	33	<100	183	<1	13.2	167	<1	<10	117	<5	<1	519	4
13H6bulk	Pulp	8	355	22	<3	7831	41	<100	222	<1	14.7	168	<1	<10	154	<5	<1	551	4
Minimum detection		2	100	1	3	1	1	100	100	1	0.1	100	1	10	100	5	1	1	1
Maximum detection		10000	10000	10000	10000	1000	10000	50000	100000	10000	100	100000	10000	10000	10000	1000	10000	10000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate# 03H1327
 Client: Metals & Materials Eng UBC
 Project: BD28F08 EFDJ 713000
 No. of Samples: 21
 Date In: Aug 15, 2003
 Date Out: Aug 18, 2003

Sample Name	Sample Type	Cl- mg/L	F.A. H2SO4 G/L	F.A. HCl G/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L
Grind Water	Solution	N/A	N/A	N/A	108.5	<0.1	<0.2	<0.01	0.5	14.43	509.9	1.72	11.8	2537.82	2269.57	0.13	<0.05
13F	Solution	N/A	N/A	N/A	1.5	0.1	<0.2	<0.01	0.4	<0.01	287.4	0.59	0.15	449.97	757.87	0.17	<0.05
13Fud	Solution	N/A	N/A	2.71	26.4	<0.1	2.1	0.19	0.1	<0.01	28912.9	35.01	4.66	45128.91	71683.1	<0.05	3.78
13G1	Solution	N/A	N/A	N/A	4.2	<0.1	<0.2	<0.01	0.5	<0.01	268.2	0.9	0.2	778.39	1086.94	0.08	4.45
13G2	Solution	N/A	N/A	N/A	5.6	<0.1	<0.2	<0.01	1.1	<0.01	256.6	1.38	0.22	804.39	1143.98	0.08	10.59
13G3	Solution	N/A	N/A	N/A	4.7	<0.1	<0.2	<0.01	<0.1	<0.01	257.1	1.02	0.18	811.84	1107.46	0.09	5.62
13G4	Solution	N/A	N/A	N/A	4.5	<0.1	0.2	<0.01	<0.1	<0.01	257.1	1.06	0.19	827.88	1117.57	0.08	6.11
13G5	Solution	N/A	N/A	N/A	4.5	0.1	0.6	<0.01	<0.1	<0.01	254.5	1.11	0.16	851.45	1152.03	<0.05	5.98
13G6	Solution	N/A	N/A	N/A	4.6	0.1	0.3	<0.01	1.6	<0.01	266.1	1.92	0.18	880.78	1180.39	0.07	5.91
13G6ud	Solution	N/A	<0.01	N/A	146.5	2.2	55.2	<0.01	0.4	2.55	23896.3	165.67	8.99	78609.77	105630.82	<0.05	542.49
13H1	Solution	N/A	N/A	N/A	4.3	<0.1	<0.2	<0.01	0.5	<0.01	269.1	0.93	0.17	796.77	1091.15	0.09	4.82
13H2	Solution	N/A	N/A	N/A	3.2	0.2	<0.2	<0.01	0.3	<0.01	281.3	0.63	0.14	571.88	851.09	0.14	0.63
13H3	Solution	N/A	N/A	N/A	3.7	<0.1	<0.2	<0.01	<0.1	<0.01	273.6	0.88	0.19	774.33	1058.67	0.11	1.25
13H4	Solution	N/A	N/A	N/A	3.3	0.2	0.5	<0.01	0.5	<0.01	275.4	0.63	0.13	598.63	875.99	0.12	0.7
13H5	Solution	N/A	N/A	N/A	3.6	<0.1	0.4	<0.01	0.2	<0.01	277.6	0.67	0.14	764.52	1060.66	<0.05	0.46
13H6	Solution	N/A	N/A	N/A	3.5	<0.1	0.4	<0.01	<0.1	<0.01	290.7	0.65	0.12	710.75	1002.51	<0.05	0.58
13HW	Solution	N/A	N/A	N/A	20.4	0.2	4.7	0.01	0.6	<0.01	6326.1	18.49	1.05	6941.67	10113.03	0.15	23.72
13Fsp	Solution	N/A	N/A	N/A	3.4	0.1	<0.2	<0.01	0.6	<0.01	319.1	0.47	1.16	479.53	727.85	0.06	0.16
11/12F	Solution	N/A	N/A	<0.01	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
13A	Solution	2227.2	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
13B	Solution	231.7	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection Maximum detection Method		0.5 1000 CHSE	0.01 1000 Env	0.01 1000 Env	0.2 9999 ICPH2O	0.1 9999 ICPH2O	0.2 9999 ICPH2O	0.01 999 ICPH2O	0.1 9999 ICPH2O	0.01 999 ICPH2O	0.1 9999 ICPH2O	0.01 9999 ICPH2O	0.01 9999 ICPH2O	0.01 9999 ICPH2O	0.03 9999 ICPH2O	0.05 999 ICPH2O	0.05 9999 ICPH2O

Sample Name	Sample Type	Mg mg/L	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L
Grind Water	Solution	48.2	214.79	<0.05	<0.02	10.15	<0.1	12	0.05	<0.02	15	0.5	<0.2	0.1	<0.1	0.11	5776.58	0.05
13F	Solution	1.1	3.94	<0.05	0.09	0.43	<0.1	20	0.01	<0.02	27	0.09	<0.2	<0.1	0.4	0.08	3.55	0.06
13Fud	Solution	4.8	350.47	<0.05	2.77	20.4	<0.1	95	0.16	<0.02	1770	7.02	<0.2	1.8	<0.1	2.47	50.92	1.87
13G1	Solution	1	4	<0.05	0.14	0.62	<0.1	11	<0.01	0.2	27	0.09	<0.2	<0.1	<0.1	0.06	18.52	0.04
13G2	Solution	1.3	4.35	<0.05	0.18	1.08	<0.1	7	0.01	0.41	30	0.08	<0.2	<0.1	<0.1	0.05	34.63	0.04
13G3	Solution	1	4.15	<0.05	0.13	0.72	<0.1	13	<0.01	0.26	31	0.08	<0.2	0.1	<0.1	0.04	22.32	0.03
13G4	Solution	0.9	4.1	<0.05	0.15	0.77	<0.1	11	<0.01	0.26	27	0.09	<0.2	<0.1	0.2	0.04	22.32	0.03
13G5	Solution	0.9	4.18	<0.05	0.07	0.89	<0.1	6	<0.01	0.28	30	0.09	<0.2	0.1	<0.1	0.04	22.36	0.03
13G6	Solution	1.2	4.32	<0.05	0.08	1.06	<0.1	12	0.01	0.33	28	0.06	<0.2	0.1	<0.1	0.05	22.92	0.03
13G6ud	Solution	42.3	368.98	<0.05	9.52	43.41	<0.1	114	0.3	19.22	1799	4.93	<0.2	6.1	<0.1	5.21	2080.22	2.65
13H1	Solution	0.8	4.03	<0.05	0.12	0.68	<0.1	12	0.01	0.26	29	0.09	<0.2	<0.1	<0.1	0.07	18.37	0.05
13H2	Solution	0.8	3.79	<0.05	<0.02	0.42	<0.1	16	0.02	0.07	29	0.11	0.2	<0.1	<0.1	0.09	4.45	0.07
13H3	Solution	0.9	3.88	<0.05	0.12	0.44	<0.1	14	<0.01	0.13	31	0.11	<0.2	<0.1	0.3	0.05	8.94	0.05
13H4	Solution	0.8	3.75	<0.05	0.05	0.47	<0.1	16	<0.01	0.1	28	0.09	<0.2	<0.1	<0.1	0.06	5.08	0.06
13H5	Solution	0.7	3.92	<0.05	0.09	0.42	<0.1	7	0.01	0.04	32	0.09	<0.2	<0.1	<0.1	0.03	7.58	0.03
13H6	Solution	0.1	4.04	<0.05	0.07	0.47	<0.1	<2	<0.01	0.04	32	0.09	<0.2	<0.1	0.1	0.06	6.66	0.02
13HW	Solution	2.8	33.87	<0.05	1.7	10.55	<0.1	20	0.05	1.17	174	3.55	0.3	0.8	<0.1	0.49	124.92	0.18
13Fsp	Solution	1.7	4.01	<0.05	0.08	0.44	<0.1	12	0.01	0.03	29	0.13	<0.2	<0.1	<0.1	0.07	0.89	0.04
11/12F	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
13A	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
13B	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection Maximum detection Method		0.1 9999 ICPH2O	0.01 999 ICPH2O	0.05 9999 ICPH2O	0.02 9999 ICPH2O	0.02 9999 ICPH2O	0.1 9999 ICPH2O	2 9999 ICPH2O	0.01 100 ICPH2O	0.02 999 ICPH2O	1 9999 ICPH2O	0.01 999 ICPH2O	0.2 999 ICPH2O	0.1 999 ICPH2O	0.1 9999 ICPH2O	0.01 999 ICPH2O	0.01 9999 ICPH2O	0.01 9999 ICPH2O

Certificate#: 03H1387
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 14
 Date In: Aug 22, 2003
 Date Out: Aug 27, 2003

Sample Name	SampleType	S(tot) %	S(ele) %	S(-2) %	S(SO4) %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm
14V1S	Pulp	N/A	N/A	N/A	N/A	609	121	2749	4	<2	<0.2	1345	55	68	104891	146353	<2
14V2S	Pulp	N/A	N/A	N/A	N/A	762	53	1272	5	<2	<0.2	2144	55	59	273190	252180	<2
14V3S	Pulp	N/A	N/A	N/A	N/A	781	95	2259	6	<2	<0.2	1762	56	68	173517	197059	<2
14V4S	Pulp	N/A	N/A	N/A	N/A	607	55	1421	5	<2	<0.2	1570	47	61	259949	250482	<2
14V5S	Pulp	N/A	N/A	N/A	N/A	631	79	2003	3	<2	<0.2	1401	50	68	207673	226263	<2
14V6S	Pulp	N/A	N/A	N/A	N/A	571	72	1799	4	<2	<0.2	1308	41	67	252085	247639	<2
14W1S	Pulp	N/A	N/A	N/A	N/A	481	144	3188	3	<2	<0.2	1198	46	74	119505	156978	<2
14W2S	Pulp	N/A	N/A	N/A	N/A	525	183	3884	<2	<2	<0.2	770	48	69	18566	80395	<2
14W3S	Pulp	N/A	N/A	N/A	N/A	682	154	3223	<2	<2	<0.2	811	81	72	61699	111538	<2
14W3Sbulk	Pulp	N/A	N/A	N/A	N/A	947	137	3097	<2	<2	<0.2	2654	85	65	53024	102172	<2
14W4S	Pulp	N/A	N/A	N/A	N/A	807	126	2422	<2	<2	<0.2	1390	75	72	30455	91798	<2
14W5S	Pulp	N/A	N/A	N/A	N/A	648	124	2837	<2	<2	<0.2	934	72	70	57593	109008	<2
14W6S	Pulp	N/A	N/A	N/A	N/A	668	116	2512	<2	<2	<0.2	1004	50	70	37811	97011	<2
14W6Sbulk	Pulp	71.86	60.01	11.5	0.06	870	128	2500	<2	<2	<0.2	1278	62	69	35974	94731	<2
Minimum detection		0.01	0.01	0.01	0.01	100	5	5	2	2	0.2	100	1	1	1	100	2
Maximum detection		100	100	100	100	50000	2000	10000	10000	20000	20000	100000	10000	10000	10000	50000	10000
Method		AsyWet	AsyWet	AsyWet	AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Sample Name	SampleType	Pb ppm	Mn ppm	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Ti ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
14V1S	Pulp	36	35	<3	1776	31	<100	<100	<1	41.5	137	<1	<10	100	<5	10	4078	4
14V2S	Pulp	33	49	<3	1154	16	<100	<100	1	76.2	148	1	<10	130	<5	19	5782	6
14V3S	Pulp	23	41	<3	1706	28	<100	107	<1	54.6	143	1	<10	138	<5	15	4055	5
14V4S	Pulp	23	41	<3	1216	15	<100	<100	<1	97.1	141	1	<10	104	<5	17	5793	6
14V5S	Pulp	18	36	<3	1901	26	<100	<100	<1	92.5	142	1	<10	104	<5	16	4561	6
14V6S	Pulp	22	34	<3	1379	13	<100	123	<1	123.8	162	<1	<10	105	<5	17	5095	6
14W1S	Pulp	21	34	<3	1981	24	<100	<100	<1	46.2	150	<1	<10	<100	<5	10	4877	4
14W2S	Pulp	19	21	<3	5351	29	<100	<100	<1	21.6	178	<1	<10	<100	<5	6	1380	3
14W3S	Pulp	10	26	<3	6896	47	<100	<100	<1	30.1	170	<1	<10	101	<5	9	2533	4
14W3Sbulk	Pulp	17	37	<3	5496	42	<100	<100	<1	26.1	164	2	<10	151	<5	9	2210	4
14W4S	Pulp	17	31	<3	4043	45	<100	125	<1	18.8	155	<1	<10	139	<5	8	1244	4
14W5S	Pulp	13	27	<3	4820	40	<100	<100	<1	27.3	149	<1	<10	<100	<5	8	2231	4
14W6S	Pulp	12	24	<3	6597	28	<100	<100	<1	19.9	160	<1	<10	<100	<5	8	1502	4
14W6Sbulk	Pulp	11	30	<3	7447	36	<100	106	<1	42.4	149	<1	<10	126	<5	8	1432	4
Minimum detection		2	1	3	1	1	100	100	1	0.1	100	1	10	100	5	1	1	1
Maximum detection		10000	10000	10000	10000	10000	50000	100000	10000	100	100000	100000	10000	100000	10000	10000	10000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate# 03H1388
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 24
 Date In: Aug 22, 2003
 Date Out: Aug 28, 2003

Sample Name	Sample Type	F.A.H2SO4 G/L	F.A.HCl G/L	Cl- mg/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L
SPTud	Solution	N/A	<0.01	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
SPT	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
14F	Solution	N/A	N/A	N/A	4.7	<0.1	<0.2	0.02	<0.1	<0.01	310.8	0.45	1.06	403.76	703.86	<0.05	<0.05
14Fud	Solution	N/A	N/A	N/A	4.7	<0.1	<0.2	0.02	0.4	<0.01	253.5	0.46	0.02	410.86	702.2	<0.05	<0.05
14V1	Solution	N/A	1.94	N/A	26.1	<0.1	<0.2	0.11	<0.1	<0.01	26310.9	33.29	4.62	43815.55	72571.79	<0.05	3.81
14V2	Solution	N/A	N/A	N/A	5.5	<0.1	<0.2	<0.01	0.4	<0.01	256.3	0.92	0.13	720.88	1022.59	<0.05	4.27
14V3	Solution	N/A	N/A	N/A	6.5	<0.1	<0.2	<0.01	1.8	<0.01	241.6	1.31	0.15	751.32	1070.57	<0.05	10.12
14V4	Solution	N/A	N/A	N/A	5.4	<0.1	<0.2	<0.01	0.5	<0.01	231.3	1.45	0.11	763.74	1082.62	<0.05	5
14V5	Solution	N/A	N/A	N/A	6	<0.1	<0.2	<0.01	0.6	<0.01	240.2	1.11	0.13	734.72	882.2	<0.05	5.6
14V6	Solution	N/A	N/A	N/A	5.8	<0.1	<0.2	<0.01	0.7	<0.01	241.3	1.02	0.12	721.72	894.15	<0.05	5.19
14V6ud	Solution	<0.01	N/A	N/A	113.4	0.2	19.3	<0.01	<0.1	4.64	23613.9	57.73	8.14	76549.18	101501.88	<0.05	4.84
14W1	Solution	N/A	N/A	N/A	5.3	<0.1	<0.2	<0.01	1	<0.01	252.1	0.91	0.07	527.88	998.41	<0.05	4.39
14W2	Solution	N/A	N/A	N/A	4.9	<0.1	<0.2	0.01	<0.1	<0.01	253.6	0.96	0.07	682.92	919.72	<0.05	1.07
14W3	Solution	N/A	N/A	N/A	4.9	<0.1	<0.2	0.01	0.5	<0.01	245.9	0.87	0.05	573.85	890.76	<0.05	0.7
14W4	Solution	N/A	N/A	N/A	5.3	<0.1	<0.2	0.01	0.7	<0.01	255.2	0.81	0.07	645.36	920.01	<0.05	0.55
14W5	Solution	N/A	N/A	N/A	3.5	<0.1	<0.2	0.03	0.7	<0.01	256.2	0.62	0.11	607.62	874.41	<0.05	0.49
14W6	Solution	N/A	N/A	N/A	18.2	<0.1	<0.2	0.02	2.5	<0.01	5645.6	14.06	0.93	5924.93	8329.17	<0.05	21.01
14W7	Solution	N/A	N/A	N/A	6	<0.1	<0.2	<0.01	0.4	<0.01	473.9	1.29	0.24	1014.52	1988.62	<0.05	9.24
14V4c	Solution	N/A	N/A	N/A	5.6	<0.1	<0.2	<0.01	0.4	<0.01	480.1	0.59	0.27	1080.64	2021.62	<0.05	8.72
14V6c	Solution	N/A	N/A	N/A	6.3	<0.1	<0.2	<0.01	<0.1	<0.01	492.2	1.11	0.24	1034.62	2018.6	<0.05	8.23
14V8b	Solution	N/A	N/A	N/A	5.1	<0.1	<0.2	<0.01	0.2	<0.01	463.9	0.23	0.22	1045.69	1883.31	<0.05	6.36
14A	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
14B	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection		0.01	0.01	0.5	0.2	0.1	0.2	0.01	0.1	0.01	0.1	0.01	0.01	0.01	0.03	0.05	0.05
Maximum detection		1000	1000	9999	9999	9999	9999	999	9999	999	9999	9999	9999	9999	9999	999	9999
Method		AsyWet	AsyWet	CH-SE	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Sample Name	Sample Type	Mg mg/L	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L
SPTud	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
SPT	Solution	1.1	3.93	<0.05	0.11	0.36	<0.1	<2	0.02	<0.02	39	0.12	<0.1	<0.1	0.2	<0.01	1.02	0.03
14F	Solution	<0.1	3.45	<0.05	0.02	0.32	<0.1	<2	<0.01	<0.02	39	0.09	<0.1	<0.1	<0.1	<0.01	0.68	<0.01
14Fud	Solution	6.7	329.74	<0.05	2.6	18.35	<0.1	80	0.16	<0.02	1944	6.75	<0.2	<0.2	<0.1	5.7	63.08	1.86
14V1	Solution	0.5	3.85	<0.05	0.13	0.39	<0.1	<2	<0.01	0.21	38	0.08	<0.2	<0.1	0.1	0.05	16.43	0.05
14V2	Solution	0.7	4.05	<0.05	0.2	0.8	<0.1	<2	<0.01	0.41	38	0.07	0.7	<0.1	<0.1	<0.01	30.23	0.02
14V3	Solution	0.3	3.9	<0.05	0.14	0.73	<0.1	<2	<0.01	0.25	36	0.08	<0.2	<0.1	<0.1	0.03	19.54	0.04
14V4	Solution	0.7	3.68	<0.05	0.11	0.67	<0.1	3	0.02	0.28	37	0.08	<0.2	<0.1	<0.1	0.04	19.7	0.05
14V5	Solution	0.6	3.77	<0.05	0.15	0.69	<0.1	<2	<0.01	0.23	39	0.08	<0.2	<0.1	0.1	0.04	18.86	0.05
14V5ud	Solution	0.7	3.81	<0.05	0.08	0.69	<0.1	<2	0.02	0.26	37	0.08	<0.2	<0.1	0.2	0.04	18.9	0.04
14V6ud	Solution	33.7	329.94	<0.05	7.28	27.62	<0.1	98	0.28	16.72	1791	5.11	<0.2	<0.2	<0.1	8.32	1880.58	2.53
14V1	Solution	0.8	3.83	<0.05	0.14	0.56	<0.1	2	0.02	0.23	36	0.08	<0.2	<0.1	0.1	0.04	16.3	0.07
14V2	Solution	<0.1	3.5	<0.05	0.09	0.46	<0.1	<2	<0.01	0.07	37	0.08	<0.2	<0.1	0.1	<0.01	5.04	0.02
14V3	Solution	0.3	3.54	<0.05	0.05	0.26	<0.1	<2	<0.01	0.1	36	0.08	<0.2	<0.1	<0.1	0.07	8.52	0.07
14V4	Solution	<0.1	3.6	<0.05	0.09	0.45	<0.1	<2	<0.01	<0.02	37	0.08	<0.2	<0.1	0.1	0.01	5.54	0.03
14V5	Solution	0.1	3.63	<0.05	0.02	0.2	<0.1	<2	<0.01	0.05	36	0.08	<0.2	<0.1	<0.1	<0.01	7.25	0.02
14V6	Solution	0.3	3.59	<0.05	0.03	0.4	<0.1	<2	<0.01	0.1	34	0.06	<0.2	<0.1	<0.1	0.05	5.8	0.05
14V7	Solution	2.2	30.23	<0.05	1.52	7.17	<0.1	4	0.04	1.07	173	3.34	<0.2	0.6	<0.1	0.43	104.38	0.18
14V4b	Solution	1	7.53	<0.05	0.13	1.23	<0.1	<2	<0.01	0.05	50	0.14	0.3	<0.1	<0.1	0.04	39.89	0.05
14V4c	Solution	0.9	7.73	<0.05	<0.02	1.29	<0.1	<2	<0.01	<0.02	52	0.16	0.5	<0.1	0.2	0.02	41.17	0.04
14V8b	Solution	1.2	7.68	<0.05	0.1	1.08	<0.1	6	<0.01	0.04	53	0.16	<0.2	<0.1	0.1	0.04	37.94	0.05
14V8c	Solution	0.8	7.3	<0.05	<0.02	1.32	<0.1	<2	<0.01	0.08	50	0.14	<0.2	<0.1	<0.1	0.04	35.81	0.05
14A	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
14B	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection		0.1	0.01	0.05	0.02	0.02	0.1	2	0.01	0.02	1	0.01	0.2	0.1	0.1	0.01	0.01	0.01
Maximum detection		9999	999	9999	9999	9999	9999	9999	100	999	9999	999	999	999	9999	999	9999	999
Method		ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Certificate#: 0311469
 Client: Metals & Materials Eng UBC
 Project: BD25F06 EFDJ 713000
 No. of Samples: 14
 Date In: Sep 08, 2003
 Date Out: Sep 11, 2003

Sample Name	SampleType	S(ot) %	S(ele) %	S(-2) %	S(SO4) %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm	Pb ppm
15S1S	Pulp	N/A	N/A	N/A	N/A	796	120	2889	7	<2	4	2213	76	74	110562	152905	<2	24
15S2S	Pulp	N/A	N/A	N/A	N/A	815	54	1412	21	<2	<0.2	2810	65	62	269919	257175	<2	25
15S3S	Pulp	N/A	N/A	N/A	N/A	1041	112	2567	5	<2	<0.2	3498	78	68	160656	186577	<2	24
15S4S	Pulp	N/A	N/A	N/A	N/A	786	86	1986	6	<2	<0.2	2686	56	68	239793	244945	<2	28
15S5S	Pulp	N/A	N/A	N/A	N/A	874	105	2315	6	<2	<0.2	3488	58	66	186849	204525	<2	27
15S6S	Pulp	N/A	N/A	N/A	N/A	692	102	2542	<2	<2	<0.2	1803	42	68	206490	217725	<2	21
15T1S	Pulp	N/A	N/A	N/A	N/A	660	146	3301	3	<2	5.1	1955	77	73	117345	155844	<2	23
15T2S	Pulp	N/A	N/A	N/A	N/A	801	172	3977	<2	<2	<0.2	1703	82	65	28434	83603	<2	20
15T3S	Pulp	N/A	N/A	N/A	N/A	600	128	3120	<2	<2	<0.2	1392	77	71	76982	123269	<2	9
15T3bulk	Pulp	N/A	N/A	N/A	N/A	944	133	3063	<2	<2	<0.2	3584	99	74	75069	123787	<2	13
15T4S	Pulp	N/A	N/A	N/A	N/A	1127	121	2418	<2	<2	<0.2	2972	99	76	38025	105219	<2	26
15T5S	Pulp	N/A	N/A	N/A	N/A	710	107	2729	<2	<2	<0.2	1386	79	72	77938	127179	<2	22
15T6S	Pulp	N/A	N/A	N/A	N/A	759	114	2521	<2	<2	<0.2	1718	76	72	41956	102740	<2	23
15T6bulk	Pulp	71.56	57.8	13.29	0.06	890	97	2060	<2	<2	<0.2	2430	65	70	38726	101343	<2	23
Minimum detection		0.01	0.01	0.01	0.01	100	5	5	2	2	0.2	100	1	1	1	100	2	2
Maximum detection		100	100	100	100	50000	2000	10000	10000	2000	2000	100000	10000	10000	10000	50000	10000	10000
Method		AsyWet	AsyWet	AsyWet	AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Sample Name	SampleType	Mg ppm	Mn ppm	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Ti ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
15S1S	Pulp	293	54	<3	4399	50	<100	<100	<1	43.7	<100	<1	<10	125	<5	13	8414	5
15S2S	Pulp	261	59	<3	1788	26	<100	<100	<1	79	<100	1	<10	131	<5	18	5776	7
15S3S	Pulp	362	70	<3	2418	41	<100	136	<1	53.9	<100	1	<10	176	<5	16	4838	6
15S4S	Pulp	277	55	<3	1730	28	<100	<100	<1	74.7	<100	<1	<10	137	<5	18	4814	7
15S5S	Pulp	311	66	<3	2555	29	<100	<100	<1	57.2	<100	<1	<10	138	<5	16	4685	6
15S6S	Pulp	241	39	<3	3563	15	<100	<100	<1	62.8	<100	<1	<10	123	<5	15	4250	6
15T1S	Pulp	229	51	<3	2937	36	<100	<100	<1	44.8	<100	<1	<10	109	<5	11	6766	4
15T2S	Pulp	280	38	<3	6393	37	<100	<100	<1	25.5	118	1	<10	137	<5	11	2092	4
15T3S	Pulp	221	34	<3	5343	42	<100	<100	<1	33.4	<100	<1	<10	<100	<5	9	2917	4
15T3bulk	Pulp	332	49	<3	4528	55	<100	<100	<1	34.8	111	1	<10	167	<5	12	2927	5
15T4S	Pulp	412	60	<3	4251	56	<100	115	<1	21.6	119	1	<10	201	<5	13	1975	6
15T5S	Pulp	262	34	<3	3915	41	<100	<100	<1	32.2	102	<1	<10	117	<5	10	2494	4
15T6S	Pulp	258	38	<3	6140	41	<100	<100	<1	21.6	<100	<1	<10	116	<5	10	1749	4
15T6bulk	Pulp	354	49	<3	5582	41	<100	<100	<1	18.7	<100	<1	<10	141	6	12	1591	5
Minimum detection		100	1	3	1	1	100	100	1	0.1	100	1	10	100	5	1	1	1
Maximum detection		100000	10000	10000	1000	10000	50000	100000	10000	100	100000	10000	10000	100000	1000	10000	10000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate#: 0311468
 Client: Metals & Materials Eng. UBC
 Project: BD28F08 EEDJ 713000
 No. of Samples: 18
 Date In: Sep 08, 2003
 Date Out: Sep 10, 2003

Sample Name	Sample Type	F.A.H2SO4 G/L	F.A. HCl G/L	Cl- mg/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L
15F	Solution	N/A	N/A	N/A	3.1	<0.1	<0.2	0.04	0.3	<0.01	272.2	0.58	0.05	477.1	801.18	<0.05	<0.05
15Fud	Solution	N/A	3.01	N/A	29	<0.1	<0.2	0.12	<0.1	<0.01	27393.1	37.79	5.08	5079.36	80294.11	<0.05	3.23
15S1	Solution	N/A	N/A	N/A	4	<0.1	<0.2	0.03	0.8	<0.01	270.8	0.93	0.13	790.79	1121.12	<0.05	4.66
15S2	Solution	N/A	N/A	N/A	4.6	<0.1	<0.2	<0.01	1.5	<0.01	246.7	1.3	0.13	845.82	1179.03	<0.05	9.75
15S3	Solution	N/A	N/A	N/A	3.9	<0.1	<0.2	<0.01	1	<0.01	255	1.07	0.14	814.65	1148.29	0.05	5.08
15S4	Solution	N/A	N/A	N/A	4.3	<0.1	<0.2	<0.01	0.8	<0.01	256.7	1.15	0.13	876.55	1213.92	<0.05	5.92
15S5	Solution	N/A	N/A	N/A	3.9	<0.1	<0.2	<0.01	0.7	<0.01	256.7	1.15	0.13	862.46	1175.47	<0.05	5.54
15S6	Solution	N/A	N/A	N/A	4.4	0.2	<0.2	0.03	0.8	<0.01	277.9	1.17	0.15	811	1129.3	<0.05	4.91
15S6ud	Solution	<0.01	N/A	N/A	118.7	1.4	22.4	<0.01	<0.1	1.73	27107.5	64.39	8.9	89348.47	118860.29	<0.05	425.6
15T1	Solution	N/A	N/A	N/A	4	<0.1	<0.2	<0.01	0.8	<0.01	270.5	0.9	0.05	796.14	1131.32	<0.05	4.2
15T2	Solution	N/A	N/A	N/A	3.3	<0.1	<0.2	0.02	<0.1	<0.01	277	0.63	0.06	559.13	884.12	<0.05	0.84
15T3	Solution	N/A	N/A	N/A	3.8	<0.1	<0.2	0.01	0.9	<0.01	275.5	0.79	0.11	740.45	1071.72	<0.05	2.31
15T4	Solution	N/A	N/A	N/A	3.2	<0.1	<0.2	0.01	0.1	<0.01	277.4	0.7	0.1	619.94	949.56	<0.05	1.21
15T5	Solution	N/A	N/A	N/A	3.4	<0.1	<0.2	0.01	0.4	<0.01	277.8	0.71	0.09	672.74	1004.4	<0.05	1.06
15T6	Solution	N/A	N/A	N/A	3.2	<0.1	<0.2	0.02	0.2	<0.01	280.4	0.69	0.07	654.21	969.16	<0.05	0.77
15T6	Solution	N/A	N/A	N/A	17.8	<0.1	<0.2	0.03	5	<0.01	5313.6	15.14	0.87	5641.58	7931.65	<0.05	18.76
15WW	Solution	N/A	N/A	2844.8	3.2	<0.1	<0.2	0.02	<0.1	<0.01	280.8	0.58	0.02	468.23	619.24	<0.05	<0.05
15A	Solution	N/A	N/A	299.1	2.2	<0.1	<0.2	<0.01	<0.1	<0.01	27.2	0.11	<0.01	85.88	118.77	<0.05	0.53
15B	Solution	N/A	N/A	N/A	0.2	0.1	0.2	0.01	0.1	0.01	0.1	0.01	0.01	0.01	0.03	0.05	0.05
Minimum detection Maximum detection Method		0.01 1000 AsyWet	0.01 1000 AsyWet	0.5 1000 CH-SE	9999 9999 ICPH2O	9999 9999 ICPH2O	9999 9999 ICPH2O	999 999 ICPH2O	9999 9999 ICPH2O	999 999 ICPH2O	9999 9999 ICPH2O	9999 9999 ICPH2O	9999 9999 ICPH2O	9999 9999 ICPH2O	9999 9999 ICPH2O	999 999 ICPH2O	9999 9999 ICPH2O

Sample Name	Sample Type	Mg mg/L	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L
15F	Solution	0.2	3.93	<0.05	0.05	0.37	<0.1	4	<0.01	<0.02	30	0.09	<0.2	<0.1	0.4	0.04	0.44	0.07
15Fud	Solution	6.7	372.41	<0.05	3.4	22.83	<0.1	82	0.18	<0.02	2019	7.48	<0.2	1.9	<0.1	6.15	41	2.25
15S1	Solution	0.5	4.26	<0.05	0.14	0.55	<0.1	4	<0.01	0.18	33	0.09	<0.2	<0.1	0.4	<0.01	14.78	0.02
15S2	Solution	0.7	4.42	<0.05	0.18	0.88	<0.1	2	<0.01	0.41	31	0.06	<0.2	<0.1	0.1	0.02	28.5	0.04
15S3	Solution	0.7	4.19	<0.05	0.18	0.59	<0.1	<2	0.02	0.32	31	0.09	<0.2	<0.1	<0.1	0.04	19.22	0.05
15S4	Solution	0.5	4.29	<0.05	0.14	0.73	<0.1	<2	0.02	0.32	30	0.09	<0.2	<0.1	0.2	0.06	21.91	0.05
15S5	Solution	0.6	4.29	<0.05	0.13	0.78	<0.1	4	0.02	0.3	35	0.09	<0.2	<0.1	0.3	0.06	20.53	0.06
15S6	Solution	0.4	4.53	<0.05	0.17	0.73	<0.1	3	0.02	0.27	35	0.09	<0.2	<0.1	<0.1	0.07	19.27	0.06
15S6ud	Solution	37	375.41	<0.05	8.69	37.33	<0.1	92	0.38	18.21	1978	5.92	<0.2	4.7	<0.1	9.5	1933.23	3.09
15T1	Solution	0.1	4.3	<0.05	0.17	0.56	<0.1	<2	<0.01	0.16	33	0.09	<0.2	<0.1	<0.1	<0.01	14.93	<0.01
15T2	Solution	<0.1	4	<0.05	<0.02	0.48	<0.1	<2	<0.01	0.05	32	0.09	<0.2	<0.1	<0.1	0.03	4.56	0.03
15T3	Solution	0.3	4.22	<0.05	0.09	0.31	<0.1	3	<0.01	0.15	31	0.09	<0.2	<0.1	0.2	0.03	10.14	0.04
15T4	Solution	0.4	4.1	<0.05	0.12	0.48	<0.1	<2	<0.01	0.05	30	0.09	<0.2	<0.1	0.1	0.02	6.36	0.03
15T5	Solution	<0.1	4.16	<0.05	0.07	0.31	<0.1	<2	<0.01	<0.02	32	0.09	<0.2	<0.1	<0.1	0.02	6.97	0.03
15T6	Solution	<0.1	4.15	<0.05	0.06	0.37	<0.1	<2	0.02	0.1	34	0.09	<0.2	<0.1	<0.1	0.05	5.74	0.04
15WW	Solution	1.5	29.91	<0.05	1.79	9.31	<0.1	2	0.03	1.09	165	3.3	<0.2	0.7	0.6	0.42	83.28	0.16
15A	Solution	<0.1	4.01	<0.05	0.08	0.34	<0.1	<2	<0.01	<0.02	36	0.09	<0.2	<0.1	0.2	<0.01	0.45	<0.01
15B	Solution	<0.1	0.45	<0.05	0.05	<0.02	<0.1	<2	<0.01	<0.02	20	<0.01	<0.2	<0.1	0.1	<0.01	1.9	<0.01
Minimum detection Maximum detection Method		0.1 9999 ICPH2O	0.01 999 ICPH2O	0.05 9999 ICPH2O	0.02 9999 ICPH2O	0.02 9999 ICPH2O	0.1 9999 ICPH2O	2 9999 ICPH2O	0.01 100 ICPH2O	0.02 999 ICPH2O	1 9999 ICPH2O	0.01 999 ICPH2O	0.2 999 ICPH2O	0.1 999 ICPH2O	0.1 9999 ICPH2O	0.01 999 ICPH2O	0.01 9999 ICPH2O	0.01 999 ICPH2O

Certificate#: 0311515
 Client: Metals & Materials Eng.UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 14
 Date In: Sep 15, 2003
 Date Out: Sep 18, 2003

Sample Name	Sample Type	S(ot) %	S(ele) %	S(-2) %	S(SO4) %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm	Pb ppm
16X1S	Pulp	N/A	N/A	N/A	N/A	749	127	2878	4	<2	<0.2	2139	45	71	145959	182597	<2	15
16X2S	Pulp	N/A	N/A	N/A	N/A	726	51	1269	7	<2	<0.2	3052	45	63	263599	273121	<2	31
16X3S	Pulp	N/A	N/A	N/A	N/A	761	95	2088	5	<2	<0.2	2922	29	66	185678	217079	<2	15
16X4S	Pulp	N/A	N/A	N/A	N/A	451	55	1371	5	<2	<0.2	1714	24	64	231320	247180	<2	20
16X5S	Pulp	N/A	N/A	N/A	N/A	755	95	2235	7	<2	<0.2	3227	60	67	215842	236948	<2	23
16X6S	Pulp	N/A	N/A	N/A	N/A	546	82	1984	4	<2	<0.2	2311	37	66	230191	249278	<2	21
16Y1S	Pulp	N/A	N/A	N/A	N/A	639	131	2960	2	<2	<0.2	1867	70	74	146814	185348	<2	13
16Y2S	Pulp	N/A	N/A	N/A	N/A	764	165	3532	<2	<2	<0.2	1787	46	68	66583	120219	<2	12
16Y3S	Pulp	N/A	N/A	N/A	N/A	734	135	2980	<2	<2	<0.2	1555	77	70	108987	152447	<2	12
16Y3bulk	Pulp	N/A	N/A	N/A	N/A	788	120	2666	<2	<2	<0.2	1910	40	64	93370	137352	<2	18
16Y4S	Pulp	N/A	N/A	N/A	N/A	1133	130	2491	<2	<2	<0.2	3525	65	73	69372	133503	<2	15
16Y5S	Pulp	N/A	N/A	N/A	N/A	822	114	2612	<2	<2	<0.2	2119	62	72	93550	144423	<2	14
16Y6S	Pulp	N/A	N/A	N/A	N/A	1005	114	2459	<2	<2	<0.2	2758	70	70	79374	134559	<2	16
16Y6bulk	Pulp	68.61	52.22	16.09	0.06	1203	122	2522	<2	<2	<0.2	2843	90	71	77586	132711	<2	14
Minimum detection		0.01	0.01	0.01	0.01	100	5	5	2	2	0.2	100	1	1	1	100	2	2
Maximum detection		100	100	100	100	50000	2000	10000	10000	2000	2000	100000	10000	10000	10000	50000	10000	10000
Method		AsyWet	AsyWet	AsyWet	AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Sample Name	Sample Type	Mg ppm	Mn ppm	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Ti ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
16X1S	Pulp	253	56	<3	4286	13	<100	101	<1	45.8	<100	<1	<10	<100	<5	8	8280	5
16X2S	Pulp	306	67	<3	1137	16	<100	128	<1	74.2	<100	<1	<10	<100	<5	14	6375	6
16X3S	Pulp	306	64	<3	3496	12	<100	137	<1	54.2	<100	<1	<10	<100	<5	11	6591	5
16X4S	Pulp	216	42	<3	2010	14	<100	105	<1	63.9	<100	<1	<10	<100	<5	11	5914	5
16X5S	Pulp	286	69	<3	2062	31	<100	121	<1	62.4	<100	<1	<10	106	<5	13	6453	6
16X6S	Pulp	225	53	<3	1946	7	<100	158	<1	65	<100	<1	<10	<100	<5	13	6319	5
16Y1S	Pulp	224	57	<3	4122	38	<100	<100	<1	49.7	<100	<1	<10	<100	<5	9	8521	5
16Y2S	Pulp	264	42	<3	7733	21	<100	108	<1	30.4	102	<1	<10	<100	<5	5	3943	4
16Y3S	Pulp	244	43	<3	6303	38	<100	122	<1	38.5	<100	<1	<10	<100	<5	8	4634	4
16Y3bulk	Pulp	258	43	<3	6716	17	<100	<100	<1	33.2	<100	<1	<10	<100	<5	7	4095	5
16Y4S	Pulp	372	73	<3	6785	37	<100	134	<1	26.8	108	<1	<10	153	<5	11	3809	5
16Y5S	Pulp	283	48	<3	6034	29	<100	168	<1	33.3	107	<1	<10	<100	<5	8	4161	4
16Y6S	Pulp	337	60	<3	6336	35	<100	177	<1	29.2	138	<1	<10	142	<5	9	3904	5
16Y6bulk	Pulp	386	63	<3	7470	46	<100	120	<1	28.7	116	<1	<10	179	<5	10	3822	5
Minimum detection		100	1	3	1	1	100	100	1	0.1	100	1	10	100	5	1	1	1
Maximum detection		100000	10000	10000	1000	10000	50000	100000	10000	100	100000	10000	1000	10000	1000	10000	10000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate# 031514
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 20
 Date In: Sep 15, 2003
 Date Out: Sep 18, 2003

Sample Name	Sample Type	F.A.H2SO4 G/L	F.A.HCl G/L	Cl- mg/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L
Cu	Solution	N/A	N/A	N/A	2.6	<0.1	<0.2	<0.01	1	<0.01	0.5	0.17	<0.01	1369.34	2.75	<0.05	<0.05
Fe	Solution	N/A	N/A	N/A	2.8	<0.1	<0.2	<0.01	<0.1	<0.01	0.5	0.09	<0.01	0.4	1138.81	<0.05	<0.05
16F	Solution	N/A	N/A	N/A	3.7	<0.1	<0.2	0.02	0.1	<0.01	252.3	0.55	0.04	480.15	752.56	<0.05	0.07
16Fud	Solution	N/A	3.69	N/A	30.7	<0.1	<0.2	<0.01	<0.1	<0.01	25915.6	38.26	4.99	46763.02	74827.94	<0.05	3.03
16X1	Solution	N/A	N/A	N/A	4.7	0.2	<0.2	<0.01	0.3	<0.01	257.3	0.9	0.11	766.18	1049.16	0.05	4.24
16X2	Solution	N/A	N/A	N/A	5	<0.1	<0.2	<0.01	1.6	<0.01	234.2	1.25	0.08	816.27	1091.48	<0.05	8.79
16X3	Solution	N/A	N/A	N/A	4.6	<0.1	<0.2	<0.01	1	<0.01	237.4	1.01	0.11	788.99	1046.8	0.05	5.07
16X4	Solution	N/A	N/A	N/A	4.8	<0.1	<0.2	<0.01	0.5	<0.01	240.6	0.99	0.12	811.99	1076.01	<0.05	5.56
16X5	Solution	N/A	N/A	N/A	4.4	<0.1	<0.2	<0.01	0.8	<0.01	246.5	1	0.08	805.77	1074.79	<0.05	5.06
16X6	Solution	N/A	N/A	N/A	4.5	<0.1	<0.2	0.04	0.7	<0.01	231.3	0.93	0.1	750.83	1002.13	<0.05	4.5
16X6ud	Solution	<0.01	N/A	N/A	121.2	0.3	10.6	<0.01	<0.1	<0.01	26159.8	65.19	9.11	85823.04	112687.49	<0.05	471.16
16Y1	Solution	N/A	N/A	N/A	4.7	0.1	<0.2	<0.01	1	<0.01	257.3	0.91	0.08	764.84	1046.42	<0.05	4.43
16Y2	Solution	N/A	N/A	N/A	3.6	<0.1	<0.2	<0.01	0.3	<0.01	264.1	0.62	0.08	565.45	832.96	<0.05	0.56
16Y3	Solution	N/A	N/A	N/A	4.1	<0.1	<0.2	0.02	<0.1	<0.01	257.4	0.68	0.05	685.21	939.2	<0.05	1.18
16Y4	Solution	N/A	N/A	N/A	4.1	<0.1	<0.2	0.02	0.2	<0.01	264	0.61	0.08	613.12	883.55	0.09	0.88
16Y5	Solution	N/A	N/A	N/A	3.9	<0.1	<0.2	<0.01	0.4	<0.01	261.7	0.66	0.1	664.87	920.21	<0.05	0.91
16Y6	Solution	N/A	N/A	N/A	4.1	<0.1	<0.2	0.02	<0.1	<0.01	267.8	0.65	0.1	638.17	915.3	<0.05	0.8
16W	Solution	N/A	N/A	N/A	18	<0.1	<0.2	0.01	<0.1	<0.01	4898.1	12.75	0.89	5761.1	8026.4	0.07	18.65
16A	Solution	N/A	N/A	2537.3	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
16B	Solution	N/A	N/A	256.9	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection		0.01	0.01	0.5	0.2	0.1	0.2	0.01	0.1	0.01	0.1	0.01	0.01	0.01	0.03	0.05	0.05
Maximum detection		1000	1000	1000	9999	9999	9999	999	9999	999	9999	9999	9999	9999	9999	999	9999
Method		AsyWet	AsyWet	CH-SE	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Sample Name	Sample Type	Mg mg/L	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L	
Cu	Solution	<0.1	0.02	0.05	0.04	<0.02	<0.1	<2	0.03	<0.02	20	<0.01	<0.2	<0.1	0.7	0.06	0.05	0.04	
Fe	Solution	<0.1	0.09	<0.05	0.37	<0.02	<0.1	9	<0.01	<0.02	18	<0.01	<0.2	<0.1	0.5	0.03	0.02	0.03	
16F	Solution	<0.1	3.76	0.15	0.1	0.52	<0.1	5	<0.01	<0.02	39	0.11	<0.2	<0.1	0.4	0.04	0.24	0.04	
16Fud	Solution	3.9	358.04	<0.05	4.04	23.75	<0.1	78	0.23	<0.02	1936	7.48	<0.2	<0.1	0.9	6.64	22.6	2.09	
16X1	Solution	0.4	4.03	0.06	0.12	0.59	<0.1	13	0.01	0.17	38	0.11	<0.2	<0.1	0.7	0.03	12.63	0.06	
16X2	Solution	0.6	4.09	<0.05	0.07	0.74	<0.1	<2	0.01	0.38	37	0.07	<0.2	<0.1	0.2	0.04	24.37	0.05	
16X3	Solution	0.5	3.85	0.06	0.12	0.63	<0.1	8	0.02	0.32	39	0.07	<0.2	<0.1	0.3	0.05	17.06	0.06	
16X4	Solution	0.7	3.96	0.09	0.17	0.64	<0.1	<2	<0.01	0.25	39	0.07	<0.2	<0.1	0.3	0.04	18.8	<0.01	
16X5	Solution	0.3	4.05	<0.05	0.16	0.68	<0.1	<2	<0.01	0.25	37	0.09	<0.2	<0.1	0.5	0.02	18.17	<0.01	
16X6	Solution	0.4	3.77	0.08	0.17	0.6	<0.1	<2	<0.01	0.21	36	0.09	<0.2	<0.1	0.3	0.07	16.54	0.03	
16X6ud	Solution	33.6	357.55	<0.05	9.77	36.2	<0.1	92	0.45	20.53	1757	6.05	<0.2	4	0.3	10.03	1911.7	2.91	
16Y1	Solution	0.4	4.01	0.06	0.15	0.39	<0.1	3	0.02	0.2	39	0.11	<0.2	<0.1	0.3	0.09	12.63	0.04	
16Y2	Solution	0.3	3.78	0.2	0.12	0.35	<0.1	8	<0.01	0.03	36	0.11	<0.2	<0.1	0.2	0.05	4.87	0.05	
16Y3	Solution	<0.1	3.82	0.09	0.07	0.44	<0.1	3	0.01	0.1	37	0.11	<0.2	<0.1	0.3	0.06	7.01	0.07	
16Y4	Solution	0.6	3.84	0.32	0.1	0.44	<0.1	8	<0.01	0.04	38	0.11	<0.2	<0.1	<0.1	0.04	5.39	<0.01	
16Y5	Solution	0.3	3.84	0.16	0.09	0.39	<0.1	3	<0.01	0.12	39	0.11	<0.2	<0.1	0.2	0.08	5.79	0.08	
16Y6	Solution	0.5	3.9	0.19	0.18	0.39	<0.1	8	0.01	0.08	38	0.11	<0.2	<0.1	0.4	0.07	5.67	0.06	
16WW	Solution	2.1	30.74	<0.05	1.7	6.63	<0.1	11	0.05	1.04	168	3.01	<0.2	0.7	0.2	0.56	80.54	0.2	
16A	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
16B	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection		0.1	0.01	0.05	0.02	0.02	0.1	2	0.01	0.02	1	0.01	0.2	0.1	0.1	0.01	0.01	0.01	
Maximum detection		9999	9999	9999	9999	9999	9999	9999	100	999	9999	999	999	999	9999	999	9999	9999	
Method		ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	

Certificate# 0311563
Client: Metals & Materials Eng UBC
Project: BD28F06 EFDJ 713000
No. of Samples: 15
Date In: Sep 22, 2003
Date Out: Oct 05, 2003

Sample Name	Sample Type	S(tot) %	S(ele) %	S(-2) %	S(SO4) %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm	Pb ppm
17K1S	Pulp	N/A	N/A	N/A	N/A	766	73	1660	3	<2	<0.2	2302	22	66	234143	261107	<2	10
17K2S	Pulp	N/A	N/A	N/A	N/A	633	46	1282	5	<2	<0.2	1609	28	65	271411	281159	<2	21
17K3S	Pulp	N/A	N/A	N/A	N/A	652	65	1568	5	<2	<0.2	1713	73	67	251805	266364	<2	18
17K4S	Pulp	N/A	N/A	N/A	N/A	562	59	1463	4	<2	<0.2	1321	61	63	255114	270135	<2	19
17K5S	Pulp	N/A	N/A	N/A	N/A	633	62	1543	2	<2	<0.2	1262	62	65	248997	265873	<2	10
17K6S	Pulp	N/A	N/A	N/A	N/A	663	61	1530	5	<2	<0.2	1278	31	67	240156	263287	<2	14
17K6Sbulk	Pulp	N/A	N/A	N/A	N/A	622	65	1585	3	<2	<0.2	1156	41	66	249548	267422	<2	13
17L1S	Pulp	N/A	N/A	N/A	N/A	970	45	1012	14	<2	<0.2	3250	276	28	13461	432380	<2	758
17L2S	Pulp	N/A	N/A	N/A	N/A	619	49	1105	11	<2	<0.2	1682	175	27	28793	407942	<2	26
17L3S	Pulp	N/A	N/A	N/A	N/A	503	52	1214	13	<2	<0.2	925	194	34	29214	413979	<2	34
17L3Sbulk	Pulp	N/A	N/A	N/A	N/A	601	44	1344	10	<2	<0.2	6010	182	27	22591	456505	<2	25
17L4S	Pulp	N/A	N/A	N/A	N/A	605	54	1258	11	<2	<0.2	1089	182	32	37195	400401	<2	15
17L5S	Pulp	N/A	N/A	N/A	N/A	558	47	1242	11	<2	<0.2	883	148	31	39271	401229	<2	12
17L6S	Pulp	N/A	N/A	N/A	N/A	551	47	1221	11	<2	<0.2	863	179	30	38811	402601	<2	15
17L6Sbulk	Pulp	26.31	19.02	6.5	0.82	520	51	1213	10	<2	<0.2	8131	174	31	41958	365752	<2	14
Minimum detection		0.01	0.01	0.01	0.01	100	5	10000	2	2	0.2	100	1	1	1	100	2	2
Maximum detection		100	100	100	100	50000	2000	10000	10000	2000	ICP	100000	10000	10000	10000	50000	10000	10000
Method		AsyWet	AsyWet	AsyWet	AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Sample Name	Sample Type	Mg ppm	Mn ppm	Hg ppm	Mo ppm	Ni ppm	P ppm	K ppm	Sc ppm	Ag ppm	Na ppm	Sr ppm	Ti ppm	Ti ppm	W ppm	V ppm	Zn ppm	Zr ppm
17K1S	Pulp	278	50	<3	2722	9	<100	150	<1	64.4	132	1	<100	<100	<5	12	5384	6
17K2S	Pulp	220	41	<3	1978	9	<100	<100	<1	79.2	122	<1	<10	<10	<5	13	6937	6
17K3S	Pulp	232	39	<3	1764	39	<100	171	<1	73.4	148	1	<10	106	<5	13	4865	6
17K4S	Pulp	192	33	<3	1985	27	<100	196	<1	73	176	1	<10	<100	<5	12	5244	6
17K5S	Pulp	204	34	<3	2806	31	<100	<100	<1	70.1	107	1	<10	111	<5	11	4912	5
17K6S	Pulp	239	33	<3	1835	15	<100	134	<1	67.7	116	1	<10	113	<5	12	4752	6
17K6Sbulk	Pulp	228	33	<3	2034	20	<100	141	<1	75.5	104	1	<10	106	<5	13	4835	5
17L1S	Pulp	287	59	<3	2455	34	<100	351	<1	9.4	169	2	<10	<100	<5	28	1280	10
17L2S	Pulp	205	28	<3	2614	<1	<100	163	<1	9.9	119	<1	<10	<100	<5	23	340	9
17L3S	Pulp	138	16	<3	3245	13	<100	128	<1	11.6	161	1	<10	<100	<5	23	331	10
17L3Sbulk	Pulp	161	17	<3	3049	1	<100	128	<1	9.8	147	3	<10	<100	<5	22	274	8
17L4S	Pulp	182	19	<3	2496	11	<100	156	<1	12.8	114	1	<10	<100	7	24	334	9
17L5S	Pulp	177	14	<3	2335	<1	<100	192	<1	12.9	122	1	<10	<100	<5	22	332	9
17L6S	Pulp	199	16	<3	1996	13	<100	171	<1	13	<100	1	<10	<100	<5	24	271	9
17L6Sbulk	Pulp	153	14	<3	3045	27	<100	132	<1	15	107	4	<10	<100	8	23	304	9
Minimum detection		100	1	3	1	1	50000	10000	1	0.1	100	1	10	100	5	1	1	1
Maximum detection		100000	10000	10000	1000	10000	ICP	100000	10000	100	100000	10000	10000	100000	10000	10000	10000	10000
Method		ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate#: 0311562
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 18
 Date In: Sep 22, 2003
 Date Out: Sep 24, 2003

Sample Name	Sample Type	F.A H2SO4 G/L	F.A. HCl G/L	Cl- mg/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L
17F	Solution	N/A	N/A	N/A	5.5	0.1	<0.2	<0.01	0.1	<0.01	557.2	0.15	0.06	474.35	298.75	<0.05	<0.05
17Fud	Solution	N/A	<0.01	N/A	20.1	<0.1	<0.2	0.39	<0.1	<0.01	44729.5	7.94	1.75	45961.02	29164.06	<0.05	1.55
17K1	Solution	N/A	N/A	N/A	6.4	<0.1	<0.2	<0.01	0.6	<0.01	547.8	0.43	0.09	606.54	424.63	0.05	4.86
17K2	Solution	N/A	N/A	N/A	7.8	<0.1	<0.2	<0.01	1.2	0.1	560.9	0.6	0.19	1074.18	159.47	0.09	11.84
17K3	Solution	N/A	N/A	N/A	6.8	<0.1	<0.2	0.03	1.3	0.04	574.4	0.39	0.09	912.73	259.48	<0.05	6.26
17K4	Solution	N/A	N/A	N/A	7.3	<0.1	<0.2	0.03	0.5	0.06	569.7	0.42	0.12	972.57	202.93	<0.05	7.44
17K5	Solution	N/A	N/A	N/A	6.9	<0.1	<0.2	0.01	0.5	0.05	576.2	0.39	0.15	954.56	244.36	0.06	6.59
17K6	Solution	N/A	N/A	N/A	6.6	<0.1	<0.2	0.01	1	0.05	593.7	0.45	0.14	939.07	261.81	<0.05	6.25
17K6ud	Solution	<0.01	N/A	N/A	142.2	<0.1	2.5	0.31	<0.1	1.83	47375.5	26.29	6.35	91884.26	25655.4	0.09	533.48
17L1	Solution	N/A	N/A	N/A	5.8	0.2	<0.2	0.03	0.5	0.05	602	0.27	0.14	985.84	1.06	0.09	3.94
17L2	Solution	N/A	N/A	N/A	5.8	0.1	<0.2	0.02	0.4	<0.01	580.6	0.02	0.07	716.23	107.49	0.06	0.7
17L3	Solution	N/A	N/A	N/A	5.8	<0.1	<0.2	0.02	0.8	0.03	598.5	<0.01	0.09	885.45	55.21	<0.05	1.9
17L4	Solution	N/A	N/A	N/A	5.3	<0.1	<0.2	0.02	0.9	<0.01	598.8	0.04	0.07	790.94	90.02	<0.05	0.94
17L5	Solution	N/A	N/A	N/A	5.4	<0.1	<0.2	0.02	0.2	0.01	594.8	0.04	0.07	767.51	96.99	<0.05	0.94
17L6	Solution	N/A	N/A	N/A	5.3	<0.1	<0.2	0.04	<0.1	<0.01	623	0.01	0.1	793.33	113.42	<0.05	1.04
17WW	Solution	N/A	N/A	N/A	21.1	<0.1	<0.2	0.09	<0.1	0.17	8135.3	8.38	0.81	9416.49	1063.28	0.06	25.26
17A	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
17B	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection		0.01	0.01	0.5	0.2	0.1	0.2	0.01	0.1	0.01	0.1	0.01	0.01	0.01	0.03	0.05	0.05
Maximum detection		1000	1000	1000	9999	9999	9999	999	9999	999	9999	9999	9999	9999	9999	999	9999
Method		AsyWet	AsyWet	CH-SE	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Sample Name	Sample Type	Mg mg/L	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L
17F	Solution	0.5	0.94	<0.05	0.04	0.06	<0.1	10	0.02	<0.02	50	0.15	<0.2	<0.1	<0.1	0.03	0.48	0.02
17Fud	Solution	2.3	57.68	<0.05	1.18	7.47	<0.1	130	0.23	<0.02	3097	12.68	<0.2	0.1	<0.1	1.46	<0.01	0.52
17K1	Solution	0.7	1.16	<0.05	0.07	0.25	<0.1	12	<0.01	0.14	52	0.15	<0.2	<0.1	<0.1	<0.01	14.13	<0.01
17K2	Solution	1.5	1.53	<0.05	0.06	0.69	<0.1	13	0.01	0.52	57	0.12	<0.2	<0.1	<0.1	<0.01	39.96	<0.01
17K3	Solution	0.7	1.37	<0.05	0.06	0.32	<0.1	6	0.01	0.26	54	0.15	<0.2	<0.1	<0.1	<0.01	24.85	<0.01
17K4	Solution	1.1	1.44	<0.05	0.1	0.51	<0.1	8	<0.01	0.35	55	0.15	<0.2	<0.1	<0.1	<0.01	28.73	<0.01
17K5	Solution	1.2	1.41	<0.05	0.06	0.44	<0.1	12	<0.01	0.29	54	0.15	<0.2	<0.1	<0.1	<0.01	25.22	<0.01
17K6	Solution	1	1.44	<0.05	0.07	0.5	<0.1	9	<0.01	0.31	53	0.15	<0.2	<0.1	<0.1	<0.01	25.67	<0.01
17K6ud	Solution	34.9	114.85	<0.05	4.94	28.31	<0.1	167	0.56	21.45	3574	11.7	<0.2	3.1	<0.1	1.91	2492.97	0.4
17L1	Solution	0.7	1.27	<0.05	<0.02	0.24	<0.1	14	0.01	0.27	55	0.15	<0.2	<0.1	<0.1	0.04	20.26	0.02
17L2	Solution	0.6	1.05	<0.05	<0.02	0.12	<0.1	9	<0.01	0.07	54	0.15	<0.2	<0.1	<0.1	<0.01	7.57	0.01
17L3	Solution	0.6	1.16	<0.05	<0.02	0.16	<0.1	9	0.01	0.11	58	0.15	<0.2	<0.1	<0.1	<0.01	13.2	<0.01
17L4	Solution	0.5	1.11	<0.05	<0.02	0.12	<0.1	10	<0.01	0.1	54	0.16	<0.2	<0.1	<0.1	0.05	8.85	0.03
17L5	Solution	0.4	1.11	<0.05	<0.02	0.15	<0.1	7	0.03	0.04	55	0.15	<0.2	<0.1	<0.1	<0.01	8.41	<0.01
17L6	Solution	0.8	1.15	<0.05	<0.02	0.18	<0.1	10	<0.01	0.08	55	0.18	<0.2	<0.1	<0.1	<0.01	7.95	<0.01
17WW	Solution	3	11.43	<0.05	0.88	4.47	<0.1	23	0.08	1.53	414	4.11	<0.2	0.4	<0.1	0.09	133.99	0.03
17A	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
17B	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection		0.1	0.01	0.05	0.02	0.02	0.1	2	0.01	0.02	1	0.01	0.2	0.1	0.01	0.01	0.01	0.01
Maximum detection		9999	999	9999	9999	9999	9999	9999	100	999	9999	999	999	999	9999	999	9999	999
Method		ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Certificate# 0311616
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 17
 Date In: Sep 29, 2003
 Date Out: Oct 05, 2003

Sample Name	SampleType	S(tot) %	S(ele) %	S(-2) %	S(GO4) %	Al ppm	Sb ppm	As ppm	Ba ppm	Bi ppm	Cd ppm	Ca ppm	Cr ppm	Co ppm	Cu ppm	Fe ppm	La ppm	Pb ppm
18FSa	Pulp	N/A	N/A	N/A	N/A	1683	25	582	14	<2	20.7	388	1189	95	268029	267244	<2	465
18FSb	Pulp	N/A	N/A	N/A	N/A	1831	29	573	14	<2	19.4	411	1207	95	267135	269410	<2	472
18A1S	Pulp	N/A	N/A	N/A	N/A	2279	26	1118	14	<2	-0.2	171	57	144	6666	290321	<2	44
18A2S	Pulp	N/A	N/A	N/A	N/A	3272	22	788	22	<2	-0.2	119	60	114	141028	301369	<2	34
18A3S	Pulp	N/A	N/A	N/A	N/A	833	17	1075	31	<2	-0.2	<100	26	141	8578	285812	<2	26
18A4S	Pulp	N/A	N/A	N/A	N/A	4107	64	1075	16	<2	-0.2	221	52	131	53371	287111	<2	28
18A5S	Pulp	N/A	N/A	N/A	N/A	6004	28	1122	16	<2	-0.2	683	69	138	21381	280937	2	58
18A6S	Pulp	N/A	N/A	N/A	N/A	6388	30	1136	16	<2	-0.2	501	119	135	20829	284916	4	60
18A7S	Pulp	N/A	N/A	N/A	N/A	5863	28	1110	12	<2	-0.2	184	83	137	20833	280188	4	59
18A8S	Pulp	N/A	N/A	N/A	N/A	4973	30	1063	14	<2	-0.2	1389	119	137	20833	280188	4	59
18B1S	Pulp	N/A	N/A	N/A	N/A	6273	25	995	16	<2	-0.2	1389	119	137	20833	280188	4	59
18B2S	Pulp	N/A	N/A	N/A	N/A	6273	25	995	16	<2	-0.2	1389	119	137	20833	280188	4	59
18B3S	Pulp	N/A	N/A	N/A	N/A	6490	25	995	16	<2	-0.2	1389	119	137	20833	280188	4	59
18B4S	Pulp	N/A	N/A	N/A	N/A	6490	25	995	16	<2	-0.2	1389	119	137	20833	280188	4	59
18B5S	Pulp	N/A	N/A	N/A	N/A	6490	25	995	16	<2	-0.2	1389	119	137	20833	280188	4	59
18B6S	Pulp	N/A	N/A	N/A	N/A	6490	25	995	16	<2	-0.2	1389	119	137	20833	280188	4	59
18B6Sbulk	Pulp	N/A	N/A	N/A	N/A	4479	26	783	13	<2	-0.2	244	140	135	11020	274124	3	53
18B6Sbulk	Pulp	N/A	N/A	N/A	N/A	4988	27	735	13	<2	-0.2	161	143	139	10822	275373	2	51
Minimum detection		0.01	0.01	0.01	0.01	100	5	10000	2	2	0.2	100	1	1	1	100	2	2
Maximum detection		100	100	100	100	50000	2000	10000	10000	2000	2000	10000	10000	10000	10000	50000	10000	10000
Method		AsyWet	AsyWet	AsyWet	AsyWet	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP	ICP

Certificate# 0311768
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 5
 Date In: Oct 24, 2003
 Date Out: Oct 29, 2003

Sample Name	SampleType	S(tot) %	SO4 G/L
18FSa (Rosario fine grind)	Pulp	35.62	N/A
18FSb (Rosario fine grind)	Pulp	35.43	N/A
13PLS5	Solution	N/A	0.55
15PLS8	Solution	N/A	0.38
17PLS8	Solution	N/A	0.39
Minimum detection		0.01	0.01
Maximum detection		100	1000
Method		AsyWet	AsyWet

Certificate# 031615
 Client: Metals & Materials Eng UBC
 Project: BD28F06 EFDJ 713000
 No. of Samples: 18
 Date In: Sep 29, 2003
 Date Out: Oct 06, 2003

Sample Name	Sample Type	F.A.H2SO4 G/L	F.A.HCl G/L	Cl- mg/L	Al mg/L	Sb mg/L	As mg/L	Ba mg/L	Bi mg/L	Cd mg/L	Ca mg/L	Cr mg/L	Co mg/L	Cu mg/L	Fe mg/L	La mg/L	Pb mg/L
18F	Solution	N/A	N/A	N/A	2.8	<0.1	<0.2	0.01	<0.1	<0.01	267.9	0.52	0.08	511.89	820.49	0.06	<0.05
18Fud	Solution	N/A	2.35	N/A	25.3	<0.1	<0.2	0.1	<0.1	0.37	26397	32.24	5.35	49960.37	81995.6	<0.05	5.69
18A1	Solution	N/A	N/A	N/A	3.2	<0.1	<0.2	0.03	0.2	0.03	263.6	2	0.08	1067.96	1045.41	<0.05	0.61
18A2	Solution	N/A	N/A	N/A	3.7	<0.1	<0.2	0.09	0.3	0.16	243.4	3.96	0.08	905.25	1020.87	<0.05	1.32
18A3	Solution	N/A	N/A	N/A	4.2	<0.1	<0.2	0.06	<0.1	0.04	252.5	2.69	0.09	898.13	1047.09	<0.05	0.89
18A4	Solution	N/A	N/A	N/A	3.2	<0.1	<0.2	0.06	0.4	0.07	245.3	2.26	0.1	882.32	1009.32	<0.05	0.64
18A5	Solution	N/A	N/A	N/A	3.4	<0.1	<0.2	0.06	0.9	0.03	256.8	2.26	0.09	911.22	1013.47	<0.05	0.33
18A6	Solution	N/A	N/A	N/A	76.2	0.7	5.3	2.69	0.4	0.03	251.6	2.34	0.09	9232.63	99622.1	<0.05	0.62
18A6ud	Solution	<0.01	N/A	N/A	3.9	0.2	<0.2	0.06	0.6	0.03	264.5	2.06	0.11	871.97	1002.2	<0.05	45.93
18B1	Solution	N/A	N/A	N/A	3.2	<0.1	<0.2	0.03	0.2	<0.01	269.1	0.78	0.09	555.91	867.37	<0.05	0.42
18B2	Solution	N/A	N/A	N/A	2.8	<0.1	<0.2	0.05	0.4	<0.01	259.8	1.03	0.07	882.92	908.24	<0.05	<0.05
18B3	Solution	N/A	N/A	N/A	3	<0.1	<0.2	0.01	0.4	<0.01	259.5	0.76	0.07	554.61	835.36	<0.05	<0.05
18B4	Solution	N/A	N/A	N/A	3	<0.1	<0.2	0.01	0.5	<0.01	283.4	0.85	0.06	613.81	914.48	<0.05	<0.05
18B5	Solution	N/A	N/A	N/A	2.8	<0.1	<0.2	0.01	0.2	<0.01	261.1	0.73	0.05	551.33	849.07	<0.05	<0.05
18B6	Solution	N/A	N/A	N/A	9.9	<0.1	<0.2	0.14	2.4	<0.01	2351.3	15.68	0.46	2869.27	3921.95	<0.05	0.56
18BW	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
18A	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
18B	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection		0.01	0.01	0.5	0.2	0.1	0.2	0.01	0.1	0.01	9999	0.01	0.01	0.01	0.03	0.05	0.05
Maximum detection		1000	1000	1000	9999	9999	9999	999	9999	999	9999	9999	9999	9999	9999	999	9999
Method		AsyWet	AsyWet	CHSE	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Sample Name	Sample Type	Mg mg/L	Mn mg/L	Hg mg/L	Mo mg/L	Ni mg/L	P mg/L	K mg/L	Sc mg/L	Ag mg/L	Na mg/L	Sr mg/L	Ti mg/L	Ti mg/L	W mg/L	V mg/L	Zn mg/L	Zr mg/L
18F	Solution	0.4	3.8	<0.05	0.09	0.33	<0.1	10	<0.01	0.04	24	0.08	<0.2	<0.1	<0.1	<0.01	0.64	<0.01
18Fud	Solution	7.6	356.26	<0.05	2.73	21.92	<0.1	81	0.14	<0.02	1680	6.91	<0.2	1.7	<0.1	1.25	64.35	2.06
18A1	Solution	0.6	4.19	<0.05	0.12	1.14	<0.1	7	<0.01	0.05	23	0.09	<0.2	<0.1	0.2	0.02	13.47	<0.01
18A2	Solution	1	4.62	<0.05	0.17	2.24	<0.1	<2	<0.01	0.12	23	0.08	<0.2	<0.1	<0.1	<0.01	27.5	<0.01
18A3	Solution	1.1	4.23	<0.05	0.17	1.26	<0.1	9	<0.01	0.09	26	0.09	<0.2	<0.1	0.3	0.04	15.38	0.03
18A4	Solution	0.6	4.29	<0.05	0.12	1.49	<0.1	8	<0.01	0.08	26	0.09	<0.2	<0.1	<0.1	<0.01	18.38	<0.01
18A5	Solution	0.8	4.26	<0.05	0.13	1.39	<0.1	3	<0.01	0.07	24	0.09	<0.2	<0.1	0.1	<0.01	14.67	<0.01
18A6	Solution	38.4	4.23	<0.05	0.13	1.37	<0.1	4	<0.01	0.04	24	0.09	<0.2	<0.1	0.2	<0.01	14.83	<0.01
18A6ud	Solution	0.6	396.89	<0.05	6.73	74.15	<0.1	100	0.36	6.73	1698	6.03	<0.2	3	<0.1	1.43	1470.23	2.48
18B1	Solution	0.2	4.22	<0.05	0.16	1.04	<0.1	7	<0.01	0.07	27	0.08	<0.2	<0.1	0.3	0.05	13.42	0.03
18B2	Solution	0.2	3.97	<0.05	0.07	0.54	<0.1	4	<0.01	<0.02	27	0.08	<0.2	<0.1	0.2	0.02	2.88	<0.01
18B3	Solution	0.5	3.91	<0.05	0.07	0.56	<0.1	4	<0.01	0.03	24	0.08	<0.2	<0.1	<0.1	<0.01	5.25	<0.01
18B4	Solution	0.2	3.8	<0.05	0.03	0.38	<0.1	<2	<0.01	<0.02	26	0.08	<0.2	<0.1	0.3	<0.01	2.8	<0.01
18B5	Solution	<0.1	4.07	<0.05	0.07	0.47	<0.1	<2	<0.01	<0.02	26	0.09	<0.2	<0.1	<0.1	<0.01	3.38	<0.01
18B6	Solution	0.2	3.85	<0.05	0.08	0.49	<0.1	<2	<0.01	<0.02	25	0.06	<0.2	<0.1	0.2	<0.01	3	<0.01
18BW	Solution	1.9	16.67	<0.05	1.15	8.79	<0.1	8	0.01	0.14	79	1.4	<0.2	0.3	<0.1	0.1	34.44	0.02
18A	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
18B	Solution	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
Minimum detection		0.1	0.01	0.05	0.02	0.02	0.1	2	0.01	0.02	1	0.01	0.2	0.1	0.1	0.01	0.01	0.01
Maximum detection		9999	9999	9999	9999	9999	9999	9999	100	999	9999	999	999	999	9999	999	9999	999
Method		ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O	ICPH2O

Appendix 2 Certificates of Analysis (ChemMet)

Appendix 3 Certificates of Analysis (Malvern Mastersizer)

MASTERSIZER

Result Analysis Report

Sample Name:
Ant - Whole - Average

Sample Source & type:
Factory

Sample bulk lot ref:

SOP Name:

Measured by:
contract

Result Source:
Averaged

Measured:

Monday, October 06, 2003 11:01:08 AM

Analysed:

Monday, October 06, 2003 11:01:09 AM

Particle Name:

Chalcopyrite

Particle RI:

1.450

Dispersant Name:

Water

Accessory Name:

Hydro 2000S (A)

Absorption:

0

Dispersant RI:

1.330

Analysis model:

General purpose

Size range:

0.020 to 2000.000 μ m

Weighted Residual:

0.956 %

Sensitivity:

Normal

Obscuration:

18.04 %

Result Emulation:

Off

Concentration:

0.0629 %Vol

Span :

2.267

Uniformity:

0.72

Result units:

Volume

Specific Surface Area:

0.246 m^2/g

Surface Weighted Mean D[3,2]:

24.418 μ m

Vol. Weighted Mean D[4,3]:

52.146 μ m

d(0.1): 10.613 μ m

d(0.5): 41.971 μ m

d(0.9): 105.757 μ m

Size (μ m)	Volume In %	Size (μ m)	Volume In %	Size (μ m)	Volume In %	Size (μ m)	Volume In %	Size (μ m)	Volume In %	Size (μ m)	Volume In %
0.010	0.00	0.071	0.00	0.501	0.00	3.548	0.38	25.119	0.94	177.526	0.57
0.011	0.00	0.079	0.00	0.562	0.00	3.981	0.51	28.184	4.27	199.526	0.32
0.013	0.00	0.089	0.00	0.631	0.00	4.467	0.65	31.523	4.62	223.872	0.17
0.014	0.00	0.100	0.00	0.708	0.00	5.012	0.79	35.481	4.95	251.189	0.08
0.016	0.00	0.112	0.00	0.794	0.00	5.623	0.94	39.811	5.24	281.838	0.05
0.018	0.00	0.126	0.00	0.891	0.00	6.310	1.09	44.958	5.45	316.228	0.04
0.020	0.00	0.141	0.00	1.000	0.00	7.079	1.25	50.119	5.55	354.813	0.04
0.022	0.00	0.158	0.00	1.122	0.00	7.943	1.42	56.234	5.52	398.107	0.03
0.025	0.00	0.178	0.00	1.259	0.00	8.913	1.59	63.096	5.35	446.684	0.03
0.028	0.00	0.200	0.00	1.413	0.00	10.000	1.78	70.795	5.02	501.187	0.00
0.032	0.00	0.224	0.00	1.595	0.00	11.220	1.96	79.433	4.56	562.341	0.00
0.035	0.00	0.251	0.00	1.778	0.00	12.589	2.19	89.125	3.96	630.957	0.00
0.040	0.00	0.282	0.00	1.995	0.00	14.125	2.42	100.000	3.33	707.946	0.00
0.045	0.00	0.316	0.00	2.239	0.00	15.849	2.67	112.202	2.65	794.328	0.00
0.050	0.00	0.355	0.00	2.512	0.07	17.783	2.94	125.893	2.01	891.251	0.00
0.056	0.00	0.399	0.00	2.818	0.14	19.953	3.24	141.264	1.42	1000.000	0.00
0.063	0.00	0.447	0.00	3.162	0.26	22.387	3.56	158.488	0.94		
0.071	0.00	0.501	0.00	3.548		25.119		177.526

MASTERSIZER

Result Analysis Report

Sample Name:
Ant - Fine Grind - Average

Sample Source & type:
Factory

Sample bulk lot ref:

SOP Name:

Measured by:
contract

Result Source:
Averaged

Measured:

Monday, October 06, 2003 10:53:44 AM

Analysed:

Monday, October 06, 2003 10:53:46 AM

Particle Name:
Chalcopryite

Particle RI:
1.450

Dispersant Name:
Water

Accessory Name:
Hydro 2000S (A)

Absorption:
0

Dispersant RI:
1.330

Analysis model:
General purpose

Size range:
0.020 to 2000.000 μ m

Weighted Residual:
1.495 %

Sensitivity:
Normal

Obscuration:

16.22 %

Result Emulation:
Off

Concentration:
0.0279 %Vol

Span :

2.059

Uniformity:
0.642

Result units:
Volume

Specific Surface Area:
0.476 m^2/g

Surface Weighted Mean D[3,2]:
12.597 μ m

Vol. Weighted Mean D[4,3]:
20.816 μ m

d(0.1): 6.136 μ m

d(0.5): 16.861 μ m

d(0.9): 40.855 μ m

Ant - Fine Grind - Average, Monday, October 06, 2003 10:53:44 AM

Size (μ m)	Volume In %	Size (μ m)	Volume In %	Size (μ m)	Volume In %	Size (μ m)	Volume In %	Size (μ m)	Volume In %	Size (μ m)	Volume In %
0.010	0.00	0.071	0.00	0.501	0.00	3.548	1.09	25.119	5.44	177.828	0.00
0.011	0.00	0.079	0.00	0.562	0.00	3.981	1.42	28.184	4.95	199.526	0.00
0.013	0.00	0.089	0.00	0.631	0.00	4.467	1.78	31.623	4.37	223.872	0.00
0.014	0.00	0.100	0.00	0.706	0.00	5.012	2.16	35.481	3.73	251.189	0.00
0.016	0.00	0.112	0.00	0.794	0.00	5.623	2.56	39.811	3.07	281.838	0.00
0.018	0.00	0.126	0.00	0.891	0.00	6.310	2.98	44.696	2.44	316.228	0.00
0.020	0.00	0.141	0.00	1.000	0.00	7.079	3.42	50.119	1.85	354.813	0.00
0.022	0.00	0.158	0.00	1.122	0.00	7.943	3.88	56.234	1.35	398.107	0.00
0.025	0.00	0.178	0.00	1.259	0.00	8.913	4.34	63.096	0.92	446.684	0.00
0.028	0.00	0.200	0.00	1.413	0.00	10.000	4.80	70.795	0.59	501.187	0.00
0.032	0.00	0.224	0.00	1.585	0.00	11.220	5.22	79.433	0.38	562.341	0.00
0.035	0.00	0.251	0.00	1.778	0.00	12.599	5.69	89.125	0.14	630.957	0.00
0.040	0.00	0.282	0.00	1.995	0.01	14.125	5.88	100.000	0.01	707.946	0.00
0.045	0.00	0.316	0.00	2.239	0.10	15.849	6.05	112.202	0.00	794.328	0.00
0.050	0.00	0.355	0.00	2.512	0.26	17.783	6.12	125.893	0.00	891.251	0.00
0.056	0.00	0.398	0.00	2.818	0.52	19.953	6.03	141.254	0.00	1000.000	0.00
0.063	0.00	0.447	0.00	3.162	0.77	22.387	5.80	158.489	0.00		
0.071	0.00	0.501	0.00	3.548		25.119		177.828	0.00

MASTERSIZER

Result Analysis Report

Sample Name:
Ros - Fine Grind - Average

Sample Source & type:
Factory

Sample bulk lot ref:

SOP Name:

Measured by:
contract

Result Source:
Averaged

Measured:
Monday, October 06, 2003 10:40:43 AM

Analysed:
Monday, October 06, 2003 10:40:44 AM

Particle Name:
Chalcopryite

Particle RI:
1.450

Dispersant Name:
Water

Accessory Name:
Hydro 2000S (A)

Absorption:
0

Dispersant RI:
1.330

Analysis model:
General purpose

Size range:
0.020 to 2000.000 um

Weighted Residual:
1.394 %

Sensitivity:
Normal

Obscuration:
17.01 %

Result Emulation:
Off

Concentration:
0.0283 %Vol

Span :
1.925

Uniformity:
0.6

Result units:
Volume

Specific Surface Area:
0.492 m²/g

Surface Weighted Mean D[3,2]:
12.206 um

Vol. Weighted Mean D[4,3]:
19.465 um

d(0.1): 6.041 um

d(0.5): 16.243 um

d(0.9): 37.306 um

Size (µm)	Volume In %	Size (µm)	Volume In %	Size (µm)	Volume In %	Size (µm)	Volume In %	Size (µm)	Volume In %	Size (µm)	Volume In %
0.010	0.00	0.071	0.00	0.501	0.00	3.548	1.13	25.119	5.50	177.828	0.00
0.011	0.00	0.079	0.00	0.552	0.00	3.961	1.45	28.184	4.88	199.526	0.00
0.013	0.00	0.089	0.00	0.631	0.00	4.467	1.79	31.623	4.19	223.872	0.00
0.014	0.00	0.100	0.00	0.708	0.00	5.012	2.16	35.481	3.45	251.189	0.00
0.016	0.00	0.112	0.00	0.794	0.00	5.623	2.56	39.811	2.71	281.838	0.00
0.018	0.00	0.126	0.00	0.891	0.00	6.310	2.99	44.669	2.04	316.228	0.00
0.020	0.00	0.141	0.00	1.000	0.00	7.079	3.47	50.119	1.45	354.813	0.00
0.022	0.00	0.158	0.00	1.122	0.00	7.943	3.97	56.234	0.96	398.107	0.00
0.025	0.00	0.176	0.00	1.269	0.00	8.913	4.49	63.095	0.59	446.684	0.00
0.028	0.00	0.200	0.00	1.413	0.00	10.000	5.02	70.795	0.35	501.187	0.00
0.032	0.00	0.224	0.00	1.585	0.00	11.220	5.50	79.433	0.05	562.341	0.00
0.035	0.00	0.251	0.00	1.778	0.00	12.589	5.93	89.125	0.00	630.957	0.00
0.040	0.00	0.282	0.00	1.995	0.01	14.125	6.25	100.000	0.00	707.946	0.00
0.045	0.00	0.316	0.00	2.238	0.15	15.849	6.44	112.202	0.00	794.328	0.00
0.050	0.00	0.355	0.00	2.512	0.35	17.783	6.46	125.893	0.00	891.251	0.00
0.056	0.00	0.398	0.00	2.818	0.58	19.853	6.31	141.254	0.00	1000.000	0.00
0.063	0.00	0.447	0.00	3.162	0.84	22.387	5.98	158.489	0.00		
0.071	0.00	0.501	0.00	3.548	0.84	25.119	5.98	177.828	0.00		

Appendix 4 XRD Spectra

Antamina XRD Profile

Rosario XRD Profile

Appendix 5 Methods

A. Free Acid Titration

B. Cerium Titration

C. Light's Solution Preparation

Appendix 5A. Free Acid Titration (with oxalate masking)

The purpose of this titration was to determine the free acid concentration of the feed liquor. Potassium oxalate ($K_2C_2O_4 \cdot H_2O$) was used to complex metal ions that would normally contribute protons (H^+), via complexation with hydroxyl ions (OH^-) in water, e.g. $Cu^{2+} + 4(OH^-) \rightarrow Cu(OH)_4^{2-}$.

Method used

1. In a beaker containing ~65mL DI water, add a 1 or 2mL aliquot of the feed liquor.
2. Add 25mL Potassium Oxalate solution (280g $K_{ox} \cdot H_2O$ in 1L)
3. Measure the pH of the solution before and after addition of $K(ox)$.
4. Titrate solution with 0.1M NaOH (accurately determined) and record pH changes with volume added.
5. Plot pH vs volume NaOH added. The mid-point of the steepest part of the curve indicates the volume required to neutralize the free acid. This volume can be used to determine moles of free acid in the aliquot used, as shown in the following reaction.

The results of titrations performed at UBC, shown in the following table, indicate that for all but H3 and H4 the results were in general agreement. There is still some slight variation from the IPL data but as the concentration of the feed liquor is extremely high in copper, iron and calcium chloride this may impact on the method and output reproducibility. Example titration curves are provided for experiment H7.

Table 34 Comparing IPL free acid results with test titration value

Expt	IPL result (g/L HCl)	UBC titrations - averages given (g/L HCl)
H1	5.74	Not performed
H2	5.28	Not performed
H3	12.97	4.06
H4	12.53	4.06
H5	2.71	3.04
H6	1.94	2.19
H7	3.01	2.96
H8	3.69	3.14
H9	2.35	2.55
G1	0.72	Not performed
G2	10.02	Not performed
G3	<0.01	<0.1

Example free acid titration curves for experiment H7 (1mL and 2mL aliquots)

Aliquot = 1mL

Vol (mL)	pH
7.6	6.73
7.8	6.85
8.0	6.97
8.2	7.21
8.5	7.67
8.7	7.92
9.0	8.13

Calculation:

Midpoint of steepest section (between points in bold):

Vol = 8.35mL

Titration Vol = 8.35-7.6 = 0.75mL

Mol NaOH = Mol HCl = 0.1M x 0.75mL = 0.075mmol

[HCl] = 0.075mmol/0.001L = 0.075M = 2.73g/L

Aliquot = 2mL

Vol (mL)	pH
9.5	6.21
9.7	6.26
9.9	6.35
10.2	6.46
10.5	6.58
10.7	6.75
11.1	7.05
11.4	7.44
11.7	7.69
11.9	7.80
12.2	7.94
12.5	8.00
12.7	8.05
13.0	8.12
13.6	8.21
14.2	8.27
15.3	8.36

Calculation:

Midpoint of steepest section (between points in bold):

Vol = 11.25mL

Titration Vol = 11.25-9.5 = 1.75mL

Mol NaOH = Mol HCl = 0.1M x 1.75mL = 0.175mmol

[HCl] = 0.175mmol/0.002L = 0.175M = 3.19g/L

Average of two free acid titrations = (2.73 + 3.19)/2 = 2.96 g/L HCl

Appendix 5B Cerium Titration (for reduced species determination)

This titration was used to determine reduced species in the goethite feed liquor and in the final LS1 (PLS) and LS2 exit liquors of selected experiments. Certified acidic cerium (Ce^{4+}) sulfate solution (0.1M) was used as the titrant, and as the $\text{Ce}^{4+}/\text{Ce}^{3+}$ redox potential is significantly high (at +1.61V) it has the ability to oxidize many reduced metals ions, e.g. Cu^+ or Fe^{2+} , via the following reactions.

Method used

1. A 0.5, 1 or 2mL aliquot was added to a beaker containing 80-100mL DI water.
2. A few drops of HCl were then added, if required, and a few drops of Ferroin indicator.
3. The change in redox potential was then recorded as 0.1M Ce^{4+} titrant was introduced into the solution.
4. The endpoint was detected by a change in color of the indicator as well as a sharp rise in the redox potential, i.e. $>800\text{mV}_{\text{Ag}/\text{AgCl}}$.
5. The concentration of total reduced species was determined by calculating the moles of Ce^{4+} reacted using the titration volume, and then dividing by the aliquot of test solution added.

Example cerium titration curve for experiment H7 – Final PLS liquor

Aliquot = 0.5mL

Vol (mL)	E (mV _{Ag/AgCl})
2.0	162
2.5	176
2.7	181
3.2	190
3.5	199
3.9	209
4.3	227
4.5	248
4.8	320
5.4	389
5.6	405
6.2	415
6.5	421
6.8	426
7.1	430
7.4	434
7.7	438
8.2	443
9.0	450
9.3	453
10.1	460
11.1	469
12.3	481
12.6	486
13.1	493
13.6	502
14.0	512
14.4	523
14.9	553
15.0	endpoint (>800mV)

Calculation:

Titration Vol = 15.0-12.0mL = 13.0mL

Mol NaOH = Mol HCl = 0.1M x 13.0mL = 1.30mmol

[HCl] = 1.30mmol/0.0005L = 2.60M Total Reduced Species

Appendix 5C. Light's Solution Preparation

Redox probes cannot be recalibrated and thus performance must be monitored throughout the duration of its lifespan. A solution of known potential, such as Light's solution, can be used to check probe performance.

Dissolve 39.21g of ferrous ammonium sulfate-6-hydrate and 48.22g of ferric ammonium sulfate-12-hydrate in 800mL of DI water. Then add 56.2ml of concentrated sulfuric acid and adjust volume to 1 liter with DI water. This solution has a pH near 0. It is a corrosive strong acid solution and should be handled with care and kept stored away from light.

For a stable reading, the redox electrode should be placed into stirred light's solution for at least 30 minutes for equilibrium to be established. The value that should be obtained for Ag/AgCl (sat.KCl) probes is +476mV and Calomel (sat.KCl) probes is +430mV at 25C.

Appendix 6 Experimental Logs

- A. Measurements (Temperature, pH and E)
- B. Samples
- C. Mass and Volume Transfers

Date: Thursday 25 September 2003

Experiment#18 (H9) Continuous 18h Countercurrent Leach, Fine Grind, No Air to LS2, 135g/L, 95C, RT 3h.

ROSARIO Concentrate

Concentrate fine grind filtered, dried and rolled with SS rolling pin.

Leach Solution: 50g/L Cu²⁺, 80g/L Fe³⁺, 110g/L CaCl₂, ~3g/L HCl

RT - C; E(mV/AgAgCl)=

pH =

Light's Soln: Start=

End=

Average=

Time	Leach time	LS1			LS2			Comments
		T (C)	E (mV Ag/AgCl)	pH	T (C)	E (mV Ag/AgCl)	pH	
I.								
	0							
	1.5h							
	2.75h							A110 to LS1 15mL
	3h							
	Bench pH -							
	Transfer time =							
II.								
	0							
	1.5h							
	2.75h							A110 to LS1 15mL
	3h							
	Bench pH -							
	Transfer time =							
III.								
	0							
	1.5h							
	2.75h							A110 to LS1 15mL
	3h							
	Bench pH -							
	Transfer time =							
IV.								
	0							
	1.5h							
	2.75h							A110 to LS1 15mL
	3h							
	Bench pH -							
	Transfer time =							
V.								
	0							
	1.5h							
	2.75h							A110 to LS1 15mL
	3h							
	Bench pH -							
	Transfer time =							
VI.								
	0							
	1.5h							
	3h							
	Bench pH -							

Experiment 18 (H9): Sample and Input/Output Log

Time	Samples	Name (Location)	Weight	Volume	Comments	Assays	Residues Mass in bag (g)
	18Fud (S)				Undiluted	ICP, FA(HCl)	Fine grind Conc=6g
	18F				100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	
	18A1 (S)	LS1		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	
	18B1 (S)	LS2		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	
			18B1 bulk sample	Wet cake =	; W&D =		2-4
Start Leach II:							
	18A2 (S)	LS1		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	2-4
	18B2 (S)	LS2		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	2-4
			18B2 bulk sample	Wet cake =	; W&D =		
Time taken for transfer =							
Start Leach III:							
	18A3 (S)	LS1		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	2-4
	18B3 (S)	LS2		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	2-4
			18B3 bulk sample	Wet cake =	; W&D =	18B3bulk	10
Time taken for transfer =							
Start Leach IV:							
	18A4 (S)	LS1		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	2-4
	18B4 (S)	LS2		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	2-4
			18B4 bulk sample	Wet cake =	; W&D =		
Time taken for transfer =							
Start Leach V:							
	18A5 (S)	LS1		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	2-4
	18B5 (S)	LS2		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	2-4
			18B5 bulk sample	Wet cake =	; W&D =		
Time taken for transfer =							
Start Leach VI:							
	18A6 (S)	LS1		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	2-4
	18B6 (S)	LS2		80mL	100xdil(5mLHCl, 2ml in 200mL DI H2O)	ICP	2-4
			18B6 bulk sample	Wet cake =	; W&D =		
Time taken for transfer =							
Transfer at:							
	LS1 -Pressure Filter PLS =						
	18A6bulk sample	Wet cake =	; W&D =			18B6bulk	2x10

Other samples:

18WW	wash water	undiluted - record volume =	ICP 30
18K6ud	LS1	undiluted	ICP 30, Free Acid(H2SO4)
18A	Feed Liquor	100x dilution in DI H2O ONLY	Total Cl (ISE)
18B	PLS final	1000x dil ONLY DI H2O	Total Cl (ISE)

Start: _____ Page: _____

Feed Liquor = 1L **CuFeS₂ = 135g** **PLS =**

A110 15mL

80mL Sample

Feed Liquor = 1L **CuFeS₂ = 135g**

LS2

80mL Sample

Pressure Filter

LR wet cake = vol. liquor? = washed and dried =

Transfer I.

Volume for LS1 =

LS1 **CuFeS₂ = 135g** **PLS =**

A110 15mL

80mL Sample

Feed Liquor = 1L

LS2

80mL Sample

Pressure Filter

LR wet cake = vol. liquor? = washed and dried =

Transfer II.

Volume for LS1 =

LS1 **CuFeS₂ = 135g** **PLS =**

A110 15mL

80mL Sample

Feed Liquor = 1L

LS2

80mL Sample

Pressure Filter

LR wet cake = vol. liquor? = washed and dried =

Transfer III.

Volume for LS1 =

LS1 **CuFeS₂ = 135g** **PLS =**

A110 15mL

80mL Sample

Feed Liquor = 1L

LS2

80mL Sample

Pressure Filter

LR wet cake = vol. liquor? = washed and dried =

Transfer IV.

Volume for LS1 =

LS1 **CuFeS₂ = 135g** **PLS =**

A110 15mL

80mL Sample

Feed Liquor = 1L

LS2

80mL Sample

Pressure Filter

LR wet cake = vol. liquor? = washed and dried =

Transfer V.

Volume for LS1 =

LS1 **CuFeS₂ = 135g**

80mL Sample

Pressure Filter

LR wet cake = vol. liquor? = washed and dried =

Feed Liquor = 1L

80mL Sample

Pressure Filter

LR wet cake = vol. liquor? = washed and dried =

Appendix 7 Calculations

- A. Copper and iron extraction
- B. Required oxidant concentration for hematite feed liquor
- C. Oxygen addition to LS2
- D. Theoretical reduced species

Appendix 7A. Copper and iron extraction

The extraction of copper and iron from the concentrate was calculated in the following manner.

An example for copper is provided for experiment H5 (Antamina p90=41 μ m, 3h, 95C).

Cu% in feed = 28.8%, Cu% in LS residue = 1.96%

Amount of copper in feed = 135g x 28.8% = 38.88g

Final mass of LS2 residue (80mL slurry sample and bulk pressure filter sample)

= 3.1 + 37.8 = 40.9g

Copper in final LS2 residue = 40.9g x 1.96% = 0.80g

Extraction of Copper = (copper in feed – copper in LS2 residue)/ (copper in feed) x 100%

= (38.88 – 0.80)/38.88 x 100 = 97.9%

This calculation does not take into account the small residue sample taken from LS1, which may decrease the lower extraction values by no more than 1-2%.

Appendix 7B. Required oxidant concentration for hematite feed liquor

Calculation for determining if 70g/L ferric (Fe³⁺) and 40g/L cupric (Cu²⁺) in the feed liquor is sufficient for leaching 100% of CuFeS₂ in the Antamina concentrate feed:

28.8% Cu in 135g feed concentrate = 38.9g Cu = 0.61mol

If all of the copper is contained in CuFeS₂ this implies 0.61mol CuFeS₂.

The ferric and cupric leach reactions are as follows:

If Fe³⁺ = 70g/L = 1.25 mol in 1L, then ferric can leach 1.25/4 = 0.31mol CuFeS₂ and produce 0.31 mol Cu²⁺. If Cu²⁺ is 40g/L (0.63 mol in 1L) and is combined with the 0.31mol Cu²⁺ produced by the ferric leach, this amounts to Cu²⁺ = 0.94mol in 1L. This total Cu²⁺ amount, 0.94mol, has the ability to leach 0.94/3 = 0.31mol CuFeS₂.

The total amount of CuFeS₂ that can be leached by 70g/L Fe³⁺ and 40g/L Cu²⁺ is therefore 0.31 + 0.31 = 0.62mol CuFeS₂, which is 0.01 mol greater than the amount of CuFeS₂ delivered in the Antamina concentrate.

Appendix 7C. Calculation for oxygen addition to LS2 (Goethite model)

Delivery of oxygen to LS2 is required in the goethite model experiments to regenerate cupric and ferric species. The following calculation assisted in determining an appropriate flow rate for air delivery.

Leach time = 2h = 120min

Air = assume 21% oxygen

Oxygen requirement (determined from the flowsheet mass balance)

per 135 g pure chalcopyrite feed = 17.65g = 0.55mol

Moles of air required = 0.55mol x 100/21 = 2.62 mol

If 1 mol gas approximates 24.5L at room temperature (298K),

2.62 mol air = 64.2L

Over two hours the flow rate to deliver a stoichiometric quantity of oxygen =

$64.2\text{L} \times 1000\text{mL/L} / 120\text{min} = 535 \text{ mL/min}$

To ensure a sufficient amount of oxygen is delivered to LS2 a 5-10 times excess should be considered, to overcome inefficiencies caused by transfer and solubility limitations. This would mean an airflow rate of 2.7L/min or 5.3L/min.

For experiment G2, a flow rate of 2.5L/min was used, a 4.7 times excess. Although it would be better to have a 10 times excess this would have lowered the temperature of LS2 too much, as even this rate depressed the temperature by 4C.

For experiment G3, almost pure oxygen (98%) gas was delivered at a flow rate of 2.5L/min. As this gas is approximately 98/21 times more concentrated than the air and the residence time was extended from 2 to 3 hours, the actual excess of oxygen delivered is close to x33.

Appendix 7D. Theoretical reduced species

An example calculation follows for determining the theoretical reduced species concentration for the exit PLS in experiment H2 (75 μ m, 2h, 95C), assuming a 1L volume of feed liquor and PLS:

$$\text{Feed CuFeS}_2 = 0.612\text{mol}$$

If copper extraction = 87%, then (assuming this is equivalent to CuFeS₂ extraction) the amount of reacted CuFeS₂ = $0.87 \times 0.612 = 0.532\text{mol}$

$$\begin{aligned} \text{The total reduced species produced via CuFeS}_2 \text{ leaching (i.e. 5mol per molCuFeS}_2) \\ = 5 \times 0.532\text{mol} = 2.66\text{mol} \end{aligned}$$

Based on 1L of feed liquor ($\text{Cu}^{2+} = 0.743 \text{ M}$; $\text{Fe}^{3+} = 1.431 \text{ M}$)

the theoretical total species would be

$$\begin{aligned} &= \text{Cu and Fe from CuFeS}_2 (0.532 \times 2) + \text{Cu and Fe in the feed } (0.743 + 1.431) \\ &= 3.24\text{M} \end{aligned}$$

Appendix 8 Mass balances for experimental accountability

Experiment H1									
Sample guide: LS1 = M, LS2 = N									
Cu and Fe Input									
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)		
Concentrate	6 x 135g	810.0	28.8	28.4		233.28	230.04		
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
Feed liquor	6 x 1L	6.0	47.8	76.72		286.56	460.32		
			Total Input			519.84	690.36		
							Input per 135g CuFeS2		
Cu and Fe Output							Cu =	38.88	g
Samples - balance solution reading with residue - record amounts (vol or wgt) and concentration							Fe=	38.34	g
							Extraction		
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	Cu %	Fe %
7N1S	bulk and sample	72.2	21	22.4767		15.16	16.23	61.0	57.7
7N2S	bulk and sample	46	19	24		8.74	11.04	77.5	71.2
7N3S	bulk and sample	51.3	16	20		8.21	10.26	78.9	73.2
7N4S	bulk and sample	73.8	16.8	18.4174		12.40	13.59	68.1	64.5
7N5S	bulk and sample	44.5	17.47	22.12		7.77	9.85	80.0	74.3
7M5S	bulk and sample	87.6	18	23		15.77	20.15	59.4	47.4
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
7M1	bulk and sample	0.84	65	95.1		54.60	79.88		
7M2	bulk and sample	0.74	86.04	113.77		63.67	84.19		
7M3	bulk and sample	0.82	71.83	98.14		58.90	80.47		
7M4	bulk and sample	0.88	76.9	107.6		67.67	94.69		
7M5	bulk and sample	1.19	74.09	101.69		88.17	121.01		
7N5	bulk and sample	1.13	54.06	85.19		61.09	96.26		
Wash		1.1	3.45	4.8		3.80	5.28		
A110	4x10mL	0.04							
Estimated loss from samples not analyzed (see box below)						23.58	34.84		
Total Vol PLS + samples + flocc			Total Output			489.52	677.74		
= 5.64									
						Total Expected Cu and Fe	519.84	690.36	
						in concentrate and solution			
						% Recovery	94.17	98.17	
** Note this includes the estimated copper and iron in samples not analyzed (see box below)									
Unaccounted for mass output:									
7M1-M4 residues = 33.2g									
7N1-4 solutions = 320mL									
Estimate additional mass of this output here:									
Estimate average LS1 residue Cu and Fe % (from7M5)									
Thus	Est %	Total g in 33.2g							
Cu	18	5.976							
Fe	23	7.636							
Estimate average LS2 liquor Cu and Fe g/L (from7N5)									
	Est g/L	Total g in 320mL							
Cu	55	17.6							
Fe	85	27.2							
Total extra output (g)									
Cu	23.576								
Fe	34.836								

Experiment H2									
Sample guide: LS1 = K, LS2 = L.									
Cu and Fe Input									
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)		
Concentrate	6 x 135g	810.0	28.8	28.4		233.28	230.04		
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
Feed liquor	6 x 1L	6.0	47.2	79.5		283.48	476.84		
			Total Input			516.76	706.88		
							Input per 135g CuFeS2		
Cu and Fe Output							Cu =	38.88 g	
							Fe=	38.34 g	
							Extraction		
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	Cu %	Fe %
9L1S	bulk and sample	56.98	17.00	19.61		9.69	11.18	75.1	70.9
9L2S	bulk and sample	34.8	13.41	15.81		4.67	5.50	88.0	85.7
9L3S	bulk and sample	53.13	11.52	14.98		6.12	7.96	84.3	79.2
9L4S	bulk and sample	40.9	7.62	11.10		3.12	4.54	92.0	88.2
9L5S	bulk and sample	62.6	8.13	12.44		5.09	7.79	86.9	79.7
9K1S	sample	5	16.16	19.72		0.81	0.99		
9K2S	sample	7.1	23.17	24.55		1.64	1.74		
9K3S	sample	5.2	16.28	19.11		0.85	0.99		
9K4S	sample	5.4	18.76	20.44		1.01	1.10		
9K5S	bulk and sample	79.3	17.85	19.57		14.16	15.52	63.6	59.5
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
9K1	bulk and sample	0.88	74.05	108.59		65.16	95.56		
9K2	bulk and sample	0.66	86.16	120.15		56.87	79.30		
9K3	bulk and sample	0.83	78.67	111.14		65.30	92.24		
9K4	bulk and sample	0.97	81.76	114.75		79.31	111.30		
9K5	bulk and sample	1.15	81.75	114.28		94.01	131.42		
9L1	sample	0.08	75.64	110.40		6.05	8.83		
9L2	sample	0.08	54.25	89.27		4.34	7.14		
9L3	sample	0.08	66.32	100.84		5.31	8.07		
9L4	sample	0.08	58.47	92.08		4.68	7.37		
9L5	bulk and sample	1.21	60.11	93.09		72.73	112.64		
Wash		3.1	4.17	6.35		12.91	19.67		
A110	4x10mL	0.04							
	Sum of volumes =	6.06	Total Output			513.82	730.85		
			Total Expected Cu and Fe			516.76	706.88		
			in concentrate and solution						
			% Recovery			99.43	103.39		

Experiment H3									
Sample guide: LS1 = C, LS2 = D.									
Cu and Fe Input									
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)		
Concentrate	7 x 135g	945.0	28.8	28.4		272.16	268.38		
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
Feed liquor	7 x 1L ¹	7.0	52.9	87.2		370.321	610.106		
			Total Input			642.48	878.49		
							Input per 135g CuFeS2		
Cu and Fe Output							Cu =	38.88 g	
							Fe=	38.34 g	
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	Extraction	
								Cu %	Fe %
11D1S	bulk and sample	55.8	20.61	22.68		11.50	12.65	70.4	67.0
11D2S	bulk and sample	49	17.66	20.36		8.65	9.98	77.7	74.0
11D3S	bulk and sample	50.5	14.29	17.98		7.22	9.08	81.4	76.3
11D4S	bulk and sample	44.8	15.22	19.31		6.82	8.65	82.5	77.4
11D5S	bulk and sample	49.9	12.76	17.00		6.37	8.48	83.6	77.9
11D6S	bulk and sample	57.7	11.32	16.24		6.53	9.37	83.2	75.6
11C1S	sample	4.2	19.44	22.30		0.82	0.94		
11C2S	sample	5.9	25.30	25.86		1.49	1.53		
11C3S	sample	4.9	19.93	22.34		0.98	1.09		
11C4S	sample	4.9	22.41	24.06		1.10	1.18		
11C5S	sample	4.9	19.03	21.22		0.93	1.04		
11C6S	bulk and sample	88.9	20.73	22.02		18.43	19.58	52.6	48.9
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
11C1	bulk and sample	0.83	74.03	110.70		61.44	91.88		
11C2	bulk and sample	0.75	90.71	130.22		68.03	97.67		
11C3	bulk and sample	0.91	78.88	116.05		71.78	105.60		
11C4	bulk and sample	0.87	85.34	123.39		74.25	107.35		
11C5	bulk and sample	0.85	54.54	123.83		46.36	105.26		
11C6	bulk and sample	1.09	86.28	125.09		94.04	136.34		
11D1	sample	0.08	76.16	112.14		6.09	8.97		
11D2	sample	0.08	57.72	93.34		4.62	7.47		
11D3	sample	0.08	66.56	105.49		5.32	8.44		
11D4	sample	0.08	61.37	96.52		4.91	7.72		
11D5	sample	0.08	64.75	102.70		5.18	8.22		
11D6	bulk and sample	1.08	63.03	100.70		68.07	108.75		
Wash		3.75	5.12	7.68		19.19	28.81		
A110	5x10mL	0.05							
	Sum of volumes =	6.83	Total Output			600.13	906.05		
	(just PLS+sample not inside LS1)								
			Total Expected Cu and Fe			642.48	878.49		
			in concentrate and solution						
				% Recovery		93.41	103.14		

Experiment H4									
Sample guide: LS1 = M; LS2 = N.									
Cu and Fe Input									
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)		
Concentrate	7 x 135g	945.0	28.8	28.4		272.16	268.38		
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
Feed liquor	7 x 1L	7.0	55.8	90.5		390.733	633.325		
			Total Input			662.89	901.71		
Cu and Fe Output							Input per 135g CuFeS2		
							Cu =	38.88	g
							Fe=	38.34	g
							Extraction		
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	Cu %	Fe %
12N1S	bulk and sample	42.7	13.32	18.37		5.69	7.85	85.4	79.5
12N2S	bulk and sample	35.9	7.10	12.84		2.55	4.61	93.4	88.0
12N3S	bulk and sample	48.5	8.71	14.97		4.22	7.26	89.1	81.1
12N4S	bulk and sample	40.6	5.78	12.39		2.35	5.03	94.0	86.9
12N5S	bulk and sample	46.9	7.31	13.80		3.43	6.47	91.2	83.1
12N6S	bulk and sample	45	6.14	12.48		2.76	5.61	92.9	85.4
12M1S	sample	3.4	13.34	17.38		0.45	0.59		
12M2S	sample	9.7	26.99	29.65		2.62	2.88		
12M3S	sample	4.2	16.67	19.61		0.70	0.82		
12M4S	sample	4.2	20.56	22.23		0.86	0.93		
12M5S	sample	4	17.59	20.06		0.70	0.80		
12M6S	bulk and sample	46.6	21.37	24.33		9.96	11.34	74.4	70.4
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
12M1	bulk and sample	0.81	86.46	122.65		70.04	99.35		
12M2	bulk and sample	0.66	102.52	133.30		67.66	87.98		
12M3	bulk and sample	0.85	91.95	125.08		78.16	106.32		
12M4	bulk and sample	0.9	93.27	125.93		83.94	113.34		
12M5	bulk and sample	0.92	91.94	125.02		84.58	115.02		
12M6	bulk and sample	1.1	94.59	127.92		104.05	140.71		
12N1	sample	0.08	88.81	129.48		7.10	10.36		
12N2	sample	0.08	66.13	103.07		5.29	8.25		
12N3	sample	0.08	76.59	113.30		6.13	9.06		
12N4	sample	0.08	68.18	104.11		5.45	8.33		
12N5	sample	0.08	72.88	107.89		5.83	8.63		
12N6	bulk and sample	1.2	68.09	102.95		81.70	123.53		
Wash		3.5	5.80	8.37		20.29	29.28		
A110	5x10mL	0.05							
	Sum of volumes =	6.89	Total Output			656.53	914.36		
	(just PLS+sample not inside LS1)								
			Total Expected Cu and Fe			662.89	901.71		
			in concentrate and solution						
			% Recovery			99.04	101.40		

Experiment H5									
Sample guide: LS1 = G, LS2 = H.									
Cu and Fe Input									
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)		
Concentrate	7 x 135g	945.0	28.5	28.7		269.19317	271.367		
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
Feed liquor	7 x 1L	7.0	45.0	75.8		314.979	530.509		
			Total Input			584.17	801.88		
								Input per 135g CuFeS2	
								Cu =	38.45617 g
								Fe=	38.76667 g
								Extraction	
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	Cu %	Fe %
13H1S	bulk and sample	46.6	11.61	16.01		5.41	7.46	85.9	80.7
13H2S	bulk and sample	15.2	1.40	7.73		0.21	1.17	99.4	97.0
13H3S	bulk and sample	26.8	3.56	9.87		0.95	2.65	97.5	93.2
13H4S	bulk and sample	36.8	0.94	7.65		0.35	2.81	99.1	92.7
13H5S	bulk and sample	49	2.50	8.59		1.23	4.21	96.8	89.1
13H6S	bulk and sample	40.9	1.96	8.50		0.80	3.48	97.9	91.0
13G1S	sample	4.6	11.83	15.87		0.54	0.73		
13G2S	sample	11.2	27.80	25.86		3.11	2.90		
13G3S	sample	6.6	18.31	20.66		1.21	1.36		
13G4S	sample	10	22.71	23.14		2.27	2.31		
13G5S	sample	6.5	22.23	23.44		1.45	1.52		
13G6S	bulk and sample	113.9	25.03	24.73		28.50	28.17	25.9	27.3
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
13G1	bulk and sample	0.83	77.84	106.69		64.61	88.56		
13G2	bulk and sample	0.67	80.44	114.40		53.89	76.65		
13G3	bulk and sample	0.83	81.18	110.75		67.38	91.92		
13G4	bulk and sample	0.83	82.79	111.76		68.71	92.76		
13G5	bulk and sample	0.83	85.15	115.20		70.67	95.62		
13G6	bulk and sample	1.28	86.08	118.04		110.18	151.09		
13H1	sample	0.08	79.68	109.12		6.37	8.73		
13H2	sample	0.08	57.19	85.11		4.58	6.81		
13H3	sample	0.08	77.43	105.87		6.19	8.47		
13H4	sample	0.08	59.86	87.60		4.79	7.01		
13H5	sample	0.08	76.45	106.07		6.12	8.49		
13H6	bulk and sample	1	71.08	100.25		71.08	100.25		
Wash			6.94	10.11		0.00	0.00		
A110	5x10mL	0.05							
	Sum of volumes =	6.72	Total Output			580.61	795.12		
	(just PLS+sample not inside LS1)								
			Total Expected Cu and Fe			584.17	801.88		
			in concentrate and solution						
			% Recovery			99.39	99.16		

Experiment H6									
Sample guide: LS1 = V, LS2 = W.									
Cu and Fe Input									
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)		
Concentrate	7 x 135g	945.0	28.5	28.7		269.19317	271.367		
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
Feed liquor	7 x 1L	7.0	41.1	70.2		287.602	491.54		
			Total Input			556.80	762.91		
Cu and Fe Output							Input per 135g CuFeS2		
							Cu =	38.45617 g	
							Fe=	38.76667 g	
							Extraction		
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	Cu %	Fe %
14W1S	bulk and sample	47.7	11.95	15.70		5.70	7.49	85.2	80.7
14W2S	bulk and sample	34.39	1.86	8.04		0.64	2.76	98.3	92.9
14W3S	bulk and sample	56.6	5.74	10.69		3.25	6.05	91.6	84.4
14W4S	bulk and sample	43.5	3.05	9.18		1.32	3.99	96.6	89.7
14W5S	bulk and sample	52	5.76	10.90		2.99	5.67	92.2	85.4
14W6S	bulk and sample	46.6	3.69	9.59		1.72	4.47	95.5	88.5
14V1S	sample	3.7	10.49	14.64		0.39	0.54		
14V2S	sample	10.9	27.32	25.22		2.98	2.75		
14V3S	sample	5.5	17.35	19.71		0.95	1.08		
14V4S	sample	8.6	25.99	25.05		2.24	2.15		
14V5S	sample	5.9	20.77	22.63		1.23	1.33		
14V6S	bulk and sample	100.1	25.21	24.76		25.23	24.79	34.4	36.1
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
14V1	bulk and sample	0.83	72.09	102.26		59.83	84.87		
14V2	bulk and sample	0.62	75.13	107.06		46.58	66.38		
14V3	bulk and sample	0.86	76.37	106.26		65.68	91.39		
14V4	bulk and sample	0.82	73.47	98.22		60.25	80.54		
14V5	bulk and sample	0.89	72.17	99.42		64.23	88.48		
14V6	bulk and sample	1.13	75.27	103.88		85.05	117.38		
14W1	sample	0.08	73.27	99.84		5.86	7.99		
14W2	sample	0.08	52.77	79.11		4.22	6.33		
14W3	sample	0.08	68.29	91.97		5.46	7.36		
14W4	sample	0.08	57.37	85.08		4.59	6.81		
14W5	sample	0.08	64.54	92.00		5.16	7.36		
14W6	bulk and sample	1.23	60.76	87.44		74.74	107.55		
Wash		3.6	5.92	8.33		21.33	29.99		
A110	2x5mL+3x10mL	0.04							
	Sum of volumes =	6.820	Total Output			551.63	765.49		
	(just PLS+sample not inside LS1)								
			Total Expected Cu and Fe			556.80	762.91		
			in concentrate and solution						
			% Recovery			99.07	100.34		

Experiment H7									
sample guide: LS1 = S, LS2 = T.									
Cu and Fe Input									
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)		
Concentrate	7 x 135g	945.0	28.5	28.7		269.19317	271.367		
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
Feed liquor	7 x 1L	7.0	47.7	80.1		333.97	560.826		
			Total Input			603.16	832.19		
							Input per 135g CuFeS2		
							Cu =	38.45617	g
							Fe=	38.76667	g
							Extraction		
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	Cu %	Fe %
15T1	bulk and sample	54.1	11.73	15.58		6.35	8.43	83.5	78.3
15T2	bulk and sample	37.4	2.84	8.36		1.06	3.13	97.2	91.9
15T3	bulk and sample	59.1	7.60	12.35		4.49	7.30	88.3	81.2
15T4	bulk and sample	38.8	3.80	10.52		1.48	4.08	96.2	89.5
15T5	bulk and sample	43.3	7.79	12.72		3.37	5.51	91.2	85.8
15T6	bulk and sample	43	4.03	10.20		1.73	4.39	95.5	88.7
15S1	sample	3.6	11.06	15.29		0.40	0.55		
15S2	sample	9.2	26.99	25.72		2.48	2.37		
15S3	sample	5.5	16.07	18.66		0.88	1.03		
15S4	sample	6	23.98	24.49		1.44	1.47		
15S5	sample	5.3	18.68	20.45		0.99	1.08		
15S6	bulk and sample	71.5	20.65	21.77		14.76	15.57	61.6	59.8
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
15S1	bulk and sample	0.85	79.08	112.11		67.22	95.30		
15S2	bulk and sample	0.53	84.58	117.90		44.83	62.49		
15S3	bulk and sample	0.68	81.47	114.83		55.40	78.08		
15S4	bulk and sample	0.89	87.66	121.39		78.01	108.04		
15S5	bulk and sample	0.78	85.25	117.55		66.49	91.69		
15S6	bulk and sample	1.2	81.10	112.93		97.32	135.52		
15T1	sample	0.08	79.81	113.13		6.39	9.05		
15T2	sample	0.08	55.91	88.41		4.47	7.07		
15T3	sample	0.08	74.05	107.17		5.92	8.57		
15T4	sample	0.08	61.99	94.96		4.96	7.60		
15T5	sample	0.08	67.27	100.44		5.38	8.04		
15T6	bulk and sample	1.2	65.42	96.92		78.51	116.30		
Wash		4	5.64	7.93		22.57	31.73		
A110	5x10mL	0.05							
	Sum of volumes =	6.580	Total Output			576.91	814.36		
	(just PLS+sample not inside LS1)								
			Total Expected Cu and Fe			603.16	832.19		
			in concentrate and solution						
			% Recovery			95.65	97.86		

Experiment H8									
Sample guide: LS1 = X, LS2 = Y.									
Cu and Fe Input									
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)		
Concentrate	7 x 135g	945.0	28.5	28.7		269.19317	271.367		
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
Feed liquor	7 x 1L	7.0	48.0	75.3		336.105	526.792		
			Total Input			605.30	798.16		
Cu and Fe Output							Input per 135g CuFeS2		
							Cu =	38.45617	g
							Fe=	38.76667	g
							Extraction		
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	Cu %	Fe %
16Y1	bulk and sample	54.8	14.68	18.53		8.05	10.16	79.1	73.8
16Y2	bulk and sample	43.3	6.66	12.02		2.88	5.21	92.5	86.6
16Y3	bulk and sample	68.3	10.12	14.49		6.91	9.90	82.0	74.5
16Y4	bulk and sample	47.3	6.94	13.35		3.28	6.31	91.5	83.7
16Y5	bulk and sample	49	9.36	14.44		4.58	7.08	88.1	81.7
16Y6	bulk and sample	49.1	7.85	13.36		3.85	6.56	90.0	83.1
16X1	sample	4.6	14.60	18.26		0.67	0.84		
16X2	sample	8.4	26.36	27.31		2.21	2.29		
16X3	sample	5.8	18.57	21.71		1.08	1.26		
16X4	sample	7.1	23.13	24.72		1.64	1.75		
16X5	sample	6.7	21.58	23.69		1.45	1.59		
16X6	bulk and sample	87	23.02	24.93		20.03	21.69	47.9	44.1
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
16X1	bulk and sample	0.82	76.62	104.92		62.83	86.03		
16X2	bulk and sample	0.67	81.63	109.15		54.69	73.13		
16X3	bulk and sample	0.8	78.90	104.68		63.12	83.74		
16X4	bulk and sample	0.81	81.20	107.60		65.77	87.16		
16X5	bulk and sample	0.8	80.58	107.48		64.46	85.98		
16X6	bulk and sample	1.04	80.44	106.45		83.66	110.71		
16Y1	sample	0.08	76.48	104.64		6.12	8.37		
16Y2	sample	0.08	56.55	83.30		4.52	6.66		
16Y3	sample	0.08	68.52	93.92		5.48	7.51		
16Y4	sample	0.08	61.31	88.36		4.90	7.07		
16Y5	sample	0.08	66.49	92.02		5.32	7.36		
16Y6	bulk and sample	1.25	63.82	91.53		79.77	114.41		
Wash		3.85	5.76	8.03		22.18	30.90		
A110	2x10mL+3x15mL	0.065							
	Sum of volumes =	6.655	Total Output			579.46	783.68		
	(just PLS+sample not inside LS1)								
			Total Expected Cu and Fe			605.30	798.16		
			in concentrate and solution						
			% Recovery			95.73	98.19		

Experiment H9									
Sample guide: LS1 = A, LS2 = B.									
Cu and Fe Input									
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)		
Concentrate	7 x 135g	945.0	26.8	26.8		252.86499	253.569		
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
Feed liquor	7 x 1L	7.0	50.6	82.0		354.0228	573.806		
			Total Input			606.89	827.38		
							Input per 135g CuFeS2		
							Cu =	36.12357	g
							Fe=	36.22415	g
							Extraction		
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	Cu %	Fe %
18B1	bulk and sample	70.1	0.67	28.18		0.47	19.75	98.7	45.5
18B2	bulk and sample	63.5	0.40	29.42		0.25	18.68	99.3	48.4
18B3	bulk and sample	59.1	0.57	28.83		0.34	17.04	99.1	53.0
18B4	bulk and sample	65.8	0.51	28.00		0.34	18.42	99.1	49.1
18B5	bulk and sample	74.3	1.46	28.62		1.09	21.27	97.0	41.3
18B6	bulk and sample	68.6	1.09	27.47		0.75	18.85	97.9	48.0
18A1	sample	5.6	0.67	29.05		0.04	1.63		
18A2	sample	9.1	14.10	30.14		1.28	2.74		
18A3	sample	5.9	0.86	28.58		0.05	1.69		
18A4	sample	7.2	5.34	29.71		0.38	2.14		
18A5	sample	6	2.14	28.09		0.13	1.69		
18A6	bulk and sample	76.3	2.07	28.26		1.58	21.56	95.6	40.5
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
18A1	bulk and sample	0.82	86.81	96.35		71.19	79.00		
18A2	bulk and sample	0.68	106.80	104.54		72.62	71.09		
18A3	bulk and sample	0.88	90.53	102.09		79.66	89.84		
18A4	bulk and sample	0.78	99.81	104.71		77.85	81.67		
18A5	bulk and sample	0.9	88.23	100.93		79.41	90.84		
18A6	bulk and sample	0.98	91.68	100.48		89.84	98.47		
18B1	sample	0.08	87.20	100.22		6.98	8.02		
18B2	sample	0.08	55.59	86.74		4.45	6.94		
18B3	sample	0.08	68.29	90.82		5.46	7.27		
18B4	sample	0.08	55.46	83.54		4.44	6.68		
18B5	sample	0.08	61.38	91.45		4.91	7.32		
18B6	bulk and sample	1.1	55.13	84.91		60.65	93.40		
Wash		4.9	2.97	3.92		14.55	19.22		
A110	5x15mL	0.075							
	Sum of volumes =	6.615	Total Output			578.70	805.21		
	(just PLS+sample not inside LS1)								
			Total Expected Cu and Fe			606.89	827.38		
			in concentrate and solution						
				% Recovery		95.36	97.32		

Experiment G1									
Sample guide: LS1 = P, LS2 = Q									
Cu and Fe Input									
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)		
Concentrate	6 x 135g	810.0	28.8	28.4		233.28	230.04		
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
Feed liquor	6 x 1L	6.0	54.1	35.0		324.35379	209.821		
			Total Input			557.63	439.86		
Cu and Fe Output							Input per 135g CuFeS ₂		
							Cu =	38.88 g	
							Fe =	38.34 g	
							Extraction		
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	Cu %	Fe %
8Q1S	bulk and sample	90.8	15.89	31.72		14.43	28.80	62.9	24.9
8Q2S	bulk and sample	60.8	11.38	32.28		6.92	19.62	82.2	48.8
8Q3S	bulk and sample	97.1	13.99	31.27		13.58	30.37	65.1	20.8
8Q4S	bulk and sample	102.8	14.32	30.32		14.72	31.17	62.1	18.7
8Q5S	bulk and sample	112.4	13.87	29.80		15.59	33.49	59.9	12.6
8P1S	sample	5	24.32	24.72		1.22	1.24		
8P2S	sample	7.3	26.69	27.14		1.95	1.98		
8P3S	sample	6.4	25.81	26.81		1.65	1.72		
8P4S	sample	5	26.42	27.33		1.32	1.37		
8P5S	bulk and sample	90.4	25.49	25.42		23.05	22.98	40.7	40.1
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
8P1	bulk and sample	0.85	62.66	41.61		53.26	35.37		
8P2	bulk and sample	0.68	71.25	34.34		48.45	23.35		
8P3	bulk and sample	0.78	69.05	35.45		53.86	27.65		
8P4	bulk and sample	0.93	68.54	35.02		63.74	32.57		
8P5	bulk and sample	1.05	51.99	25.36		54.59	26.63		
8Q1	sample	0.08	71.22	31.62		5.70	2.53		
8Q2	sample	0.08	60.23	27.78		4.82	2.22		
8Q3	sample	0.08	69.10	32.34		5.53	2.59		
8Q4	sample	0.08	68.77	31.45		5.50	2.52		
8Q5	bulk and sample	1.18	67.32	29.55		79.43	34.87		
Wash		3.57	6.05	4.27		21.61	15.25		
	SUM of volumes=	5.79	Total Output			490.92	378.29		
			Total Expected Cu and Fe in concentrate and solution			557.63	439.86		
			% Recovery			88.04	86.00		

Experiment G2								
Sample guide: LS1 = J, LS2 = K.								
Cu and Fe Input								
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	
Concentrate	6 x 135g	810.0	28.8	28.4		233.28	230.04	
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)	
Feed liquor	6 x 1L	6.0	55.9	34.5		335.304	207.036	
			Total Input			568.58	437.08	
Cu and Fe Output							Input per 135g CuFeS ₂	
							Cu =	38.88 g
							Fe =	38.34 g
							Extraction	
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	
10K1S	bulk and sample	102.2	16.25	26.60		16.61	27.18	
10K2S	bulk and sample	56.6	12.95	20.83		7.33	11.79	
10K3S	bulk and sample	35.5	10.25	21.51		3.64	7.64	
10K4S	bulk and sample	80.3	15.82	23.10		12.70	18.55	
10K5S	bulk and sample	77.8	16.55	23.17		12.87	18.03	
10J1S	sample	6.1	24.31	23.01		1.48	1.40	
10J2S	sample	9.4	30.30	27.78		2.85	2.61	
10J3S	sample	16.7	25.89	26.12		4.32	4.36	
10J4S	sample	8.4	26.90	25.30		2.26	2.12	
10J5S	bulk and sample	92.9	29.10	26.85		27.03	24.95	
							30.5	34.9
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)	
10J1	bulk and sample	0.81	77.40	55.10		62.69	44.63	
10J2	bulk and sample	0.68	89.69	56.47		60.99	38.40	
10J3	bulk and sample	0.88	84.79	56.65		74.62	49.85	
10J4	bulk and sample	0.85	85.73	55.56		72.87	47.22	
10J5	bulk and sample	1.08	87.95	59.73		94.98	64.51	
10K1	sample	0.08	87.00	51.25		6.96	4.10	
10K2	sample	0.08	71.71	44.89		5.74	3.59	
10K3	sample	0.08	78.14	48.42		6.25	3.87	
10K4	sample	0.08	75.67	48.43		6.05	3.87	
10K5	bulk and sample	1.08	76.74	48.48		82.87	52.35	
Wash		3.1	5.91	4.51		18.33	13.99	
A110	4x10mL	0.04						
	Sum of volumes =	5.74	Total Output			583.45	445.02	
	(just PLS+sample - not inside LS1)							
			Total Expected Cu and Fe			568.58	437.08	
			in concentrate and solution					
			% Recovery			102.61	101.82	

Experiment G3									
Sample guide: LS1 = K, LS2 = L.									
Cu and Fe Input									
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)		
Concentrate	7 x 135g	945.0	28.5	28.7		269.325	271.215		
Solution		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
Feed liquor	7 x 1L	7.0	47.4	30.0		332.045	209.825		
			Total Input			601.37	481.04		
							Input per 135g CuFeS2		
							Cu =	38.475	g
							Fe=	38.745	g
							Extraction		
Solids	Description	Wgt (g)	Cu (%)	Fe (%)		Cu (g)	Fe (g)	Cu %	Fe %
17L1	bulk and sample	134.6	1.35	43.24		1.81	58.20	95.3	-50.2
17L2	bulk and sample	112.9	2.88	40.79		3.25	46.06	91.6	-18.9
17L3	bulk and sample	136.9	2.59	43.52		3.55	59.58	90.8	-53.8
17L4	bulk and sample	116.3	3.72	40.04		4.33	46.57	88.8	-20.2
17L5	bulk and sample	104.5	3.93	40.12		4.10	41.93	89.3	-8.2
17L6	bulk and sample	108.2	4.04	38.42		4.37	41.57	88.6	-7.3
17K1	sample	7.1	23.40	26.11		1.66	1.85		
17K2	sample	13.7	27.14	28.12		3.72	3.85		
17K3	sample	8	25.18	26.84		2.01	2.15		
17K4	sample	7.9	25.51	27.01		2.02	2.13		
17K5	sample	8.7	24.90	26.59		2.17	2.31		
17K6	bulk and sample	88.2	24.49	26.54		21.60	23.40	43.9	39.6
Solutions		Vol (L)	[Cu] (g/L)	[Fe] (g/L)		Cu (g)	Fe (g)		
17K1	bulk and sample	0.825	60.65	42.46		50.04	35.03		
17K2	bulk and sample	0.39	107.42	15.95		41.89	6.22		
17K3	bulk and sample	0.72	91.27	25.95		65.72	18.68		
17K4	bulk and sample	0.74	97.26	20.29		71.97	15.02		
17K5	bulk and sample	0.755	95.46	24.44		72.07	18.45		
17K6	bulk and sample	0.8	93.91	26.18		75.13	20.94		
17L1	sample	0.08	98.58	0.11		7.89	0.01		
17L2	sample	0.08	71.62	10.75		5.73	0.86		
17L3	sample	0.08	86.55	5.52		6.92	0.44		
17L4	sample	0.08	79.09	9.00		6.33	0.72		
17L5	sample	0.08	76.75	9.70		6.14	0.78		
17L6	bulk and sample	0.89	79.33	11.34		70.61	10.09		
Wash		6	9.42	1.06		56.50	6.38		
A110	5x15mL	0.075							
	Sum of volumes =	5.595	Total Output			591.51	463.23		
	(just PLS+sample not inside LS1)								
			Total Expected Cu and Fe			601.37	481.04		
			in concentrate and solution						
			% Recovery			98.36	96.30		

Appendix 9 Experimental Profiles

Experiment H1: Coarse Antamina concentrate, 85C, 2h per leach stage

Experiment H2: Coarse Antamina concentrate, 95C, 2h per leach stage

Experiment H3: Coarse Antamina concentrate, 85C, 3h per leach stage

Experiment H4: Coarse Antamina concentrate, 95C, 3h per leach stage

Experiment H5: Fine grind Antamina concentrate, 95C, 3h per leach stage

Experiment H6: Fine grind Antamina concentrate, 95C, 2h per leach stage

Experiment H7: Fine grind Antamina concentrate, 85C, 3h per leach stage

Experiment H8: Fine grind Antamina concentrate, 85C, 2h per leach stage

Experiment H9: Fine grind Rosario concentrate, 95C, 3h per leach stage

Experiment G1: Air to LS2 (200ml/min), Coarse Antamina concentrate, 85C, 2h per leach stage

Experiment G2: Air to LS2 (2.5L/min), Coarse Antamina concentrate, 95C, 2h per leach stage

Experiment G3: O₂ to LS2 (2.5L/min), Fine grind Antamina concentrate, 95C, 3h per leach stage